

TEST REPORT

APPLICANT

: Mid Ocean Hong Kong Ltd.

ADDRESS: 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan,
Kowloon, Hong Kong.**SAMPLE DESCRIPTION**

: JUTE DOORMAT WITH ANTI SLIP

ITEM NO.

: MO2064

SAMPLE RECEIVED DATE

: 06-May-2023

TURN AROUND TIME

: 06-May-2023 to 16-May-2023

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Total Cadmium Content	REACH Annex XVII, Entry 23	Pass
Total Lead Content	REACH Annex XVII, Entry 63	Pass
Phthalates Content	REACH Annex XVII, Entry 51 & 52	Pass
Polycyclic Aromatic Hydrocarbons (PAHs)	REACH Annex XVII, Entry 50	Pass
Banned AZO Dyes	REACH Annex XVII, Entry 43	Pass
Formaldehyde Release	EN 717-3-1996	Pass
Colour Fastness to Rubbing	EN ISO 105-X12:2016	Pass

Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@eurofins.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to chinacomplaint@eurofins.com and referring to this report number.



Eurofins (Shanghai) contact information**Customer service:** SunnyZhang@eurofins.com/ +86 216 1819 181**Sales specialist:** Jack.Zhang@cpt.eurofinscn.com/ +86 216 1819 181

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****


Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd



Joyce Liu
Operation Director



SAMPLE PHOTO(S)



A

EFSH23050231-CG-01

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Sample No.
1	Brown mesh fabric with black foam	A
2	Brown threads (piping)	A

TO BE CONTINUED

TEST RESULT

Total Cadmium Content

Test Request: Total cadmium content as specified in Commission Regulation (EU) 2016/217 amending entry 23 of Annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: EPA 3050B:1996, EPA 3052:1996, EN 1122:2001 Method B, acid digestion method was used and total cadmium content was determined by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result	
				1	2
Cadmium (Cd)	mg/kg	100	5	11	11

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

Total Lead Content

Test Request: Total lead content as specified in entry 63 of annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 2015/628.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996, acid digestion/ microwave digestion method was used, analysis was performed by ICP-OES.

Test Item(s)	Unit	Limit	MDL	Result	
				1	2
Lead (Pb)	mg/kg	500	10	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Phthalates Content

Test Request: Phthalates content as specified in entry 51&52 of annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Commission Regulation (EU) 2018/2005.

Test Method: EPA 3550C:2007, EPA 8270E:2018, solvent extraction and quantification by GC-MS.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					1
Di-n-butyl phthalate (DBP)	84-74-2	%	-	0.005	ND
Benzylbutyl phthalate (BBP)	85-68-7	%	-	0.005	ND
Diethylhexyl phthalate (DEHP)	117-81-7	%	-	0.005	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	-	0.005	ND
Sum of DEHP, DBP, BBP, DIBP	-	%	0.1	-	ND
Di-n-octyl phthalate (DNOP)	117-84-0	%	-	0.005	ND
Diisononyl phthalate (DINP)	28553-12-0	%	-	0.005	ND
Diisodecyl phthalate (DIDP)	26761-40-0	%	-	0.005	ND
Sum of DNOP, DINP, DIDP	-	%	0.1	-	ND

Remarks:

MDL = method detection limit

ND = Not detected, less than MDL

"-"= Not Regulated

TO BE CONTINUED

TEST RESULT

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Request: Polycyclic Aromatic Hydrocarbons (PAHs) content as specified in entry 50 of Annex XVII of REACH Regulation (EC) No 1907/2006 and its latest amendment.

Test Method: Solvent extraction and quantification by gas chromatography-mass selective detection (GC-MS) with respect to AfPS GS 2019:01 PAK

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					1
Benzo(a)anthracene	56-55-3	mg/kg	1	0.1	ND
Chrysene	218-01-9	mg/kg	1	0.1	ND
Benzo(b)fluoranthene	205-99-2	mg/kg	1	0.1	ND
Benzo(j)fluoranthene	205-82-3	mg/kg	1	0.1	ND
Benzo(k)fluoranthene	207-08-9	mg/kg	1	0.1	ND
Benzo(a)pyrene	50-32-8	mg/kg	1	0.1	ND
Dibenzo(a,h)anthracene	53-70-3	mg/kg	1	0.1	ND
Benzo(e)pyrene	192-97-2	mg/kg	1	0.1	ND

Remarks:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Banned AZO Dyes

Test Request: Banned AZO dyes as specified in entry 43 of annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: EN ISO 14362-1:2017, sampling procedure and sample preparation according to Annex E4.2 and Annex E4.3.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result	
					1	2
4-methyl-m-phenylenediamine	95-80-7	mg/kg	30	5	ND	ND
4-Amino-azobenzene (Note 2)	60-09-3	mg/kg	30	5	ND	ND
2-Naphthylamine	91-59-8	mg/kg	30	5	ND	ND
4,4'-methylenedi-o-toluidine	838-88-0	mg/kg	30	5	ND	ND
Bis-(4-aminophenyl)methane	101-77-9	mg/kg	30	5	ND	ND
4,4'-Oxydianiline	101-80-4	mg/kg	30	5	ND	ND
4,4'-Thiodianiline	139-65-1	mg/kg	30	5	ND	ND
Benzidine	92-87-5	mg/kg	30	5	ND	ND
o-Toluidine	95-53-4	mg/kg	30	5	ND	ND
5-Nitro-o-toluidine (Note 1)	99-55-8	mg/kg	30	5	ND	ND
4-methoxy-m-phenylenediamine	615-05-4	mg/kg	30	5	ND	ND
4,4'-Methylene-bis-(2-chloroaniline)	101-14-4	mg/kg	30	5	ND	ND
o-Aminoazotoluene (Note 1)	97-56-3	mg/kg	30	5	ND	ND
2,4,5-Trimethylaniline	137-17-7	mg/kg	30	5	ND	ND
4-Aminobiphenyl	92-67-1	mg/kg	30	5	ND	ND
o-Anisidine	90-04-0	mg/kg	30	5	ND	ND
3,3'-Dichlorobenzidine	91-94-1	mg/kg	30	5	ND	ND
4-Chloroaniline	106-47-8	mg/kg	30	5	ND	ND
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	30	5	ND	ND
n.d.3,3'-Dimethoxybenzidine	119-93-7	mg/kg	30	5	ND	ND
2-Methoxy-5-methylaniline	120-71-8	mg/kg	30	5	ND	ND
4-Chloro-2-methylaniline	95-69-2	mg/kg	30	5	ND	ND

Remarks:

Note 1: The CAS-numbers 97-56-3 and 99-55-8 are further reduced to CAS-numbers 95-53-4 and 95-80-7.

Note 2: 4-Amino-azobenzene(CAS No.:60-09-3) is reduced to aniline and 1,4-phenylenediamine.

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

TO BE CONTINUED

TEST RESULT

Formaldehyde Release

Test Request: Formaldehyde content as per client's request

Test Method: EN 717-3-1996, formaldehyde release was determined by UV-Visible Spectrophotometer (UV-Vis) analysis.

Test Item(s)	CAS No.	Unit	Limit	MDL	Result
					1
Formaldehyde Release	50-00-0	mg/kg	80	5	19

Remarks:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

Colour Fastness to Rubbing

EN ISO 105-X12:2016.

	(1)	(2)	Requirement:
Lengthwise-Dry	4-5	4-5	2-3
Lengthwise-Wet	4-5	4-5	2-3
Widthwise-Dry	4-5	/	2-3
Widthwise-Wet	4-5	/	2-3

Remark:

Grey Scale for Assessing Colour Change/Staining

Grade 5 Negligible or no change/staining

Grade 4 Slightly changed/stained

Grade 3 Noticeably changed/stained

Grade 2 Considerably changed/stained

Grade 1 Much changed/stained

The test was subcontracted to Eurofins Product Testing Service (Shanghai) Co., Ltd. Hangzhou Branch.

END OF THE REPORT