

Test Report

Report No. : AGC05443240414-001

SAMPLE NAME : Emergency hammer

MODEL NAME : MO2357

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : May 28, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V

Report No.: AGC05443240414-001

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Emergency hammer

Model : MO2357
Vendor code : 115205
Country of Origin : CHINA
Country of Destination : EUROPE
Sample Received Date : Apr. 11, 2024

Testing Period : Apr. 11, 2024 to May 27, 2024

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863 - Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43

- Aromatic Amines Azodyes (AZO) Content

Pass

- Color fastness to rubbing Pass

Approved by: Leon

Suhongliang, Leon

Technical Director



May 28, 2024

Valid


		Report Revise Record	
Report Version	Issued Date	Valid Version	Notes


Report No.: AGC05443240414-001


Initial release




The photo of the sample











































The photo of AGC05443240414-001 is for use only with the original report.





Test point	Test module	Test parts	Test point description
MO2357			
1			Transparent plastic lampshade
2			Plastic reflective bowl with silver electroplated coating
3		Outer shell	Silver coating
4			Black plastic shell
5			Black metallic shell
6			Black sling
7		Sling	Black plastic buckle
8			Black string
9			Silver metal hammer
10			Metal blade
11			Milk white silicone keypad
12			Milk white plastic ring
13			Silver screw
14			Chip LED
15			Metal aluminum plate
16		٦	Solder
17		Lamp board	Red wire jacket
18			White wire jacket
19			Conductor
20			Yellow wick
21			Metal aluminum plate
22		-	Solder
23		Lamp board	Black wire jacket
24			Red wire jacket
25			Conductor
26			Micro metal plug
27		Micro plug	Grey plastic plug
28			Metal pin
29			Black plastic button
30			Metallic shell
31		Key	Metallic shrapnel
32	Circuit board		Black plastic base
33	7		Chip resistor
34	7		Chip triode
35	7		IC body
36	7		Metallic pin with solder
37	7		PCB
38			Solder
39		D	Black foam
40		Battery	White plastic sheet



			110001110110003113210111 001
41			Green bushing
42			Solder
43			Black wire jacket
44			White wire jacket
45			Conductor
USB cable	•		
46			USB metal plug
47		<u> </u>	White plastic plug
48			Metal pin
49			Black handle
50			Solder
51			Micro metal plug
52			Grey plastic plug
53		Micro plug	Metal pin
54			Metallic pogopin
55			Solder
56			Black outer wire jacket
57		W: 1	Black wire jacket
58		Wire rod	Red wire jacket
59			Conductor
1+4+7			Transparent plastic lampshade+Black plastic shell+Black plastic buckle
49+56			Black handle+Black outer wire jacket
6+8			Black sling+ Black string

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method		•	
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-0 Conclusion
]	Pb	BL	/	
		Cd	BL	/	
		Нg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
]	Pb	BL	/	
Ţ		Cd	BL	/	
	I	Нg	BL	/	
		Cr ⁶⁺)	BL	/	
2	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
ļ		Cd	BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
4	Br PBBs PBDEs		BL	/	Conformity
-	D	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	-



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-00
	I	Pb	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
5	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
_		ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		łg	BL	/	
		Cr ⁶⁺)	BL	/	
6	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Нд		BL	/	
	$Cr(Cr^{6+})$		BL	/	
7	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
8	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	Di	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-00
]	Pb	BL	/	
	(Cd	BL	/	
	I	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
9	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
			BL	/	
			BL	/	
		Cr ⁶⁺)	IN	N.D.	
10		PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
11	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
12	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	D.	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
<u> </u>		ЕНР	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr ⁶⁺)	BL	/	
13	Br	PBBs PBDEs	N/A	/	Conformity
-	D	IBP	N/A	/	
)BP	N/A	/	
-		BP	N/A	/	
		EHP	N/A	/	
		 Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
14		PBBs PBDEs	BL	/	Conformity
-	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
-	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
-	Hg		BL	/	
-	$Cr(Cr^{6+})$		BL	/	
15	Br	PBBs PBDEs	N/A	/	Conformity
-	D	IBP	N/A	/	
-)BP	N/A	/	
		BP	N/A	/	
	DEHP		N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
ļ		(Cr ⁶⁺)	BL	/	
16	Br PBBs PBDEs		N/A	/	Conformity
}	ח	IBP	N/A	/	
-		BP	N/A	/	
		BP	N/A	/	
}				,	
	DEHP		N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-0
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
17	Br	PBBs PBDEs	BL	/	Conformity
	Γ	OIBP	N/A	N.D.	
		OBP	N/A	57	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/ /	
		Cd	BL	/	
-		Hg	BL	/	
-		(Cr ⁶⁺)	BL	/	
-	CI		DL	/	
18	Br Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	1
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
19	Br	PBBs PBDEs	N/A	/	Conformity
	Γ	OIBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
		EHP	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
			BL	/	
-		Hg (Cr ⁶⁺)	BL	/	
-	Cr	PBBs	DL	/	
20	Br	PBDEs	BL	/	Conformity
-	Г	OIBP	N/A	N.D.	
-					
-		OBP OBD	N/A	N.D.	
		BBP	N/A	N.D.	
	DEHP		N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-0 Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr^{6+})	BL	/	
21	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
		ЕНР	N/A	/	
	:	Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
		(Cr^{6+})	BL	/	
22	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
]	Hg	BL	/	
	$Cr(Cr^{6+})$		BL	/	
23	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	99	
	DBP		N/A	121	
	BBP		N/A	N.D.	
		ЕНР	N/A	N.D.	1
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
24	Br PBBs PBDEs		BL	/	Conformity
-	D	IBP	N/A	86	
-)BP	N/A	103	
-		BBP	N/A	N.D.	
-		EHP	N/A	N.D.	-

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Web: http://www.agccert.com/



Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-0 Conclusion
	Pb	BL	/	
	Cd	BL	/	
		BL	/	
Cr(Cr ⁶⁺)	BL	/	
Br	PBBs PBDEs	N/A	/	Conformity
D		N/A	/	
			/	
			/	
		N/A	/	
	Pb	BL	/	
		BL	/	
]	Hg	BL	/	
		BL	/	
Br	PBBs	N/A	/	Conformity
		N/A	/	
			/	
			/	
DEHP			/	
			/	
			/	
		BL	/	
			/	
Br	PBBs	BL	/	Conformity
D		N/A	N.D.	
			/	
			/	
]	Hg		/	
		BL	/	
PBBs PBBs		N/A	/	Conformity
D		N/A	/	
			/	
			/	
		N/A	/	-
	Cr(Br Dr Cr(Br Cr(Cr(Br Cr(Cr	$ \begin{array}{c c} & Pb \\ \hline & Cd \\ \hline & Hg \\ \hline & Cr(Cr^{6+}) \\ \hline & Br & PBBs \\ \hline & PBDEs \\ \hline & DBP \\ \hline & DBP \\ \hline & DBP \\ \hline & DBP \\ \hline & DEHP \\ \hline & Pb \\ \hline & Cd \\ \hline & Hg \\ \hline & Cr(Cr^{6+}) \\ \hline & Br & PBBs \\ \hline & PBBs \\ \hline & PBDEs \\ \hline & DIBP \\ \hline & DBP \\ \hline & DBP \\ \hline & DBP \\ \hline & DBP \\ \hline & PBBs \\ \hline & PBDEs \\ \hline & DEHP \\ \hline & Pb \\ \hline & Cd \\ \hline & Hg \\ \hline & Cr(Cr^{6+}) \\ \hline & Br & PBBs \\ \hline & PBDEs \\ \hline & DIBP \\ \hline & DBP \\ \hline$	Test Item Spectrometry (XRF) mg/kg Pb BL Cd BL BL BL Cr(Cr ⁶⁺) BL Br PBBs PBBs PM/A PBDEs N/A DBP N/A BBP N/A DEHP N/A Pb BL Cd BL Br PBBs PBDEs N/A DIBP N/A DBP N/A DBP N/A DBP N/A DBP N/A DBP N/A BBP N/A DEHP N/A BL BL Cr(Cr ⁶⁺) BL BB BL DIBP N/A DBP N/A DBP N/A BBL BL Cd BL BL BL Cd BL BB	Test Item



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	P b	BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
20		PBBs	DI	/	
29	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	B	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	P b	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
		PBBs		/	
30	Br	PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
31	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		Pb	BL	/	
-		Cd Cd	BL	/	
-	Hg		BL	/	
-		Cr^{6+})	BL	/	
32	Br	PBBs	BL	/	Conformity
<u> </u>	וח	PBDEs	NT/A	·	
<u> </u>		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
	DE	EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion	
	Pb		BL	/		
		Cd	BL	/		
		Hg	BL	/		
		(Cr^{6+})	BL	/		
33	Br	PBBs	BL	/	Conformity	
		PBDEs		/	J	
		IBP	N/A	N.D.		
		DBP	N/A	N.D.		
		BBP	N/A	N.D.		
		EHP	N/A	N.D.		
		Pb	BL	/		
		Cd	BL	/		
		Hg	BL	/		
	Cr	(Cr^{6+})	BL	/		
34	Br	PBBs PBDEs	BL	/	Conformity	
	DIBP		N/A	N.D.		
	DBP		N/A	N.D.		
	BBP		N/A	N.D.		
	DEHP		N/A	N.D.		
	Pb		BL	/		
	Cd		BL	/		
	Hg		BL	/		
	$Cr(Cr^{6+})$		BL	/		
35	Br	PBBs	BL	/	Conformity	
_		PBDEs	NT/A	,		
-		IBP	N/A	N.D.		
_		OBP OBP	N/A	N.D.		
-		BBP	N/A	N.D.		
		EHP	N/A	N.D.		
_		Pb	BL	/		
_		Cd	BL	/		
_		Hg	BL	/		
	Cr	(Cr^{6+})	BL	/		
36	Br PBBs		N/A	/	Conformity	
		PBDEs		/	Comorning	
_		IBP	N/A	/		
<u> </u>)BP	N/A	/		
<u> </u>		BBP	N/A	/		
	D	EHP	N/A	/		



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-0 Conclusion	
	Pb		BL	/		
		Cd	BL	/		
		Hg	BL	/		
	Cr	(Cr ⁶⁺)	BL	/		
37	Br	PBBs PBDEs	BL	/	Conformity	
	Γ	DIBP	N/A	N.D.		
		OBP	N/A	N.D.		
		BBP	N/A	N.D.		
		ЕНР	N/A	N.D.		
		Pb	BL	/		
		Cd	BL	/		
		Hg	BL	/		
		(Cr^{6+})	BL	/		
38	Br	PBBs PBDEs	N/A	/	Conformity	
	DIBP		N/A	/	1	
	DBP		N/A	/		
	BBP		N/A	/		
	DEHP		N/A	/		
		Pb	BL	/		
	Cd		BL	/		
	Hg		BL	/		
	Cr(Cr ⁶⁺)		BL	/		
39	Br	PBBs PBDEs	BL	/	Conformity	
	Γ	DIBP	N/A	N.D.		
		OBP	N/A	N.D.		
		BBP	N/A	N.D.		
		EHP	N/A	N.D.	l	
		Pb	BL	/		
		Cd	BL	/		
		Hg	BL	/		
		(Cr ⁶⁺)	BL	/		
40	Br PBBs PBDEs		BL	/	Conformity	
-	Γ	OIBP	N/A	N.D.	-	
-)BP	N/A	N.D.	-	
		BBP	N/A N/A	N.D.		
			N/A N/A	N.D.		
	DEHP		IN/A	N.D.		



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr^{6+})	BL	/	
41	Br	PBBs PBDEs	BL	/	Conformity
-	Γ	OIBP	N/A	N.D.	
-		OBP	N/A	N.D.	
-		BBP	N/A	N.D.	
-		EHP	N/A	N.D.	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
-		(Cr ⁶⁺)	BL	/	
-	CI	PBBs	DL	/	
42	Br	PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
43	Br	PBBs PBDEs	BL	/	Conformity
-	Γ	OIBP	N/A	154	
-)BP	N/A	236	
-		BBP	N/A	N.D.	
-		EHP	N/A	N.D.	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
-		(Cr ⁶⁺)	BL	/	
-		PBBs		/	
44	Br PBDEs		BL	/	Conformity
-	Г	OIBP	N/A	199	
-)BP	N/A	262	
-		овг ВВР	N/A	N.D.	
	DEHP		N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443240414-00
	Pb		BL	/	
	(Cd	BL	/	
	I	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
45	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
			BL	/	
		Cr ⁶⁺)	BL	/	
46	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
47	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
_		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
			BL	/	
		Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
48	Br PBBs PBDEs		N/A	/	Conformity
-	D	IBP	N/A	/	
-		BP	N/A	/	
-		BP	N/A	/	
		ЕНР	N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr^{6+})	BL	/	
49		PBBs	DI	/	Conformity
49	Br	PBDEs	BL	/	Conformity
	Σ	IBP	N/A	N.D.	
	Ι)BP	N/A	N.D.	
	I	BBP	N/A	N.D.	
	D	EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr^{6+})	BL	/	
50	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
-	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		IN	N.D.	
51	Br	PBBs PBDEs	N/A	/	Conformity
-	Γ	OIBP	N/A	/	
-)BP	N/A	/	
-		BBP	N/A	/	
-		EHP	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
-		Hg	BL	/	
		(Cr^{6+})	BL	/	
52	Br	PBBs	BL	/	Conformity
-		PBDEs	NT/A	N.D.	
-		OIBP	N/A	N.D.	
-		OBP ODD	N/A	N.D.	
-		BBP	N/A	N.D.	
	DEHP		N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr^{6+})	BL	/	
52		PBBs	27/4	/	
53	Br	PBDEs	N/A	/	Conformity
	Г	OIBP	N/A	/	
	Ι)BP	N/A	/	
	F	BBP	N/A	/	
	D	ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr^{6+})	IN	N.D.	
54	Br	PBBs PBDEs	N/A	/	Conformity
-	DIBP		N/A	/	1
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	1
	Pb		BL	/	
	Cd		BL	/	
-	Hg		BL	/	
-	Cr(Cr ⁶⁺)		BL	/	
55	Br	PBBs PBDEs	N/A	/	Conformity
-	Г	DIBP	N/A	/	
-		OBP	N/A	/	
		BBP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
56	PBBs PBBs		BL	/	Conformity
-	r	PBDEs DIBP	N/A	N.D.	
-					
-		OBP ODD	N/A	N.D.	
-		BBP	N/A	N.D.	
	DEHP		N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion	
	F	P b	BL	/		
		Cd	BL	/		
		Ig	BL	/		
	Cr(Cr ⁶⁺)	BL	/		
57	Br	PBBs	BL	/	Conformity	
37	DI	PBDEs	DL	/	Comornity	
	DI	BP	N/A	N.D.		
	D	BP	N/A	N.D.		
	B	BP	N/A	N.D.		
	DE	ЕНР	N/A	N.D.		
	Pb Cd		BL	/		
			BL	/	l	
	Hg		BL	/		
	Cr(Cr ⁶⁺)		BL	/		
58	Br	PBBs	BL	/	Conformity	
36	DI	PBDEs	DL	/	Comorning	
	DIBP		N/A	N.D.		
	DBP		N/A	N.D.		
	BBP		N/A	N.D.		
	DE	EHP	N/A	N.D.		
	F	Pb	BL	/		
		Cd	BL	/		
		Ig	BL	/		
	Cr(Cr ⁶⁺)	BL	/		
59	Br	PBBs	N/A	/	Conformity	
39	DI	PBDEs	IN/A	/	Conformity	
	DI	BP	N/A	/		
	D	BP	N/A	/		
	В	BP	N/A	/		
	DEHP		N/A	/		

Remark: The samples of the following test points were resubmitted on May 24, 2024:16,22,36,38,42

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>



LIG	rt No.: AGC05443240414-001			
Br	mg/kg	BL≤300-3σ <x< th=""><th>N/A</th><th>BL≤250-3σ<x< th=""></x<></th></x<>	N/A	BL≤250-3σ <x< th=""></x<>

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X < 0.1 \mu g/cm^2$	Negative
2	$0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$	Uncertainty
3	$X>0.13\mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Tost Itam(s)	Unit	Limit	MDL	Test Result(s)		
Test Item(s)	Ullit		MDL	1+4+7	11	49+56
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Con	Conformity	Conformity	Conformity			



1. As specified by client, the submitted samples were mixed to test, the test points: 1+4+7,49+56

Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Emint requiremen			`	<u> </u>
Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43

- Aromatic Amines Azodyes (AZO) Content

Test Methods and Equipment: EN ISO 14362-1:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s) 6+8
4-Aminobiphenyl CAS:92-67-1	mg/kg	30	5	N.D.
Benzidine CAS:92-87-5	mg/kg	30	5	N.D.
4-Chloro-o-toluidine CAS:95-69-2	mg/kg	30	5	N.D.
2-Naphthylamine CAS:91-59-8	mg/kg	30	5	N.D.
o-Aminoazotoluene CAS:97-56-3	mg/kg	30	5	N.D.
5-Nitro-o-toluidine CAS:99-55-8	mg/kg	30	5	N.D.
p-Chloroaniline CAS:106-47-8	mg/kg	30	5	N.D.



			MDL	Test Result(s)
Test Item(s)	Unit	Limit		6+8
4-Methoxy-m-phenylenediamine CAS:615-05-4	mg/kg	30	5	N.D.
4,4'-Diaminodiphenylmethane CAS:101-77-9	mg/kg	30	5	N.D.
3,3'-Dichlorobenzidine CAS:91-94-1	mg/kg	30	5	N.D.
3,3'-Dimethoxybenzidine CAS:119-90-4	mg/kg	30	5	N.D.
3,3'-Dimethybenzidine CAS:119-93-7	mg/kg	30	5	N.D.
4,4'-Methylenedi-o-toluidine CAS:838-88-0	mg/kg	30	5	N.D.
p-Cresidine CAS:120-71-8	mg/kg	30	5	N.D.
4,4'-Methylenebis[2-chloroaniline] CAS:101-14-4	mg/kg	30	5	N.D.
4,4'-Oxydianiline CAS:101-80-4	mg/kg	30	5	N.D.
4,4'-Thiodianiline CAS:139-65-1	mg/kg	30	5	N.D.
2-Aminotoluene CAS:95-53-4	mg/kg	30	5	N.D.
2,4-Toluylendiamine CAS:95-80-7	mg/kg	30	5	N.D.
2,4,5-Trimethylaniline CAS:137-17-7	mg/kg	30	5	N.D.
o-Anisidine CAS:90-04-0	mg/kg	30	5	N.D.
4-Aminoazobenzene CAS:60-09-3	mg/kg	30	5	N.D.
C	Conformity			

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 6+8

Note: 4-aminoazobenzene: The EN ISO 14362-1:2017 or ISO 17234-1:2020 methods will enable further cleavage of 4-aminoazobenzene to aniline and / or 1,4-phenylenediamine. If aniline and / or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.



- Color fastness to rubbing

Test Method: ISO 105-X12:2016

Rubbing finger: Cylinder

The time of conditioning as well as the atmospheric conditions during testing: 21.0°C, 65 %R.H., 4 hrs

The long direction of the specimen Endwise/ Crossrange The percentage of soak of wet rubbing cloth: 95%~100%

	Test l	Conclusion	
Test point	Colour fastness to		
	Dry rubbing	Wet rubbing	
6	4-5	4-5	Conformity
8	4-5	4-5	Conformity
Limit (Client's Requirement)	≥2-3	≥2-3	/

Note:


Colour Fastness Grade:


Grade 5 = No Colour Change (Best Grade)

Grade 1 = Colour Change Seriously (Bad Grade)

9 grades in gray sample card: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.


Test Flow Chart of XRF









Test Flow Chart of Phthalates









Test Flow Chart of Hexavalent Chromium (Cr6+)









Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)







Test Flow Chart of AZO





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.

 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***