

# **RoHS Test Report**

Report No. : AGC05443241009-001

**SAMPLE NAME** : Set of 2 COB bicycle light

MODEL NAME : MO2429

**APPLICANT**: MID OCEAN BRANDS B.V.

**STANDARD(S)** : Please refer to the following page(s).

**DATE OF ISSUE** : Nov. 13, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V.

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

#### Report on the submitted sample(s) said to be:

Sample Name : Set of 2 COB bicycle light

Model : MO2429
Vendor code : 115205
Country of Origin : CHINA
Country of Destination : EUROPE
Sample Received Date : Oct. 10, 2024

Testing Period : Oct. 10, 2024 to Nov. 13, 2024

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863 - Pb, Cd, Hg, Cr<sup>6+</sup>, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Pass

Report No.: AGC05443241009-001

Approved by: Len

Suhongliang, Leon

**Technical Director** 




Report Revise Record


Report No.: AGC05443241009-0	001
------------------------------	-----


Report Version	Issued Date	Valid Version	Notes
/	Nov. 13, 2024	Valid	Initial release





The photo of the sample
























AGC<sup>®</sup>





























The photo provided by the customer

The photo of AGC05443241009-001 is for use only with the original report.

#### **Test Point Description**

Test point	Test module	Test parts	Test point description	
Set of 2 COI	B bicycle light Mod	el: MO2429		
1			Black plastic outer shell	
2	Outer shell		Transparent plastic lampshade	
3			Black rubber stopper	
4			Chip triode	
5			Chip diode	
6			IC body	
7		IC	Metal pin	
8	Circuit board		Solder at the pins	
9	Circuit board	Key	Black plastic button	
10			Silver metal patch	
11			White plastic	
12			Solder	
13			PCB	
14			White metallic sheet	
15	LED Lamp board		Yellow LED	
16			White wire jacket	
17	Battery		White foam with glue	



			Report 110:: 118 C03 1132 11007 001
18			Tan tape
19			Blue wire jacket
20			Red wire jacket
21			Solder
22			Silver metal jack
23		Type-C jack	Black plastic
24			Metal pin
25			Black outer wire jacket
26		Wire rod	White wire jacket
27			Red wire jacket
28			Black handle
29	Data cable	True Culve	Silver metal plug
30	Data cable	Type-C plug	Black plastic
31			Metal pin
32			Silver metal plug
33		USB plug	White plastic
34			Metal pin
35	Outer shell		Red transparent plastic lampshade
36			Solder
37			Solder

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001% Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019/CNAS-GL015:2022.

## 2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

## - Pb, Cd, Hg, Cr<sup>6+</sup>, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method	-		
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr <sup>6+</sup> )	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr <sup>6+</sup> )	IEC 62321-7-1:2015/ UV-Vis	$0.1 \mu g/cm^2$	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)	_	50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443241009-0
	]	Pb	BL	/	
	(	Cd	BL	/	
		Нg	BL	/	
	Cr(	Cr <sup>6+</sup> )	BL	/	
1	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
	]	Pb	BL	/	
ļ		Cd	BL	/	
	I	Нg	BL	/	
		Cr <sup>6+</sup> )	BL	/	
2	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
		Cr <sup>6+</sup> )	BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
ļ		Cd	BL	/	
	I	Нg	BL	/	
		Cr <sup>6+</sup> )	BL	/	
4	Br PBBs PBDEs		BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
<u> </u>		ЕНР	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	OL	/	
		Cd	BL	/	
	]	Hg	BL	/	
		(Cr <sup>6+</sup> )	BL	/	
5	Br	PBBs PBDEs	BL	/	Conformity Exemption
-		IBP	N/A	N.D.	clause 7(c)-I
_		BP	N/A	N.D.	
		BP	N/A	N.D.	
-		EHP	N/A	N.D.	
		Pb	BL	N.D. /	
-		Cd	BL	/	
		Hg	BL	/	
		Cr <sup>6+</sup> )	BL	/	
-	CI(		DL	/	
6	6 Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	(	Cd	BL	/	
	Hg		BL	/	
		Cr <sup>6+</sup> )	BL	/	
7	Br	PBBs PBDEs	N/A	/	Conformity
	D		N/A	/	
	DIBP DBP		N/A	/	
_		BP	N/A	/	
_		EHP	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
_		Hg	BL	/	
8		Cr <sup>6+</sup> )	BL	/	
	Br	PBBs	N/A	/	Conformity
	PBDEs			/	Comonity
	D	IBP	N/A	/	
		BP	N/A	/	
	В	BP	N/A	/	
	D	ЕНР	N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443241009-0
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		$(Cr^{6+})$	BL	/	
9	Br	PBBs	BL	/	Conformity
		PBDEs		/	
		IBP	N/A	N.D.	
	Ι	OBP	N/A	N.D.	
		BBP	N/A	N.D.	
	D	EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr <sup>6+</sup> )	BL	/	
10	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$\frac{\text{Trg}}{\text{Cr}(\text{Cr}^{6+})}$		BL	/	
11	Br	PBBs	BL	/	Conformity
		PBDEs		/	
		OIBP	N/A	N.D.	
		OBP	N/A	N.D.	
	BBP		N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr <sup>6+</sup> )	BL	/	
12	Br PBBs PBDEs		N/A	/	Conformity
ŀ	Г	OIBP	N/A	/	
-		)BP	N/A	/	
		овг ВВР	N/A	/	
-				,	
	D	EHP	N/A	/	



			I		C05443241009-00
Test point	Tes	st Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	$(Cr^{6+})$	BL	/	
13	Br	PBBs PBDEs	BL	/	Conformity
_	Ι	DIBP	N/A	N.D.	
		OBP	N/A	N.D.	
		BBP	N/A	N.D.	
	Г	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		$(\operatorname{Cr}^{6+})$	BL	/	
14	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
15	Br	PBBs PBDEs	BL	/	Conformity
	Ι	DIBP	N/A	N.D.	
	DBP		N/A	N.D.	
_		BBP	N/A	N.D.	
_		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		$(\operatorname{Cr}^{6+})$	BL	/	
16	Br PBBs		BL	/	Conformity
-	Γ	DIBP	N/A	N.D.	
-		OBP	N/A	N.D.	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Cos443241009-0
		Pb	BL	/	
	(	Cd	BL	/	
		Hg	BL	/	
	Cr(	$(Cr^{6+})$	BL	/	
17	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		)BP	N/A	N.D.	
	E	BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
	]	Hg	BL	/	
		$(Cr^{6+})$	BL	/	
18	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
19	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		$(Cr^{6+})$	BL	/	
20	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		)BP	N/A	N.D.	
		BBP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443241009-00
		Pb	BL	/	
Cd		Cd	BL	/	
	]	Hg	BL	/	
Ī	Cr(	(Cr <sup>6+</sup> )	BL	/	
21	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
ļ-		)BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		 Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr <sup>6+</sup> )	BL	/	
22	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
23	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		)BP	N/A	N.D.	
ļ		BP	N/A	N.D.	
ļ		EHP	N/A	N.D.	
		Pb	BL	/	
ļ		Cd	BL	/	
		Hg	BL	/	
Ţ		(Cr <sup>6+</sup> )	BL	/	
24	Br PBBs PBDEs		N/A	/	Conformity
ļ	D	IBP	N/A	/	
ļ		)BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443241009-00
	I	<b>P</b> b	BL	/	
	(	Cd	BL	/	
	F	łg	BL	/	
	Cr(	Cr <sup>6+</sup> )	BL	/	
25	Br	PBBs PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd Cd	BL	/	
		Ig	BL	/	
		Cr <sup>6+</sup> )	BL	/	
26	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
27	Br	PBBs PBDEs	BL	/	Conformity
	D	BP	N/A	N.D.	
	DBP		N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd Cd	BL	/	
	Hg		BL	/	
		- <u>s</u> Cr <sup>6+</sup> )	BL	/	
28	Br	PBBs PBDEs	BL	/	Conformity
-	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
<u> </u>		BP	N/A N/A	N.D.	
-		EHP	N/A N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443241009-00
	I	Pb	BL	/	
	(	Cd	BL	/	
	Hg		BL	/	
	Cr(	Cr <sup>6+</sup> )	IN	N.D.	
29	Br	PBBs PBDEs	N/A	/	Conformity
-	DIBP		N/A	/	
-	DBP		N/A	/	
-		BP	N/A	/	
-		EHP	N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
-			BL	/	
-	Hg Cr(Cr <sup>6+</sup> )		BL	/	
_	Cr(		BL	,	
30	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	I	Pb	BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		IN	N.D.	
31	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
		Pb	BL	/	
-	Cd		BL	/	
32	Hg		BL	/	Conformity
	$Cr(Cr^{6+})$		BL	/	
	Br PBBs PBDEs	N/A	/		
			/		
-	DIBP		N/A	/	
-	DBP		N/A	,	
-	BBP		N/A	/	
<del> </del>		EHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(	Cd	BL	/	
	F	Ig	BL	/	
	$Cr(Cr^{6+})$		BL	/	
22	Br	PBBs	DI	/	Conformity
33		PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	Pb	BL	/	
	C	Cd	BL	/	
	Н	Ig	BL	/	
		Cr <sup>6+</sup> )	BL	/	Conformity
		PBBs	N/A	/	
34	Br	PBDEs		/	
	DI	BP	N/A	/	
_	DBP		N/A	/	
_	BBP		N/A	/	
	DEHP		N/A	/	
		<b>P</b> b	BL	/	
_	Cd		BL	/	
_	Hg		BL	/	
_	$Cr(Cr^{6+})$		BL	/	
35	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
36	Hg		BL	/	Conformity
	Cr(Cr <sup>6+</sup> )		BL	/	
	Br PBBs PBDEs		/		
		N/A	/		
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	,	
+		EHP	N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr <sup>6+</sup> )		BL	/	
37	Br	PBBs	N/A	/	Conformity
37		PBDEs		/	
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	

Remark: The samples of the following test points were resubmitted on October 28, 2024:5,8,12,21,25,26,27,36,37 Remark: Test result of DIBP, DBP, BBP, DEHP on specimen No.28 was resubmitted on Nov. 12, 2024.

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x &lt;130+3σ≤OL</x 	BL≤70-3σ <x &lt;130+3σ≤OL</x 	BL≤50-3σ <x &lt;150+3σ≤OL</x 
Pb	mg/kg	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤500-3σ <x &lt;1500+3σ≤OL</x 
Hg	mg/kg	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤500-3σ <x &lt;1500+3σ≤OL</x 
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>N/A</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	N/A	BL≤250-3σ <x< td=""></x<>

#### Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X < 0.1 \mu g/cm^2$	Negative
2	$0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$	Uncertainty
3	$X > 0.13 \mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).



Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.


(5) This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.


The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the

sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

Exemption clause	Exemption
	Electrical and electronic components containing lead in a glass or ceramic other than
7(c)-I	dielectric ceramic in capacitors, e.g. piezoelectronic devices, or in a glass or ceramic
	matrix compound


#### **Test Flow Chart of XRF**









## Test Flow Chart of Hexavalent Chromium (Cr6+)







### **Test Flow Chart of Phthalates**





## Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

\*\*\* End of Report \*\*\*