

RoHS Test Report

Report No. : AGC05443240611-001S1

SAMPLE NAME : Portable magnetic charger

MODEL NAME : MO6417

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Jun. 26, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Portable magnetic charger

Model : MO6417
Vendor code : 114538
Country of Origin : CHINA
Country of Destination : EUROPE

Sample Received Date : Jun. 07, 2024(Test point: Other)

Jun. 24, 2024(Test point: No.31)

Testing Period : Jun. 07, 2024 to Jun. 17, 2024(Test point: Other)

Jun. 24, 2024 to Jun. 26, 2024(Test point: No.31)

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863 - Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Pass

Report No.: AGC05443240611-001S1

Approved by: Leon

Suhongliang, Leon

Technical Director




Report Revise Record


Report Version	Issued Date	Valid Version	Notes
/	Jun. 17, 2024	Invalid	Initial release
S1	Jun. 26, 2024	Valid	Replace Test Results







The photo of the sample









AGC[®]














The photo of AGC05443240611-001S1 is for use only with the original report.





Test point	Test module	Test parts	Test point description
Portable ma	gnetic charger Mod	lel: MO6417	
1			Silver metallic base
2		Base	Grey silicone ring
3			Grey silicone pad
4		Matal sin a	Black metal ring
5		Metal ring	Double-sided tape
6			White plastic shell
7		Outer shell	Silver metallic shell
8			Black foam with glue
9			Grey ceramic
10		T 1 41 11	Tan tape
11		Induction coil	Enameled wire
12			Double-sided tape
13			PCB
14			Solder
15			Chip capacitor
16			Chip resistor
17			Chip LED
18	Circuit board		Chip diode
19			Chip triode
20			IC body
21		IC	Solder at the pins
22			Metal pin
23			Type-C metal plug
24			White plastic plug
25			Metal pin
26		T. G. 1	Metallic pogopin
27		Type-C plug	PCB
28			Solder
29			White buckle
30			White handle
31			White outer wire jacket
32			Aluminum foil
33			Black wire jacket
34			Conductor
35		Wire rod	Blue wire jacket
36			Green wire jacket
37			Red wire jacket
38			White wire jacket
39			White buckle
Adaptor	I		
40			USB metal plug



		F
41	 	White plastic plug
42	 	Metal pin
43	 	Grey plastic plug
44	 	Metal pin
45	 	Type-C metal plug
46	 	White inner glue
47	 	White handle
48	 	Chip resistor
49	 	PCB
50	 	Solder

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method		l .	
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)	\dashv	50mg/kg	1000mg/kg



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	I	Pb	BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1		PBBs	NT/A	/	C f : t
1	Br	PBDEs	N/A	/	Conformity
	D	BP	N/A	/	
	D	BP	N/A	/	
	В	BP	N/A	/	
	DH	ЕНР	N/A	/	
	I	Pb	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
2	ъ	PBBs	DI	/	Conformity
2	Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	Dì	BP	N/A	N.D.	-
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
<u> </u>			BL	/	
		Cr ⁶⁺)	IN	N.D.	
,	·	PBBs		/	
4	Br	PBDEs	N/A	/	Conformity
	Di	BP	N/A	/	
ļ		BP	N/A	/	
		BP	N/A	/	
		ЕНР	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	P	'b	BL	/	
	C	Cd	BL	/	
	F	lg	BL	/	
		Cr ⁶⁺)	BL	/	
5		PBBs	DI	/	C C : L -
5	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	Bl	BP	N/A	N.D.	
	DE	CHP	N/A	N.D.	
	P	b	BL	/	
	C	Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
	D.,	PBBs	DI	/	C f : f -
6	Br	PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DE	НР	N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
7	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
	D	BP	N/A	/	
		BP	N/A	/	
	DEHP		N/A	/	
		Pb	BL	/	
		Cd	BL	/	
ļ	Hg		BL	/	
		Cr^{6+})	BL	/	
8	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
-		BP	N/A	N.D.	1
		BP	N/A	N.D.	
-		CHP	N/A	N.D.	1



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	P	b	BL	/	
	C	Cd .	BL	/	
		[g	BL	/	
	Cr(C	Cr ⁶⁺)	BL	/	
9	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		HP	N/A	N.D.	
		'b	BL	/	
		2d	BL	/	
-		lg	BL	/	
		Cr^{6+})	BL	/	
		PBBs		/	
10	Br	PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DE	НР	N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Нд		BL	/	
	$Cr(Cr^{6+})$		BL	/	
11	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	Di	BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		b	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		Cr^{6+})	BL	/	
12	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	DI	BP	N/A	N.D.	
-		BP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
-		HP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	J	Pb	BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
12		PBBs	DI	/	C C :
13	Br	PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	EHP	N/A	N.D.	
]	Pb	BL	/	
	(Cd	BL	/	
	I	Нg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1.4	ъ	PBBs	27/4	/	Conformity
14	Br	PBDEs	N/A	/	
	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
-	Cd		BL	/	
-	Hg		BL	/	
-	$Cr(Cr^{6+})$		BL	/	
15	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
-	DEHP		N/A	N.D.	
		Pb	BL	/	
			BL	/	
-		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
16	Br	PBBs PBDEs	BL	/	Conformity
	D.	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		ЕНР	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	Pb	BL	/	
	C	Cd	BL	/	
	F	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
1.7		PBBs	DI	/	G C :
17	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D.	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	Pb	BL	/	
	C	Cd	BL	/	
	Н	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
10	,	PBBs	D.1	/	Conformity
18	8 Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
19	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
20	Br	PBBs PBDEs	BL	/	Conformity
-	DI	BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Report No.: AGCC Wet Chemistry Method mg/kg	Conclusion
]	Pb	BL	/	
	(Cd	BL	/	
	I	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
21	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
		 C d	BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
22	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
_	DBP		N/A	/	
_	BBP		N/A	/	
_	DEHP		N/A	/	
		Pb	BL	/	
_	Cd		BL	/	
_	Hg		BL	/	
_	$Cr(Cr^{6+})$		IN	N.D.	
23	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
	DBP		N/A	/	
		BP	N/A	/	
-		EHP	N/A	/	
		Pb	BL	/	
_	Cd		BL	/	
-		Hg	BL	/	
-		Cr ⁶⁺)	BL	/	
-		PBBs		/	
24	Br	PBDEs	BL	/	Conformity
-	D.	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-					
<u> </u> -		BP EHP	N/A N/A	N.D. N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	Pb	BL	/	
	(Cd	BL	/	
	I	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
25		PBBs	27/4	/	
25	Br	PBDEs	N/A	/	Conformity
	Dl	BP	N/A	/	
	D	BP	N/A	/	
	В	BP	N/A	/	
	DE	ЕНР	N/A	/	
	F	P b	BL	/	
	(Cd	BL	/]
	ŀ	Ig	BL	/	
		Cr ⁶⁺)	IN	N.D.	
26		PBBs	27/4	/	
26	Br	PBDEs	N/A	/	Conformity
	Dl	BP	N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DE	ЕНР	N/A	/	
	Pb		BL	/	
	Cd		BL	/	-
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
	PRRs	PBBs		N.D.	1
27	Br PBDEs		IN	N.D.	Conformity
	Dl	BP	N/A	N.D.	-
		BP	N/A	N.D.	-
		BP	N/A	N.D.	-
	DEHP		N/A	N.D.	-
		Pb	BL	/	
		Cd	BL	/	1
		lg	BL	/	1
		Cr ⁶⁺)	BL	/	1
		PBBs		/	
28	Br PBDEs		N/A	/	Conformity
	DI	BP	N/A	/	1
		BP	N/A	/	1
		BP	N/A	/	1
-		ЕНР	N/A	/	1



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	Pb	BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
		$\mathbb{C}\mathbf{r}^{6+}$)	BL	/	
20		PBBs	DI	/	G 6
29	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	Pb	BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
20		PBBs	DI	/	
30	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
31	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		P b	BL	/	
		Cd	BL	/	
		Ig	BL	/	
		Cr ⁶⁺)	BL	/	
		PBBs		/	
32	Br	PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	1
		BP	N/A	/	1
		BP	N/A	/	1
		EHP	N/A	/	1



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
	I	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
33	Br	PBBs	BL	/	Conformity
		PBDEs		/	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		P b	BL	/	
	(Cd	BL	/	
		Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
34	Br	PBBs PBDEs	N/A	/	Conformity
-	Di	l.	N/A	/	-
-	DIBP		N/A	/	
-	DBP BBP		N/A	/	
-	DEHP		N/A	/	
			BL	/	
-	Pb		BL	/	
_	Cd		BL	/	
_	Hg Cr(Cr ⁶⁺)			/	
35	•	PBBs	BL	/	Conformity
33	Br PBDEs		BL	/	Conformity
	Dl	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	-
	Hg		BL	/	•
	Cr(Cr ⁶⁺)		BL	/	•
36	Br	PBBs	BL	/	Conformity
-	PBDEs			N.D.	-
<u> </u>	DIBP		N/A	N.D.	-
-	DBP		N/A	N.D.	-
_	BBP		N/A	N.D.	-
	DE	EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
27	D.,	PBBs	DI	/	Conformity
37	Br	PBDEs	BL	/	
	D	IBP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
]	Pb	BL	/	
	(Cd	BL	/	
	I	Нg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
20	D	PBBs	BL /	/	Conformity
38	Br	PBDEs		/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
- -	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
39	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
			BL	/	
	Hg		BL	/	1
ļ	$Cr(Cr^{6+})$		BL	/	
10		PBBs		/	G 2 :
40	Br	PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	C	Cd	BL	/	
Ī	H	Ig	BL	/	
	Cr(0	Cr^{6+})	BL	/	
41		PBBs		/	G C :
41	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D.	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	CHP	N/A	N.D.	
	F	b	BL	/	
	C	Cd	BL	/	
	Н	lg	BL	/	
		Cr ⁶⁺)	BL	/	
12		PBBs	N/A	/	Conformity
42	Br	PBDEs		/	
	DI	BP	N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
43	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	DBP BBP		N/A	N.D.	
			N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
		PBBs		/	
44	Br PBDEs		N/A	/	Conformity
	DI	BP	N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
		CHP	N/A	/	



Test point	Test Item		X-ray Fluoresc	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/		
Cd		BL	/			
	Hg		BL	/		
	Cr(Cr ⁶⁺)	IN	N.D.		
45	Br	PBBs PBDEs	N/A	/	Conformity	
	D	IBP	N/A	/		
-		BP	N/A	/		
		BP	N/A	/		
_		ЕНР	N/A	/		
]	Pb	BL	/		
		Cd	BL	/		
		Hg	BL	/		
		Cr ⁶⁺)	BL	/		
46	Br	PBBs PBDEs	BL	/	Conformity	
_	DIBP		N/A	N.D.		
	DBP		N/A	N.D.		
_	BBP		N/A	N.D.		
_	DEHP		N/A	N.D.		
]	Pb	BL	/		
	Cd		BL	/		
	Hg		BL	/		
	Cr(Cr ⁶⁺)		BL	/		
47	Br	PBBs PBDEs	BL	/	Conformity	
	D	IBP	N/A	N.D.	1	
	DBP		N/A	N.D.	1	
		BP	N/A	N.D.	1	
	DEHP		N/A	N.D.	1	
	Pb		BL	/		
	(Cd	BL	/		
]	Hg	BL	/		
		Cr ⁶⁺)	IN	N.D.		
48	Br PBBs PBDEs		BL	/	- Conformity	
	DIBP		N/A	N.D.		
	DBP		N/A	N.D.		
	BBP		N/A	N.D.		
		ЕНР	N/A	N.D.		



			X-ray Fluorescence	Wet Chemistry	
Test point	Test Item		Spectrometry (XRF)	Method	Conclusion
F			mg/kg	mg/kg	
	Pb		BL	/	
	C	² d	BL	/	
	Н	[g	BL	/	Conformity
	Cr(C	Cr ⁶⁺)	BL	/	
40	D	PBBs	D.I.	N.D.	
49	Br	PBDEs	IN	N.D.	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
50	Cr(Cr ⁶⁺)		BL	/	
	Br	PBBs	N/A	/	Conformity
		PBDEs		/	
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Нд	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>N/A</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	N/A	BL≤250-3σ <x< td=""></x<>

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number Colorimetric result (Cr(VI) concentration)	Judgement
---	-----------



 Report No.: AGC05443240611-001S1

 1
 $X < 0.1 \mu g/cm^2$ Negative

 2
 $0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$ Uncertainty

 3
 $X > 0.13 \mu g/cm^2$ Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.


Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.


Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

- (5) This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.
 - The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.


Test Flow Chart of XRF









Test Flow Chart of Phthalates









Test Flow Chart of Hexavalent Chromium (Cr6+)









Test Flow Chart of PBBs and PBDEs







Test Flow Chart of Hexavalent Chromium (Cr6+)





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***