

## **Test Report**

Report No. : AGC05443241031-001

**SAMPLE NAME** : Double wall mug

MODEL NAME : MO6533

**APPLICANT**: MID OCEAN BRANDS B.V.

**STANDARD(S)** : Please refer to the following page(s).

**DATE OF ISSUE** : Dec. 05, 2024

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Applicant : MID OCEAN BRANDS B.V.

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

#### Report on the submitted sample(s) said to be:

Sample Name : Double wall mug

Model : MO6533

Vendor code : 114276

Country of Origin : CHINA

Country of Destination : EUROPE

Sample Received Date : Oct. 23, 2024

Testing Period : Oct. 23, 2024 to Dec. 05, 2024

Test Requested : Selected test(s) as requested by client.

Approved by: Len

Suhongliang, Leon

Report No.: AGC05443241031-001

**Technical Director** 



Conclusion Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63 Pass - Lead(Pb) Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23 Pass -Cadmium(Cd) Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52 **Pass** - Phthalates Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50 **Pass** - Polycyclic-aromatic Hydrocarbons (PAHs) Content Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 77 Pass - Formaldehyde Release Regulation (EU) 2019/1021 on persistent organic pollutants (POPs) Pass - Pentachlorophenol (PCP) Content Regulation 1935/2004/EC, Regulation(EU) No 10/2011 and its amendment Regulation (EU) 2020/1245 and Regulation (EU) 2018/213, Council of Europe Resolution AP (2004)5 - Overall migration Pass - Bisphenol A(BPA) content Pass - Specific migration of Bisphenol A(BPA) Pass - Specific migration of Primary aromatic amines Pass - Specific migration of Heavy metals Pass DM-4B-COM-003-v01 - Volatile Organic Matter **Pass** - Peroxide value **Pass** - Specific Migration of Organotin (measured as Tin) Pass

Regulation 1935/2004/EC and Technical Guide on Metals and alloys used in food contact materials

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

of Council of Europe Resolution CM/Res(2020)9

- Specific migration of Heavy metal

Pass

Report No.: AGC05443241031-001



Report Revise Record

Report Version	Issued Date	Valid Version	Notes
/	Dec. 05, 2024	Valid	Initial release



The photo of the sample



The photo of AGC05443241031-001 is for use only with the original report.

#### **Test Point Description**

Test point	Test point description
1-1	Transparent plastic lid
1-2	Black silicone sealing
1-3	Inner S/S mug
1-4	Black coating
1-5	Cork
1-6	Metal handle



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001% Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019/CNAS-GL015:2022.

### Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 63

## - Lead(Pb) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit Limit	MDL	Test Result(s)			
rest item(s)	UIII	Limit	MDL	1-1	1-2	1-3
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Conclusion			Conformity	Conformity	Conformity	

Tost Itam(s)	Unit Limit	MDL	Test Result(s)			
Test Item(s)	Unit	Limit	MDL	1-4	1-5	1-6
Lead(Pb)	mg/kg	500	10	N.D.	N.D.	N.D.
Conclusion			Conformity	Conformity	Conformity	

#### Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 23

#### -Cadmium(Cd) Content

Test Methods and Equipment: IEC 62321-5:2013; ICP-OES

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
rest item(s)	Unit	LIIIII	MIDL	1-1	1-2	1-4
Cadmium(Cd)	mg/kg	100	10	N.D.	N.D.	N.D.
Conclusion			Conformity	Conformity	Conformity	



#### Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Test Itams(s)	I Ii.	T imit	MDI	7	Test Result(s)	
Test Item(s)	Unit	Limit	MDL	1-1	1-2	1-4
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.	N.D.	N.D.
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	N.D.	N.D.	N.D.
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.	N.D.	N.D.
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.	N.D.	N.D.
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.	N.D.	N.D.
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.	N.D.	N.D.
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.	N.D.	N.D.
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	N.D.	N.D.	N.D.
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.	N.D.	N.D.
Con	clusion			Conformity	Conformity	Conformity

#### Limit requirements of Phthalates

Toys and childcare articles	Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%
Toys and childcare articles which can be placed in the mouth by children	The sum of DINP+DIDP+DNOP is less than 0.1%

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443241031-001



#### Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

#### - Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(s)	Unit 1	Limit	MDL	Test Result(s)		
Test Item(s)	Omi	Lillit	MIDL	1-1	1-2	1-4
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.	N.D.	N.D.
Con	Conformity	Conformity	Conformity			

#### Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Emilit requirements of robby ene-aromatic rhydrocarbons (1741s) (Omt. nig/kg)								
Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity				
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5				
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5				
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5				
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5				
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5				
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5				
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5				
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5				
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/				

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443241031-001



#### Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 77

#### - Formaldehyde Release

Test Methods and Equipment: EN 717-1:2004; UV-Vis

Test Item(s)	Unit	Limit	MDL	Test Result(s)
Test Item(s)	Cilit	Lillit	MDL	1-5
Formaldehyde Release	mg/m³	0.062	0.006	N.D.(240h)
Со	Conformity			

Report No.: AGC05443241031-001

#### Regulation (EU) 2019/1021 on persistent organic pollutants (POPs)

#### - Pentachlorophenol (PCP) Content

Test Methods and Equipment: EPA 3550C:2007 & EPA 8270E:2018; GC-MS

Toot Itom(a)	Unit	Limit	MDL	Test Result(s)
Test Item(s)	Onit	Lillit	MDL	1-5
Pentachlorophenol (PCP)	mg/kg	5	5	N.D.
Co	Conformity			

#### -Overall migration

Test point		Test		
		Overall migra	Conclusion	
		3% Acetic acid, 70°C,2h	50% Ethanol, 70°C,2h	
	1 <sup>st</sup> migration	N.D.	N.D.	
1-1	2 <sup>nd</sup> migration	N.D.	N.D.	Conformity
	3 <sup>rd</sup> migration	N.D.	N.D.	
	Limit	10	10	/
	MDL	5	5	/

	Test		
Test point	Overall migra	Conclusion	
	3% Acetic acid, 70°C,2h	50% Ethanol, 70°C,2h	
1-2	N.D.	N.D.	Conformity
Limit	10	10	/
MDL	5	5	/



Report No.: AGC05443241031-001

-Bisphenol A(BPA) content

Test Item Bisphenol A (BPA)	
Limit (mg/kg)	Absent
MDL(mg/kg)	0.1
Test Method/ Instrument	EPA 3540C:1996& EPA 8321B:2007/ LC-MS-MS


Test point	Test Result (mg/kg)	Conclusion	
Test point	Bisphenol A (BPA)		
1-1	N.D.	Conformity	

Test Item	Bisphenol A (BPA)	
Client's limit (mg/kg)	Absent	
MDL(mg/kg)	0.1	
Test Method/Instrument	EPA 3540C:1996& EPA 8321B:2007/ LC-MS-MS	

Test point	Test Result (mg/kg) Bisphenol A (BPA)	Conclusion
1-2	N.D.	Conformity

#### -Specific migration of Bisphenol A(BPA)


	Test Result		
Test point	Specific migration of Bisphenol A(BPA)/ (mg/kg)	Conclusion	
	3% Acetic acid,70°C,2h		
1-2	N.D.	Conformity	
Client's limit	0.05	/	
MDL	0.02	/	





#### -Specific migration of Primary aromatic amines

4-Aminobiphenyl  Benzidine  4-Chloro-o-Toluidine  2-Naphthylamine	0.002 0.002 0.002	N.D. N.D.
4-Chloro-o-Toluidine 2-Naphthylamine		N.D.
2-Naphthylamine	0.002	
•		N.D.
	0.002	N.D.
4-amino-2',3-dimethylazobenzene	0.002	N.D.
5-Nitro-o-toluidine	0.002	N.D.
4-Chloroaniline	0.002	N.D.
4-Methoxy-m-phenylenediamine	0.002	N.D.
4,4'-Diaminodiphenylmethane	0.002	N.D.
3,3'-Dichlorobenzidine	0.002	N.D.
3,3'-Dimethoxybenzidine	0.002	N.D.
3,3'-Dimethybenzidine	0.002	N.D.
4,4'-Methylenedi-o-toluidine	0.002	N.D.
6-methoxy-m-toluidine	0.002	N.D.
4,4'-methylenebis[2-chloroaniline]	0.002	N.D.
4,4'-Oxydianiline	0.002	N.D.
4,4'-Thiodianiline	0.002	N.D.
2-Aminotoluene	0.002	N.D.
4-methyl-m-phenylenediamine	0.002	N.D.
2,4,5-Trimethylaniline	0.002	N.D.
2-Methoxyaniline	0.002	N.D.
4-Aminoazobenzene	0.002	N.D.
1,3 phenylenediamine	0.002	N.D.
Total of other primary aromatic amines	0.01	0.01





		Test Result (mg/kg)			
	1-1				
Test Item(s)	3% Acetic acid 70°C, 2h				
	1 <sup>st</sup> migration	2 <sup>nd</sup> migration	3 <sup>rd</sup> migration		
4-Aminobiphenyl	N.D.	N.D.	N.D.		
Benzidine	N.D.	N.D.	N.D.		
4-Chloro-o-Toluidine	N.D.	N.D.	N.D.		
2-Naphthylamine	N.D.	N.D.	N.D.		
4-amino-2',3-dimethylazobenzene	N.D.	N.D.	N.D.		
5-Nitro-o-toluidine	N.D.	N.D.	N.D.		
4-Chloroaniline	N.D.	N.D.	N.D.		
4-Methoxy-m-phenylenediamine	N.D.	N.D.	N.D.		
4,4'-Diaminodiphenylmethane	N.D.	N.D.	N.D.		
3,3'-Dichlorobenzidine	N.D.	N.D.	N.D.		
3,3'-Dimethoxybenzidine	N.D.	N.D.	N.D.		
3,3'-Dimethybenzidine	N.D.	N.D.	N.D.		
4,4'-Methylenedi-o-toluidine	N.D.	N.D.	N.D.		
6-methoxy-m-toluidine	N.D.	N.D.	N.D.		
4,4'-methylenebis[2-chloroaniline]	N.D.	N.D.	N.D.		
4,4'-Oxydianiline	N.D.	N.D.	N.D.		
4,4'-Thiodianiline	N.D.	N.D.	N.D.		
2-Aminotoluene	N.D.	N.D.	N.D.		
4-methyl-m-phenylenediamine	N.D.	N.D.	N.D.		
2,4,5-Trimethylaniline	N.D.	N.D.	N.D.		
2-Methoxyaniline	N.D.	N.D.	N.D.		
4-Aminoazobenzene	N.D.	N.D.	N.D.		
1,3 phenylenediamine	N.D.	N.D.	N.D.		
Total of other primary aromatic amines	N.D.	N.D.	N.D.		
Conclusion	Conformity				





#### -Specific migration of Heavy metals

	Test condition/ Equipment	MDL (mg/kg)	Test Result(s) (mg/kg) 1-1			Limit (mg/kg)
Test Item(s)						
			1 <sup>st</sup>	2 <sup>nd</sup>	3 <sup>rd</sup>	(mg/Ng)
Barium (Ba)		0.1	migration N.D.	migration N.D.	migration N.D.	1
Cobalt (Co)	_	0.01	N.D.	N.D.	N.D.	0.05
Copper (Cu)		0.25	N.D.	N.D.	N.D.	5
Iron (Fe)	_	0.25	N.D.	N.D.	N.D.	48
Lithium (Li)		0.1	N.D.	N.D.	N.D.	0.6
Manganese (Mn)		0.1	N.D.	N.D.	N.D.	0.6
Zinc (Zn)	1	0.25	N.D.	N.D.	N.D.	5
Aluminum (Al)		0.1	N.D.	N.D.	N.D.	1
Europium (Eu)		0.01	N.D.	N.D.	N.D.	/
Gadolinium (Gd)		0.01	N.D.	N.D.	N.D.	/
Lanthanum (La)		0.01	N.D.	N.D.	N.D.	/
Terbium (Tb)		0.01	N.D.	N.D.	N.D.	/
Sum(Eu+Gd+La+Tb)	3% Acetic acid/	/	N.D.	N.D.	N.D.	0.05
Antimony (Sb)	70°C, 2h/ ICP-OES/ IC	0.01	N.D.	N.D.	N.D.	0.04
Arsenic (As)		0.01	N.D.	N.D.	N.D.	N.D.
Cadmium (Cd)		0.002	N.D.	N.D.	N.D.	N.D.
Chromium (Cr)		0.01	N.D.	N.D.	N.D.	N.D.
Lead (Pb)		0.01	N.D.	N.D.	N.D.	N.D.
Mercury (Hg)		0.01	N.D.	N.D.	N.D.	N.D.
Nickel (Ni)		0.01	N.D.	N.D.	N.D.	0.02
Conclusion		/		Conformity		/
Ammonium (NH <sub>4</sub> <sup>+</sup> )		0.10	N.D.	N.D.	N.D.	/
Calcium (Ca)		0.01	0.405	0.123	0.048	/
Magnesium (Mg)		0.01	0.023	N.D.	N.D.	/
Potassium (K)		0.01	0.019	N.D.	N.D.	/
Sodium (Na)		0.01	0.026	N.D.	N.D.	/



Unit: %

Test item(s)	em(s) Test Condition	MDL	Result(s)	Limit	
rest item(s)	Test Condition	WIDL	1-2		
Volatile Organic Matter		0.1	0.31	0.5	
Conclusion	200°C, 4h	/	Conformity	/	

#### - Peroxide value

Unit: %

Test Item	Test Item MDL		Limit		
Peroxide value	0.2	N.D.	Absent		
Conclusion	/	Conformity	/		

#### - Specific Migration of Organotin (measured as Tin)

	Test Result		
Test point	Specific Migration of Organotin (measured as Tin)/ (mg/kg)	Conclusion	
	3% Acetic acid, 70°C,2h		
1-2	N.D.	Conformity	
Limit	0.1	/	
MDL	0.01	/	



# Regulation 1935/2004/EC and Technical Guide on Metals and alloys used in food contact materials of Council of Europe Resolution CM/Res(2020)9


#### - Specific migration of Heavy metal

Test Method: EDQM (2024)

Item(s)	Unit	Limit		MDI	Test result(s)			
		1 <sup>st</sup> +2 <sup>nd</sup> migration	3 <sup>rd</sup> migration	MDL	1-3 1 <sup>st</sup> +2 <sup>nd</sup> migration	3 <sup>rd</sup> migration		
C' 1 . II 1 0 50	/ G': : 1				1 +2 Illigration	3 illigration		
Simulant Used: 0.5% Citric acid; Test Condition: 70°C, 2h								
Barium (Ba)	mg/kg	8.4	1.2	0.1	N.D.	N.D.		
Copper (Cu)	mg/kg	28	4	0.1	N.D.	N.D.		
Iron (Fe)	mg/kg	280	40	0.1	N.D.	N.D.		
Tin (Sn)	mg/kg	700	100	0.1	N.D.	N.D.		
Chromium (Cr)	mg/kg	7	1	0.01	N.D.	N.D.		
Manganese (Mn)	mg/kg	3.85	0.55	0.1	N.D.	N.D.		
Zinc (Zn)	mg/kg	35	5	0.1	N.D.	N.D.		
Aluminium (Al)	mg/kg	35	5	0.1	N.D.	N.D.		
Lithium (Li)	mg/kg	0.336	0.048	0.01	N.D.	N.D.		
Beryllium (Be)	mg/kg	0.07	0.01	0.005	N.D.	N.D.		
Vanadium (V)	mg/kg	0.07	0.01	0.005	N.D.	N.D.		
Nickel (Ni)	mg/kg	0.98	0.14	0.01	N.D.	N.D.		
Cobalt (Co)	mg/kg	0.14	0.02	0.01	N.D.	N.D.		
Arsenic (As)	mg/kg	0.014	0.002	0.002	N.D.	N.D.		
Molybdenum (Mo)	mg/kg	0.84	0.12	0.01	N.D.	N.D.		
Silver (Ag)	mg/kg	0.56	0.08	0.01	N.D.	N.D.		
Cadmium (Cd)	mg/kg	0.035	0.005	0.002	N.D.	N.D.		
Antimony (Sb)	mg/kg	0.28	0.04	0.01	N.D.	N.D.		
Mercury (Hg)	mg/kg	0.021	0.003	0.002	N.D.	N.D.		
Thallium (Tl)	mg/kg	0.007	0.001	0.001	N.D.	N.D.		
Lead (Pb)	mg/kg	0.07	0.01	0.01	N.D.	N.D.		
Zirconium (Zr)	mg/kg	14	2	0.01	N.D.	N.D.		
Magnesium (Mg)	mg/kg	/	/	0.01	N.D.	N.D.		
Titanium (Ti)	mg/kg	/	/	0.01	N.D.	N.D.		
Conclusion					Conformity	Conformity		


#### Note:

Results from all three migration are to be considered for compliance: Result of  $3^{rd}$  migration shall not exceed the SRL and Sum of result of  $1^{st}$  and  $2^{nd}$  migration shall not exceed 7 times of SRL.







## **Test Flow Chart of Heavy Metal Content**




#### **Test Flow Chart of Phthalates**









## **Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)**









## **Test Flow Chart of Formaldehyde Release**







## **Test Flow Chart of Pentachlorophenol (PCP)**





## Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

\*\*\* End of Report \*\*\*