

Test Report

Report No. : AGC05443220550-001

SAMPLE NAME : RPET beanie set, RPET beanie

MODEL NAME : MO6651, MO6659

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE: Jun.09, 2022

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Page 1 of 9

Applicant : MID OCEAN BRANDS B.V

7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon,

Hong Kong.

Test Site 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community,

Hangcheng Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : RPET beanie set, RPET beanie

Model : MO6651, MO6659

Country of Origin : CHINA Country of Destination : EUROPE Vendor code : 111587

Sample Received Date : May 31, 2022

Testing Period : May 31, 2022 to Jun.08, 2022

Test Requested: Conclusion

1. As specified by client, to determine the Aromatic Amines Azodyes(AZO) content in the submitted sample(s) with reference to entry 43, Annex XVII of the REACH Regulation (EC) No 1907/2006.

Pass

2. As specified by client, to determine the Polycyclic-aromatic hydrocarbons (PAHs) content in the submitted sample(s) with reference to entry 50, Annex XVII of the REACH Regulation (EC) No 1907/2006.

Pass

3. As specified by client, to determine the Phthalates content in the submitted sample(s) with reference to entry 51&52, Annex XVII of the REACH Regulation (EC) No 1907/2006.

Pass

4. As specified by client, to determine the Cadmium(Cd) content in the submitted sample(s) with reference to entry 23, Annex XVII of the REACH Regulation (EC) No 1907/2006.

Pass

5. As specified by client, to determine the Lead(Pb) content in the submitted sample(s) with reference to entry 63, Annex XVII of the REACH Regulation (EC) No 1907/2006.

Pass

6. As specified by client, to determine Colour fastness to rubbing in the submitted sample(s).

Pass

Approved by: mengushua

Approved by:

Huangguohua

Liangdan, Jessie.Liang

Vice Laboratory Manager

Technical Director



Page 2 of 9

Report Revise Record

Report Version	Issued Date	Valid Version	Notes
/	Jun.09, 2022	Valid	Initial release




Page 3 of 9

Test Result(s):

1. Test Result of Aromatic Amines Azodyes(AZO) Content

Test Item	CAS No.	Test Method/ Instrument	MDL	Limit
4-Aminobiphenyl	92-67-1		5mg/kg	≤30mg/kg
Benzidine	92-87-5		5mg/kg	≤30mg/kg
4-Chloro-o-Toluidine	95-69-2		5mg/kg	≤30mg/kg
2-Naphthylamine	91-59-8		5mg/kg	≤30mg/kg
4-amino-2',3-dimethylazobenzene	97-56-3		5mg/kg	≤30mg/kg
5-Nitro-o-toluidine	99-55-8		5mg/kg	≤30mg/kg
4-Chloroaniline	106-47-8		5mg/kg	≤30mg/kg
4-Methoxy-m-phenylenediamine	615-05-4		5mg/kg	≤30mg/kg
4,4'-Diaminodiphenylmethane	101-77-9		5mg/kg	≤30mg/kg
3,3'-Dichlorobenzidine	91-94-1		5mg/kg	≤30mg/kg
3,3'-Dimethoxybenzidine	119-90-4	EN ISO 14362-1:2017/	5mg/kg	≤30mg/kg
3,3'-Dimethybenzidine	119-93-7	GC-MS	5mg/kg	≤30mg/kg
4,4'-Methylenedi-o-toluidine	838-88-0		5mg/kg	≤30mg/kg
6-methoxy-m-toluidine	120-71-8		5mg/kg	≤30mg/kg
4,4'-methylenebis[2-chloroaniline]	101-14-4		5mg/kg	≤30mg/kg
4,4'-Oxydianiline	101-80-4		5mg/kg	≤30mg/kg
4,4'-Thiodianiline	139-65-1		5mg/kg	≤30mg/kg
2-Aminotoluene	95-53-4		5mg/kg	≤30mg/kg
4-methyl-m-phenylenediamine	95-80-7		5mg/kg	≤30mg/kg
2,4,5-Trimethylaniline	137-17-7		5mg/kg	≤30mg/kg
2-Methoxyaniline	90-04-0		5mg/kg	≤30mg/kg
4-Aminoazobenzene ^a	60-09-3		5mg/kg	≤30mg/kg

Note: ^a The EN ISO 14362-1:2017 methods will enable further cleavage of 4-aminoazobenzene to aniline and/or 1,4-phenylenediamine. If aniline and/or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017.





T (11 ()	Result(s)	(mg/kg)
Test Item(s)	1-1△	1-2△
4-Aminobiphenyl	N.D.	N.D.
Benzidine	N.D.	N.D.
4-Chloro-o-Toluidine	N.D.	N.D.
2-Naphthylamine	N.D.	N.D.
4-amino-2',3-dimethylazobenzene	N.D.	N.D.
5-Nitro-o-toluidine	N.D.	N.D.
4-Chloroaniline	N.D.	N.D.
4-Methoxy-m-phenylenediamine	N.D.	N.D.
4,4'-Diaminodiphenylmethane	N.D.	N.D.
3,3'-Dichlorobenzidine	N.D.	N.D.
3,3'-Dimethoxybenzidine	N.D.	N.D.
3,3'-Dimethybenzidine	N.D.	N.D.
4,4'-Methylenedi-o-toluidine	N.D.	N.D.
6-methoxy-m-toluidine	N.D.	N.D.
4,4'-methylenebis[2-chloroaniline]	N.D.	N.D.
4,4'-Oxydianiline	N.D.	N.D.
4,4'-Thiodianiline	N.D.	N.D.
2-Aminotoluene	N.D.	N.D.
4-methyl-m-phenylenediamine	N.D.	N.D.
2,4,5-Trimethylaniline	N.D.	N.D.
2-Methoxyaniline	N.D.	N.D.
4-Aminoazobenzene	N.D.	N.D.
Conclusion	Conformity	Conformity



Page 5 of 9

2. Test Result of Polycyclic-aromatic hydrocarbons (PAHs)Content

Test Item	Test Method/ Instrument	MDL	Limit
Benzo[a]pyrene (BaP) (CAS No.: 50-32-8)		0.1mg/kg	
Benzo[e]pyrene(BeP) (CAS No.: 192-97-2)		0.1mg/kg	
Benzo[a]anthracene (BaA) (CAS No.: 56-55-3)	_	0.1mg/kg	
Benzo[b]fluoranthene (BbF) (CAS No.: 205-99-2)	AfPS GS 2019:01 PAK/	0.1mg/kg	Rubber or plastic
Benzo[j]fluoranthene(BjFA) (CAS No.: 205-82-3)	GC-MS	0.1mg/kg	components: Single≤1mg/kg
Benzo[k]fluoranthene (BkF) (CAS No.: 207-08-9)	-	0.1mg/kg	
Chrysene (CHR) (CAS No.: 218-01-9)	-	0.1mg/kg	
Dibenzo[a,h]anthracene (DBA) (CAS No.: 53-70-3)	_	0.1mg/kg	

T4 I4(-)	Result(s) (mg/kg)
Test Item(s)	1-4
Benzo[a]pyrene (BaP)	N.D.
Benzo[e]pyrene(BeP)	N.D.
Benzo[a]anthracene (BaA)	N.D.
Benzo[b]fluoranthene (BbF)	N.D.
Benzo[j]fluoranthene(BjFA)	N.D.
Benzo[k]fluoranthene (BkF)	N.D.
Chrysene (CHR)	N.D.
Dibenzo[a,h]anthracene (DBA)	N.D.
Sum of PAHs	N.D.
Conclusion	Conformity



Page 6 of 9

3. Test Result of Phthalates Content

Test Item	Test Method/ Instrument	MDL	Limit
Diisobutyl phthalate(DIBP)		0.010%	
(CAS No.: 84-69-5)		0.01070	
Dibutyl phthalate (DBP)		0.010%	
(CAS No.: 84-74-2)		0.01070	Single<0.1%
Butylbenzyl phthalate (BBP)		0.010%	Sum<0.1%
(CAS No.: 85-68-7)		0.01070	
Di-(2-ethylhexyl) Phthalate (DEHP)	EN 14272 2004/ GG 34G	0.010%	
(CAS No.: 117-81-7)	EN 14372:2004/ GC-MS	0.01070	
Di-n-octyl phthalate (DNOP)		0.010%	
(CAS No.: 117-84-0)		0.01070	
Di-isononyl phthalate (DINP)		0.010%	G <0.10/
(CAS No.: 28553-12-0; 68515-48-0)		0.01070	Sum<0.1%
Di-isodecyl phthalate(DIDP)		0.0100/	
(CAS No.: 26761-40-0; 68515-49-1)		0.010%	

Test		Test result (%)								
point	DIBP	DBP	BBP	DEHP	Sum(DIBP+DBP +BBP+DEHP)	DNOP	DINP	DIDP	Sum(DNOP+ DINP+DIDP)	
1-4	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	Conformity

4. Test Result of Cadmium(Cd) Content

Test Item	Cadmium(Cd) (CAS No.: 7440-43-9)		
Limit(mg/kg)	<100		
MDL(mg/kg)	10		
Test Method/ Instrument	IEC 62321-5:2013/ ICP-OES		

Tost point	Test result (mg/kg)	Complysion
Test point	Cadmium(Cd)	Conclusion
1-1△	N.D.	Conformity
1-2△	N.D.	Conformity
1-3	N.D.	Conformity
1-4	N.D.	Conformity



Page 7 of 9

5. Test Result of Lead(Pb) Content

Test Item	Lead(Pb) (CAS No.: 7439-92-1)			
Limit(mg/kg)	<500			
MDL(mg/kg)	10			
Test Method/ Instrument	IEC 62321-5:2013/ ICP-OES			

Took noint	Test result (mg/kg)	Camalanian
Test point	Lead(Pb)	Conclusion
1-1△	N.D.	Conformity
1-2△	N.D.	Conformity
1-3	N.D.	Conformity
1-4	N.D.	Conformity

Note:

mg/kg = milligram per kilogram N.D.=Not Detected (less than method detection limit)

MDL = Method Detection Limit %= percentage

Remark:

- As specified by client, only test the designated sample.

- \triangle =As specified by client, the submitted samples were mixed to test.

6. Test Results of Colour fastness to rubbing

Test Method: ISO 105-X12:2016


Rubbing finger: Cylinder

The time of conditioning as well as the atmospheric conditions during testing: 20 °C, 65 %R.H., 4 hrs

The long direction of the specimen: Warp/ Weft

The percentage of soak of wet rubbing cloth: 95%~100%

	Test l		
Test point	Colour fastness to	Conclusion	
	Dry rubbing	Wet rubbing	
1-5	4-5	4-5	Conformity
1-6	4-5	4-5	Conformity
1-7	4-5	4-5	Conformity
1-8	4-5	4-5	Conformity
Limit (Client's Requirement)	≥2-3	≥2-3	/





Note:

Colour Fastness Grade:

Grade 5 = No Colour Change (Best Grade)

Grade 1 = Colour Change Seriously (Bad Grade)


9 grades in gray sample card: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.


Test Point Description

1000 1 0mm 2 000 1 pm 1	
Test point	Test point description
1-1	Black fabric (gloves)+Grey fabric (gloves)
1-2	Black fabric (HAT)+Off white hat (HAT)
1-3	Label
1-4	Brown Leather
1-5	Black fabric (gloves)
1-6	Grey fabric (gloves)
1-7	Black fabric (HAT)
1-8	Off white hat (HAT)

Test Flow Chart

1. For AZO, PAHs, Phthalates







The photo of the sample





AGC05443220550-001

AGC authenticate the photo only on original report

*** End of Report ***



Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations.
- 7.Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.