Report No.:S22122302302E-R1 Page 1 of 4

# **TEST REPORT**

Applicant:
Address:

Product name: Lithium-ion Rechargeable Cell

Test model: BTW INR 1865025EC

Serial model: BTW INR 1865026EC, BTW INR 1865025PC, BTW INR 1865032EC,

BTW INR 1865026B, BTW INR 1865025FC, BTW INR 1865020PC,

INR 1865020, BTW INR 2170040PC, BTW INR 2170045EC,

BTW INR 2170050EC, BTW INR 2170040EC, BTW INR 2170048B,

BTW INR 2170040HC,,BTW INR 2170042EC

Manufacturer&

Factory: Address:

Sample Received

Jun. 10, 2025

Date:

Testing Period: Jun. 10, 2025~Jun. 26, 2025

#### **Test Requirement:**

As specified by client, to test Lead(Pb), Cadmium(Cd), Mercury(Hg) contents of the submitted sample(s) in accordance with Regulation (EU) 2023/1542.

**Test Result(s):** Please refer to the following page(s);

**Test Method:** Please refer to the following page(s);

Approved by:

Reviewed by:

Date:

2025-06-26

Shenzhen NTEK Testing Technology Co., Ltd. Address: 1/F, Building E, Fenda Science Park, Sanwei Community, Xixiang Street, Bao'an District, Shenzhen 518126 P.R.China. | Tel: +86-755-2320 0050 | http://www.ntek.org.cn
Complaint Tel: +86-755-23218370 | Complaint E-mail: complaint@ntek.org.cn



Report No.: S22122302302E-R1

Page 2 of 4

## Test Result(s):

Test item(s)	Limit (%)	Result(s),(%)
Lead (Pb)	0.0100	N.D.
Cadmium (Cd)	0.0020	N.D.
Mercury (Hg)	0.0005	N.D.
Conclusion		Pass

## **Sample Description:**

Battery

Note: N.D. = Not Detected (<MDL)

MDL = Method Detection Limit /=Not Regulated or Not Applicable

#### Remark:

- 1. According to Regulation (EU) 2023/154, All batteries containing more than 0.002 % cadmium or more than 0.004 % lead, shall be marked with the chemical symbol for the metal concerned: Cd or Pb.
- 2. The relevant chemical symbol indicating the heavy metal content shall be printed beneath the separate collection symbol and shall cover an area of at least one-quarter the size of that symbol.
- 3. Results shown are of total weight of the battery sample
- 4. The test results in this report are only responsible for the tested samples. According to the client's statement, series models are the same material as the test models. The series model samples provided by customers have not been tested in this report.

## Test Method:

Testing Item(s)	Test Method	Test instrument	MDL(%)
Lead (Pb)	Refer to IEC 62321-5:2013	ICP-OES	0.0005
Cadmium (Cd)	Refer to IEC 62321-5:2013	ICP-OES	0.0005
Mercury (Hg)	Refer to IEC 62321-4:2013+AMD1:2017	ICP-OES	0.0001




Report No.:S22122302302E-R1


Page 3 of 4

#### **Test Flow:**

1. Lead (Pb), Cadmium (Cd)



## 2. Mercury (Hg)







Report No.:S22122302302E-R1

## Sample photo(s):




Fig.1

This test report displaces the original report No. S22122302302E, and the original one was invalid since the date of this test report released.

## \*\*\*\* End of Report\*\*\*\*

The test results or data in this report will be used only for education, scientific research, enterprise product development and internal quality control or other purposes.

The test report is effective only with both signature and specialized stamp, The result(s) shown in this report refer only to the sample(s) tested. Without written approval of NTEK, this report can't be reproduced except in full.







## TEST REPORT IEC 62133-2

Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells, and for batteries made from them, for use in portable applications – Part 2: Lithium systems

 Report Number......
 CN23QNCN 001

 Date of issue......
 2025-01-13

Total number of pages.....: 39 pages

Name of Testing Laboratory

preparing the Report .....: Shenzhen NCT Testing Technology Co., Ltd

Applicant's name....:

Address....::

Test specification:

Standard.....: IEC 62133-2:2017, IEC 62133-2:2017/AMD1:2021

Test procedure....: CB Scheme

Non-standard test method .....: N/A

TRF template used .....: IECEE OD-2020-F1:2021, Ed.1.4

Test Report Form No. ....: IEC62133\_2C

Test Report Form(s) Originator....: DEKRA Certification B.V.

Master TRF .....: Dated 2022-07-01

Copyright © 2022 IEC System of Conformity Assessment Schemes for Electrotechnical Equipment and Components (IECEE System). All rights reserved.

This publication may be reproduced in whole or in part for non-commercial purposes as long as the IECEE is acknowledged as copyright owner and source of the material. IECEE takes no responsibility for and will not assume liability for damages resulting from the reader's interpretation of the reproduced material due to its placement and context.

If this Test Report Form is used by non-IECEE members, the IECEE/IEC logo and the reference to the CB Scheme procedure shall be removed.

This report is not valid as a CB Test Report unless signed by an approved IECEE Testing Laboratory and appended to a CB Test Certificate issued by an NCB in accordance with IECEE 02.

#### General disclaimer:

The test results presented in this report relate only to the object tested.

This report shall not be reproduced, except in full, without the written approval of the Issuing NCB. The authenticity of this Test Report and its contents can be verified by contacting the NCB, responsible for this Test Report.

Page 2 of 39 Report No.: CN23QNCN 001

	•		•	
Test item description:	Lithiun	n-ion Cell		
Trade Mark(s):	N/A			
Manufacturer:	Same as applicant			
Model/Type reference::	4). IMF 7). INF 10). IN	R18650L18; 5). INR1865 R18650T22; 8). INR1865	0L22; 9). INR18650T25; 650T26; 12). INR18650L26;	
Ratings:	4). 3.7 7). 3.7 10). 3.	7V, 1200mAh; 2). 3.7V, 1600mAh; 3). 3.7V, 1800mAh; 7V, 1800mAh; 5). 3.7V, 2000mAh; 6). 3.7V, 2000mAh; 7V, 2200mAh; 8). 3.7V, 2200mAh; 9). 3.7V, 2500mAh; 3.7V, 2500mAh; 11). 3.7V, 2600mAh; 12). 3.7V, 2600mAh; 3.7V, 3000mAh; 14). 3.7V, 3200mAh		
Pennancials Testing Laboratory (co	onnlie	able) testing presedu	ro and toating location(a).	
Responsible Testing Laboratory (as	аррис			
☐ CB Testing Laboratory:			ng Technology Co., Ltd	
Testing location/ address	:	A101A&2F, B2, Fuqiao Street, Baoan District,		
Tested by (name, function, signature	e):	King Chen (Project Engineer)	jung den	
Approved by (name, function, signa	iture) :	Hely Wang (Reviewer)	Hely Wong	
☐ Testing procedure: CTF Stage	1.			
Testing location/ address				
Tested by (name, function, signature				
Approved by (name, function, signa				
	•			
☐ Testing procedure: CTF Stage	2:			
Testing location/ address	:			
Tested by (name + signature)	:			
Witnessed by (name, function, signa	ature):			
Approved by (name, function, signa	ture):			
☐ Testing procedure: CTF Stage	3:			
☐ Testing procedure: CTF Stage	4:			
Testing location/ address	:			
Tested by (name, function, signatur	e):			
Witnessed by (name, function, signa	ature):			
Approved by (name, function, signa	ture) :			
Supervised by (name, function, signa	ature):			

Page 3 of 39 Report No.: CN23QNCN 001

#### List of Attachments (including a total number of pages in each attachment):

Attachment 1: (Republic of Korea) National Differences (4 pages).

Attachment 2: Photo documentation (6 pages).

#### Summary of testing:

#### Tests performed (name of test and test clause):

cl.7.1 Charging procedure for test purposes (for Cells);

cl.7.2.1 Continuous charging at constant voltage (Cells);

cl.7.3.1 External short circuit (Cells);

cl.7.3.3 Free fall (Cells);

cl.7.3.4 Thermal abuse (Cells);

cl.7.3.5 Crush (Cells);

cl.7.3.7 Forced discharge (Cells);

cl.7.3.9 Design evaluation – Forced internal short-circuit (Cells);

#### **Testing location:**

Shenzhen NCT Testing Technology Co., Ltd A101A&2F, B2, Fuqiao 6th Area, Xintian Community, Fuhai Street, Baoan District, Shenzhen, China

Tests are made with the number of cells specified in IEC 62133-2: 2017, IEC 62133-2:2017/AMD1:2021 Table 1.

#### Summary of compliance with National Differences (List of countries addressed):

KR

KR=Korea, Republic of

☑ The product fulfils the requirements of EN 62133-2:2017, EN 62133-2: 2017/A1:2021

Page 4 of 39 Report No.: CN23QNCN 001

Use of uncertainty of measurement for decisions on conformity (decision rule) :
☑ No decision rule is specified by the IEC standard, when comparing the measurement result with the applicable limit according to the specification in that standard. The decisions on conformity are made without applying the measurement uncertainty ("simple acceptance" decision rule, previously known as "accuracy method").
☐ Other: (to be specified, for example when required by the standard or client, or if national accreditation requirements apply)
Information on uncertainty of measurement:  The uncertainties of measurement are calculated by the laboratory based on application of criteria given by OD-5014 for test equipment and application of test methods, decision sheets and operational procedures of IECEE.
IEC Guide 115 provides guidance on the application of measurement uncertainty principles and applying the decision rule when reporting test results within IECEE scheme, noting that the reporting of the measurement uncertainty for measurements is not necessary unless required by the test standard or customer.
Calculations leading to the reported values are on file with the NCB and testing laboratory that conducted the testing.

Page 5 of 39 Report No.: CN23QNCN 001

Copy of marking plate: The artwork below may be only a draft. The use of certification marks on a product must be authorized by the respective NCBs that own these marks.
N/A
Remark:
By agreement between the cell manufacturer and the battery and/or end product manufacturer, component cells used in the manufacture of a battery need not be marked.

## General product information and other remarks:

The cell consists of the positive electrode plate, negative electrode plate, separator, electrolyte, case. The positive and negative electrode plates are housed in the case in the state being separated by the separator.

#### Model Differences:

Models IMR18650T12, IMR18650T16, IMR18650T18, IMR18650L18, INR18650T20, INR1865020, INR18650T22, INR18650L22, INR18650T25, INR18650L25, INR18650T26, INR18650L26, INR18650L30, INR18650L32 are identical to each other except for capacity and colour. All the models are manufactured through the same production process, the tested models IMR18650T12, IMR18650T16, IMR18650T18, INR18650L22, INR18650L26, INR18650L32 are representatives of other models.


The main features of the cell are shown as below (clause 7.1.1):

Model (cell)	Nominal capacity	Nominal voltage	Nominal Charge Current	Nominal Discharg e Current	Maximum Charge Current	Maximum Discharge Current	Maximum Charge Voltage	Final Voltage
IMR186 50T12	1200mAh	3.7V	600mA	600mA	2400mA	3000mA	4.25V	2.5V
IMR186 50T16	1600mAh	3.7V	800mA	<b>8</b> 00mA	3200mA	4000mA	4.25V	2.5V
IMR186 50T18	1800mAh	3.7V	900mA	900mA	3600mA	4500mA	4.25V	2.5V
IMR186 50L18	1800mAh	3.7V	900mA	900mA	3600mA	4500mA	4.25V	2.5V
INR1865 0T20	2000mAh	3.7V	1000mA	1000mA	4000mA	5000mA	4.25V	2.5V
INR1865 0L20	2000mAh	3.7V	1000mA	1000mA	4000mA	5000mA	4.25V	2.5V
INR1865 0T22	2200mAh	3.7V	1100mA	1100mA	4400mA	5500mA	4.25V	2.5V
INR1865 0L22	2200mAh	3.7V	1100mA	1100mA	4400mA	5500mA	4.25V	2.5V
INR1865 0T25	2500mAh	3.7V	1250mA	1250mA	5000mA	6250mA	4.25V	2.5V
INR1865 0L25	2500mAh	3.7V	1250mA	1250mA	5000mA	6250mA	4.25V	2.5V
INR1865 0T26	2600mAh	3.7V	1300mA	1300mA	5200mA	6500mA	4.25V	2.5V
INR1865 0L26	2600mAh	3.7V	1300mA	1300mA	5200mA	6500mA	4.25V	2.5V
INR1865 0L30	3000mAh	3.7V	1500mA	1500mA	6000mA	7500mA	4.25V	2.5V
INR1865 0L32	3200mAh	3.7V	1600mA	1600mA	6400mA	8000mA	4.25V	2.5V

The main features of the cell are shown as below (clause 7.1.2):

			`	,
Model (cell)	Upper limit charge voltage	Taper-off current	Lower charge temperature	Upper charge temperature
IMR18650 T12	4.25V	60mA	0°C	45°C
IMR18650 T16	4.25V	80mA	0°C	45°C
IMR18650 T18	4.25V	90mA	0°C	45°C
IMR18650 L18	4.25V	90mA	0°C	45°C
INR18650 T20	4.25V	100mA	0°C	45°C
INR18650 L20	4.25V	100mA	0°C	45°C
INR18650 T22	4.25V	110mA	0°C	45°C
INR18650 L22	4.25V	110mA	0°C	45°C
INR18650 T25	4.25V	125mA	0°C	45°C
INR18650 L25	4.25V	125mA	0°C	45°C
INR18650 T26	4.25V	130mA	0°C	45°C
INR18650 L26	4.25V	130mA	0°C	45°C
INR18650 L30	4.25V	150mA	0°C	45°C
INR18650 L32	4.25V	160mA	0°C	45°C

## Construction:



Height: 65.0±0.3mm; Diameter: 18.3±0.3mm Cell

Circuit diagram: None, cell only.

	Page 10 of 39	Report No.: CN23	BQNCN 00
	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
4	PARAMETER MEASUREMENT TOLERANCES		Р
	Parameter measurement tolerances		Р
_			
5	GENERAL SAFETY CONSIDERATIONS		P
5.1	General		P
	Cells and batteries so designed and constructed that they are safe under conditions of both intended use and reasonably foreseeable misuse		Р
5.2	Insulation and wiring		N/A
	The insulation resistance between the positive terminal and externally exposed metal surfaces of the battery (excluding electrical contact surfaces) is not less than 5 $M\Omega$	Cell only.	N/A
	Insulation resistance (MΩ)		_
	Internal wiring and insulation are sufficient to withstand maximum anticipated current, voltage and temperature requirements		N/A
	Orientation of wiring maintains adequate clearances and creepage distances between conductors		N/A
	Mechanical integrity of internal connections accommodates reasonably foreseeable misuse		N/A
5.3	Venting		Р
	Battery cases and cells incorporate a pressure relief mechanism or are constructed so that they relieve excessive internal pressure at a value and rate that will preclude rupture, explosion and self-ignition	Venting mechanism exists on the top of cylindrical cell.	Р
	Encapsulation used to support cells within an outer casing does not cause the battery to overheat during normal operation nor inhibit pressure relief		N/A
5.4	Temperature, voltage and current management		N/A
	Batteries are designed such that abnormal temperature rise conditions are prevented	Cell only.	N/A
	Batteries are designed to be within temperature, voltage and current limits specified by the cell manufacturer		N/A
	Batteries are provided with specifications and charging instructions for equipment manufacturers so that specified chargers are designed to maintain charging within the temperature, voltage and current limits specified		N/A
5.5	Terminal contacts		Р
	The size and shape of the terminal contacts ensure that they can carry the maximum anticipated current		Р

	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
	External terminal contact surfaces are formed from conductive materials with good mechanical strength and corrosion resistance		Р
	Terminal contacts are arranged to minimize the risk of short circuits		Р
5.6	Assembly of cells into batteries		N/A
5.6.1	General		N/A
	Each battery has an independent control and protection for current, voltage, temperature and any other parameter required for safety and to maintain the cells within their operating region	Cell only.	N/A
	This protection may be provided external to the battery such as within the charger or the end devices		N/A
	If protection is external to the battery, the manufacturer of the battery provide this safety relevant information to the external device manufacturer for implementation		N/A
	If there is more than one battery housed in a single battery case, each battery has protective circuitry that can maintain the cells within their operating regions		N/A
	Manufacturers of cells specify current, voltage and temperature limits so that the battery manufacturer/designer may ensure proper design and assembly		N/A
	Batteries that are designed for the selective discharge of a portion of their series connected cells incorporate circuitry to prevent operation of cells outside the limits specified by the cell manufacturer		N/A
	Protective circuit components are added as appropriate and consideration given to the end-device application		N/A
	The manufacturer of the battery provide a safety analysis of the battery safety circuitry with a test report including a fault analysis of the protection circuit under both charging and discharging conditions confirming the compliance		N/A
5.6.2	Design recommendation		N/A
	For the battery consisting of a single cell or a single cellblock, it is recommended that the charging voltage of the cell does not exceed the upper limit of the charging voltage specified in Table 2	,	N/A

	IEC 62133-2	·	
Clause	Requirement + Test	Result - Remark	Verdict
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks, it is recommended that the voltages of any one of the single cells or single cellblocks does not exceed the upper limit of the charging voltage, specified in Table 2, by monitoring the voltage of every single cell or the single cellblocks		N/A
	For the battery consisting of series-connected plural single cells or series-connected plural cellblocks, it is recommended that charging is stopped when the upper limit of the charging voltage is exceeded for any one of the single cells or single cellblocks by measuring the voltage of every single cell or the single cellblocks		N/A
	For batteries consisting of series-connected cells or cell blocks, nominal charge voltage are not counted as an overcharge protection		N/A
	For batteries consisting of series-connected cells or cell blocks, cells have closely matched capacities, be of the same design, be of the same chemistry and be from the same manufacturer		N/A
	It is recommended that the cells and cell blocks are not discharged beyond the cell manufacturer's specified final voltage		N/A
	For batteries consisting of series-connected cells or cell blocks, cell balancing circuitry are incorporated into the battery management system		N/A
5.6.3	Mechanical protection for cells and components of batteries	Cell only.	N/A
	Mechanical protection for cells, cell connections and control circuits within the battery are provided to prevent damage as a result of intended use and reasonably foreseeable misuse		N/A
	The mechanical protection can be provided by the battery case or it can be provided by the end product enclosure for those batteries intended for building into an end product		N/A
	The battery case and compartments housing cells are designed to accommodate cell dimensional tolerances during charging and discharging as recommended by the cell manufacturer		N/A
	For batteries intended for building into a portable end product, testing with the battery installed within the end product is considered when conducting mechanical tests		N/A
5.7	Quality plan		Р

Page 13 of 39	Report No.: CN2	23QNCN 00
IEC 62133-2		
Requirement + Test	Result - Remark	Verdict
The manufacturer prepares and implements a quality plan that defines procedures for the inspection of materials, components, cells and batteries and which covers the whole process of producing each type of cell or battery	Complied. ISO 9001: 2015 certificate provided.	Р
Battery safety components	See TABLE: Critical components information	N/A
TYPE TEST AND SAMPLE SIZE		Р
Tests are made with the number of cells or batteries specified in Table 1 using cells or batteries that are not more than six months old		Р
The internal resistance of coin cells are measured in accordance with Annex D. Coin cells with internal resistance less than or equal to 3 $\Omega$ are tested in accordance with Table 1		N/A
Unless otherwise specified, tests are carried out in an ambient temperature of 20 °C ± 5 °C		Р
The safety analysis of 5.6.1 identify those components of the protection circuit that are critical for short-circuit, overcharge and over discharge protection	Cell only.	N/A
When conducting the short-circuit test, consideration is given to the simulation of any single fault condition that is likely to occur in the protecting circuit that would affect the short-circuit test	Cell only.	N/A
SPECIFIC REQUIREMENTS AND TESTS		Р
Charging procedure for test purposes		Р
First procedure		Р
This charging procedure applies to subclauses other than those specified in 7.1.2		Р
Unless otherwise stated in this document, the charging procedure for test purposes is carried out in an ambient temperature of 20 °C ± 5 °C, using the method declared by the manufacturer		Р
Prior to charging, the battery has been discharged at $20 ^{\circ}\text{C} \pm 5 ^{\circ}\text{C}$ at a constant current of 0,2 lt A down to a specified final voltage		Р
Second procedure		Р
This charging procedure applies only to 7.3.1, 7.3.4, 7.3.5, and 7.3.9		Р
	Requirement + Test  The manufacturer prepares and implements a quality plan that defines procedures for the inspection of materials, components, cells and batteries and which covers the whole process of producing each type of cell or battery  Battery safety components  TYPE TEST AND SAMPLE SIZE  Tests are made with the number of cells or batteries specified in Table 1 using cells or batteries that are not more than six months old  The internal resistance of coin cells are measured in accordance with Annex D. Coin cells with internal resistance less than or equal to 3 Ω are tested in accordance with Table 1  Unless otherwise specified, tests are carried out in an ambient temperature of 20 °C ± 5 °C  The safety analysis of 5.6.1 identify those components of the protection circuit that are critical for short-circuit, overcharge and over discharge protection  When conducting the short-circuit test, consideration is given to the simulation of any single fault condition that is likely to occur in the protecting circuit that would affect the short-circuit test  SPECIFIC REQUIREMENTS AND TESTS  Charging procedure for test purposes  First procedure  This charging procedure applies to subclauses other than those specified in 7.1.2  Unless otherwise stated in this document, the charging procedure for test purposes is carried out in an ambient temperature of 20 °C ± 5 °C, using the method declared by the manufacturer  Prior to charging, the battery has been discharged at 20 °C ± 5 °C at a constant current of 0,2 lt A down to a specified final voltage  Second procedure  This charging procedure applies only to 7.3.1, 7.3.4,	Requirement + Test

Page 14 of 39 Report No.: CN23QNCN 001

	IEC 62133-2	Report No.: CN2	
Clause	Requirement + Test	Result - Remark	Verdict
	After stabilization for 1 h to 4 h, at an ambient temperature of the highest test temperature and the lowest test temperature, respectively, as specified in Table 2, cells are charged by using the upper limit charging voltage and maximum charging current, until the charging current is reduced to 0,05 lt A, using a constant current to constant voltage charging method	Charge temperature range: 0-45°C declared. 0°C used for lower limit tests. 45°C used for upper limit tests.	Р
7.2	Intended use		Р
7.2.1	Continuous charging at constant voltage (cells)	Tested complied.	Р
	Fully charged cells are subjected for 7 days to a charge using the charging method for current and standard voltage specified by the cell manufacturer	Charging for 7 days with 0.5C.	Р
	Results: no fire, no explosion, no leakage:	(See appended table 7.2.1)	Р
7.2.2	Case stress at high ambient temperature (battery)	Cell only.	N/A
	Oven temperature (°C):		
	Results: no physical distortion of the battery case resulting in exposure of internal protective components and cells		N/A
7.3	Reasonably foreseeable misuse		Р
7.3.1	External short-circuit (cell)	Tested complied.	Р
	The cells were tested until one of the following occurred:		Р
	- 24 hours elapsed; or		N/A
	- The case temperature declined by 20 % of the maximum temperature rise		Р
	Results: no fire, no explosion:	(See appended table 7.3.1)	Р
7.3.2	External short-circuit (battery)	Cell only.	N/A
	The batteries were tested until one of the following occurred:		N/A
	- 24 hours elapsed; or		N/A
	- The case temperature declined by 20 % of the maximum temperature rise		N/A
	In case of rapid decline in short circuit current, the battery pack remained on test for an additional one hour after the current reached a low end steady state condition		N/A
	A single fault in the discharge protection circuit is conducted on one to four (depending upon the protection circuit) of the five samples before conducting the short-circuit test		N/A

	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
	A single fault applies to protective component parts such as MOSFET (metal oxide semiconductor field-effect transistor), fuse, thermostat or positive temperature coefficient (PTC) thermistor		N/A
	Results: no fire, no explosion:		N/A
7.3.3	Free fall	Tested complied.	Р
	Results: no fire, no explosion	No fire. No explosion	Р
7.3.4	Thermal abuse (cells)	Tested complied.	Р
	Oven temperature (°C)	130°C	_
	Results: no fire, no explosion	No fire. No explosion	Р
7.3.5	Crush (cells)	Tested complied.	Р
	The crushing force was released upon:		Р
	- The maximum force of 13 kN $\pm$ 0,78 kN has been applied; or		Р
	- An abrupt voltage drop of one-third of the original voltage has been obtained		N/A
	Results: no fire, no explosion:	(See appended table 7.3.5)	Р
7.3.6	Over-charging of battery	Cell only.	N/A
	The supply voltage which is:		N/A
	- 1,4 times the upper limit charging voltage presented in Table A.1 (but not to exceed 6,0 V) for single cell/cell block batteries or		N/A
	- 1,2 times the upper limit charging voltage resented in Table A.1 per cell for series connected multi-cell batteries, and		N/A
	- Sufficient to maintain a current of 2,0 lt A throughout the duration of the test or until the supply voltage is reached		N/A
	Test was continued until the temperature of the outer casing:		N/A
	- Reached steady state conditions (less than 10 °C change in 30-minute period); or		N/A
	- Returned to ambient		N/A
	Results: no fire, no explosion		N/A
7.3.7	Forced discharge (cells)	Tested complied.	Р
	Discharge a single cell to the lower limit discharge voltage specified by the cell manufacturer		Р
	The discharged cell is then subjected to a forced discharge at 1 lt A to the negative value of the upper limit charging voltage		Р

	Page 16 of 39	Report No.: CN2	3QNCN 00
	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
	- The discharge voltage reaches the negative value of upper limit charging voltage within the testing duration. The voltage is maintained at the negative value of the upper limit charging voltage by reducing the current for the remainder of the testing duration		N/A
	- The discharge voltage does not reach the negative value of upper limit charging voltage within the testing duration. The test is terminated at the end of the testing duration		Р
	Results: no fire, no explosion:	(See appended table 7.3.7)	Р
7.3.8	Mechanical tests (batteries)		N/A
7.3.8.1	Vibration	Cell only.	N/A
	Results: no fire, no explosion, no rupture, no leakage or venting:		N/A
7.3.8.2	Mechanical shock	Cell only.	N/A
	Results: no leakage, no venting, no rupture, no explosion and no fire		N/A
7.3.9	Design evaluation – Forced internal short-circuit (cells)	Tested complied.	Р
	The cells complied with national requirement for:	France, Japan, Korea, Switzerland	_
	The pressing was stopped upon:		Р
	- A voltage drop of 50 mV has been detected; or		N/A
	- The pressing force of 800 N (cylindrical cells) or 400 N (prismatic cells) has been reached	800N for cylindrical cells.	Р
	Results: no fire:	(See appended table 7.3.9)	Р

8	INFORMATION FOR SAFETY		Р
8.1	General		Р
	Manufacturers of secondary cells provides information about current, voltage and temperature limits of their products	Information for safety mentioned in manufacturer's specifications.	Р
	Manufacturers of batteries provides information regarding how to minimize and mitigate hazards to equipment manufacturers or end-users		N/A
	Systems analyses are performed by device manufacturers to ensure that a particular battery design prevents hazards from occurring during use of a product		N/A
	As appropriate, any information relating to hazard avoidance resulting from a system analysis is provided to the end user		N/A

Page 17 of 39 Report No.: CN23QNCN 001

	· · · · · · · · · · · · · · · · · · ·	•	
	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
	Do not allow children to replace batteries without adult supervision		N/A
8.2	Small cell and battery safety information	Not small cells.	N/A
	The following warning language is to be provided with the information packaged with the small cells and batteries or equipment using them:		N/A
	- Keep small cells and batteries which are considered swallowable out of the reach of children		N/A
	- Swallowing may lead to burns, perforation of soft tissue, and death. Severe burns can occur within 2 h of ingestion		N/A
	- In case of ingestion of a cell or battery, seek medical assistance promptly		N/A

9	MARKING		Р
9.1	Cell marking		Р
	Cells are marked as specified in IEC 61960, except coin cells		N/A
	Coin cells whose external surface area is too small to accommodate the markings on the cells show the designation and polarity		N/A
	By agreement between the cell manufacturer and the battery and/or end product manufacturer, component cells used in the manufacture of a battery need not be marked	Agreement between the cell manufacturer and user provided.	Р
9.2	Battery marking	Cell only.	N/A
	Batteries are marked as specified in IEC 61960, except for coin batteries		N/A
	Coin batteries whose external surface area is too small to accommodate the markings on the batteries show the designation and polarity		N/A
	Batteries are marked with an appropriate caution statement		N/A
	- Terminals have clear polarity marking on the external surface of the battery, or		N/A
	<ul> <li>Not be marked with polarity markings if the design of the external connector prevents reverse polarity connections</li> </ul>		N/A
9.3	Caution for ingestion of small cells and batteries	Not small cells.	N/A
	Coin cells and batteries identified as small batteries include a caution statement regarding the hazards of ingestion in accordance with 8.2	Not coin cells.	N/A

IEC 62133-2		
Requirement + Test	Result - Remark	Verdict
Small cells and batteries are intended for direct sale in consumer-replaceable applications, caution for ingestion is given on the immediate package		N/A
Other information		N/A
The following information are marked on or supplied with the battery:		N/A
- Storage and disposal instructions		N/A
- Recommended charging instructions		N/A
	Requirement + Test  Small cells and batteries are intended for direct sale in consumer-replaceable applications, caution for ingestion is given on the immediate package  Other information  The following information are marked on or supplied with the battery:  - Storage and disposal instructions	Requirement + Test  Small cells and batteries are intended for direct sale in consumer-replaceable applications, caution for ingestion is given on the immediate package  Other information  The following information are marked on or supplied with the battery:  - Storage and disposal instructions

•	10	PACKAGING AND TRANSPORT		N/A
		Packaging for coin cells are not be small enough to fit within the limits of the ingestion gauge of Figure 3		N/A

ANNEX A	CHARGING AND DISCHARGING RANGE OF SECONDARY LITHIUM ION CELLS FOR SAFE USE		Р
A.1	General		Р
A.2	Safety of lithium ion secondary battery	Complied.	Р
A.3	Consideration on charging voltage	Complied.	Р
A.3.1	General		Р
A.3.2	Upper limit charging voltage	4.25V applied.	Р
A.3.2.1	General		Р
A.3.2.2	Explanation of safety viewpoint		Р
A.3.2.3	Safety requirements, when different upper limit charging voltage is applied	4.25V applied.	N/A
A.4	Consideration of temperature and charging current		Р
A.4.1	General		Р
A.4.2	Recommended temperature range	Charging temperature range declared by client is: 0-45°C	Р
A.4.2.1	General		Р
A.4.2.2	Safety consideration when a different recommended temperature range is applied		N/A
A.4.3	High temperature range		N/A
A.4.3.1	General		N/A
A.4.3.2	Explanation of safety viewpoint		N/A
A.4.3.3	Safety considerations when specifying charging conditions in the high temperature range		N/A
A.4.3.4	Safety considerations when specifying a new upper limit in the high temperature range		N/A

	IEC 62133-2	Report No.: Civiz	
Clause	Requirement + Test	Result - Remark	Verdict
A.4.4	Low temperature range		N/A
A.4.4.1	General		N/A
A.4.4.2	Explanation of safety viewpoint		N/A
A.4.4.3	Safety considerations, when specifying charging conditions in the low temperature range		N/A
A.4.4.4	Safety considerations when specifying a new lower limit in the low temperature range		N/A
A.4.5	Scope of the application of charging current		Р
A.4.6	Consideration of discharge		Р
A.4.6.1	General		Р
A.4.6.2	Final discharge voltage and explanation of safety viewpoint	Cell specified final voltage 2.5V, not exceed 2.5V specified by cell manufacturer.	Р
A.4.6.3	Discharge current and temperature range		Р
A.4.6.4	Scope of application of the discharging current		Р
A.5	Sample preparation		Р
A.5.1	General		Р
A.5.2	Insertion procedure for nickel particle to generate internal short		Р
A.5.3	Disassembly of charged cell		Р
A.5.4	Shape of nickel particle		Р
A.5.5	Insertion of nickel particle in cylindrical cell		Р
A.5.5.1	Insertion of nickel particle in winding core		Р
A.5.5.2	Marking the position of the nickel particle on both ends of the winding core of the separator		Р
A.5.6	Insertion of nickel particle in prismatic cell		N/A
A.6	Experimental procedure of the forced internal short-circuit test		Р
A.6.1	Material and tools for preparation of nickel particle		Р
A.6.2	Example of a nickel particle preparation procedure		Р
A.6.3	Positioning (or placement) of a nickel particle		Р
A.6.4	Damaged separator precaution		Р
A.6.5	Caution for rewinding separator and electrode		Р
A.6.6	Insulation film for preventing short-circuit		Р
A.6.7	Caution when disassembling a cell		Р
A.6.8	Protective equipment for safety		Р
A.6.9	Caution in the case of fire during disassembling		Р

	Page 20 of 39	Report No.: CN2	3QNCN 0
	IEC 62133-2		
Clause	Requirement + Test	Result - Remark	Verdict
A.6.10	Caution for the disassembling process and pressing the electrode core		Р
A.6.11	Recommended specifications for the pressing device		Р
ANNEX B	RECOMMENDATIONS TO EQUIPMENT MANUF ASSEMBLERS	ACTURERS AND BATTERY	N/A
ANNEX C	RECOMMENDATIONS TO THE END-USERS		N/A
ANNEX D	MEASUREMENT OF THE INTERNAL AC RESIS	TANCE FOR COIN CELLS	N/A
D.1	General	Not coin cells.	N/A
D.2	Method		N/A
	A sample size of three coin cells is required for this measurement		N/A
	Coin cells with an internal resistance greater than 3 $\Omega$ require no further testing		N/A
	Coin cells with an internal resistance less than or equal to 3 $\Omega$ are subjected to the testing according to Clause 6 and Table 1		N/A
ANNEX E	PACKAGING AND TRANSPORT		N/A
ANNEX F	COMPONENT STANDARDS REFERENCES		N/A

			1 ago 21 01 00	Ropoli No.: ONZ	, Q. 10. 1 00
			IEC 62133-2		
Cla	ause	Requirement + Test		Result - Remark	Verdict

7.2.1 TABLE: Continuous charging at constant voltage (cells)					
Sample No.	Recommended charging voltage Vc (Vdc)	Recommended charging current $I_{rec}$ (A)	OCV before test (Vdc)	Results	
Model: IMR18650	T12				
NCT23027001- IMR18650T12-C1#	4.25	0.60	4.24	Р	
NCT23027001- IMR18650T12-C2#	4.25	0.60	4.24	Р	
NCT23027001- IMR18650T12-C3#	4.25	0.60	4.24	Р	
NCT23027001- IMR18650T12-C4#	4.25	0.60	4.24	Р	
NCT23027001- IMR18650T12-C5#	4.25	0.60	4.24	Р	
Model: IMR18650	T16				
NCT23027001- IMR18650T16-C1#	4.25	0.80	4.24	Р	
NCT23027001- IMR18650T16-C2#	4.25	0.80	4.24	Р	
NCT23027001- IMR18650T16-C3#	4.25	0.80	4.23	Р	
NCT23027001- IMR18650T16-C4#	4.25	0.80	4.24	Р	
NCT23027001- IMR18650T16-C5#	4.25	0.80	4.23	Р	
Model: IMR18650	T18				
NCT23027001- IMR18650T18-C1#	4.25	0.90	4.24	Р	
NCT23027001- IMR18650T18-C2#	4.25	0.90	4.24	Р	
NCT23027001- IMR18650T18-C3#	4.25	0.90	4.24	Р	
NCT23027001- IMR18650T18-C4#	4.25	0.90	4.24	Р	
NCT23027001- IMR18650T18-C5#	4.25	0.90	4.23	Р	
Model: INR18650	L22				
NCT23027001- INR18650L22-C1#	4.25	1.10	4.23	Р	
NCT23027001- INR18650L22-C2#	4.25	1.10	4.23	Р	

			Page 22 01 39	Kepon	. INO CINZS	CINCIN OC
			IEC 62133-2			
Clause	Require	ment + Test		Result - Remark		Verdict
	027001- 0L22-C3#	4.25	1.10	4.24	Р	
	027001- 0L22-C4#	4.25	1.10	4.23	Р	
	027001- 0L22-C5#	4.25	1.10	4.23	Р	
Model: II	NR18650L2	26				
	027001- 0L26-C1#	4.25	1.30	4.24	Р	
	027001- 0L26-C2#	4.25	1.30	4.23	Р	
	027001- 0L26-C3#	4.25	1.30	4.23	Р	
	027001- 0L26-C4#	4.25	1.30	4.24	Р	
	027001- 0L26-C5#	4.25	1.30	4.23	Р	
Model: II	NR18650L3	32				
	027001- 0L32-C1#	4.25	1.60	4.23	Р	
	027001- 0L32-C2#	4.25	1.60	4.23	Р	
	027001- 0L32-C3#	4.25	1.60	4.23	Р	
	027001- 0L32-C4#	4.25	1.60	4.24	Р	
	027001- 0L32-C5#	4.25	1.60	4.23	Р	
Sunnlem	entary inf	ormation:				

## Supplementary information:

- No fire or explosion
- No leakage

7.3.1	7.3.1 TABLE: External short circuit (cell)						
Sample No.  Ambient (°C)  Ambient (°C)  Column Ambient (°C)  Ambient (°C)  Column Ambient (°C)  Ambient (°C)  Column Ambient (°C)  Col						Re	sults
Model: IM	R18650T1	2					
	Sai	mples charge	ed at charging te	mperature uppe	er limit (45°C)		
	NCT23027001- IMR18650T12-C6# 55.5 4.20 78.5 76.7						Р
NCT23027001- IMR18650T12-C7#		55.5	4.21	83.2	80.2		Р

		IEC 621			. 01123Q11011 00
Clause Requirem	ent + Test			t - Remark	Verdict
NCT23027001- IMR18650T12-C8#	55.5	4.20	81.6	78.5	Р
NCT23027001- IMR18650T12-C9#	55.5	4.20	80.2	82.3	Р
NCT23027001- IMR18650T12-C10#	55.5	4.21	85.4	81.6	Р
Sa	amples charg	ed at charging t	emperature low	ver limit (0°C)	
NCT23027001- IMR18650T12-C11#	55.6	4.14	84.6	82.3	Р
NCT23027001- IMR18650T12-C12#	55.6	4.14	81.1	79.1	Р
NCT23027001- IMR18650T12-C13#	55.6	4.13	79.4	80.3	Р
NCT23027001- IMR18650T12-C14#	55.6	4.13	83.8	83.1	Р
NCT23027001- IMR18650T12-C15#	55.6	4.14	82.6	77.5	Р
Model: IMR18650T1	6				
Sai	mples charge	ed at charging te	emperature upp	er limit (45°C)	
NCT23027001- IMR18650T16-C6#	54.8	4.20	81.0	77.7	Р
NCT23027001- IMR18650T16-C7#	54.8	4.21	79.8	74.1	Р
NCT23027001- IMR18650T16-C8#	54.8	4.20	83.6	75.6	Р
NCT23027001- IMR18650T16-C9#	54.8	4.20	85.4	75.4	Р
NCT23027001- IMR18650T16-C10#	54.8	4.21	86.7	77.9	Р
Sa	amples charg	ed at charging t	emperature low	ver limit (0°C)	
NCT23027001- IMR18650T16-C11#	54.6	4.13	82.7	81.3	Р
NCT23027001- IMR18650T16-C12#	54.6	4.14	86.2	72.8	Р
NCT23027001- IMR18650T16-C13#	54.6	4.13	83.3	79.1	Р
NCT23027001- IMR18650T16-C14#	54.6	4.13	85.8	73.3	Р
NCT23027001- IMR18650T16-C15#	54.6	4.14	81.4	81.0	Р
Model: IMR18650T1	8	_		_	

Page 24 of 39 Report No.: CN23QNCN 001

		3	<u>!</u>	-
		IEC 62133-2		
Clause	Requirement + Test		Result - Remark	Verdict

Samples charged at charging temperature upper limit (45°C)								
NCT23027001- IMR18650T18-C6#	55.6	4.21	83.2	80.3	Р			
NCT23027001- IMR18650T18-C7#	55.6	4.21	78.9	82.4	Р			
NCT23027001- IMR18650T18-C8#	55.6	4.20	81.5	76.6	Р			
NCT23027001- IMR18650T18-C9#	55.6	4.21	85.6	81.9	Р			
NCT23027001- IMR18650T18-C10#	55.6	4.22	82.1	78.3	Р			
Sa	mples charg	ed at charging t	emperature low	er limit (0°C)				
NCT23027001- IMR18650T18-C11#	55.6	4.13	83.6	79.4	Р			
NCT23027001- IMR18650T18-C12#	55.6	4.14	82.4	81.9	Р			
NCT23027001- IMR18650T18-C13#	55.6	4.14	79.6	84.0	Р			
NCT23027001- IMR18650T18-C14#	55.6	4.13	81.1	77.6	Р			
NCT23027001- IMR18650T18-C15#	55.6	4.13	82.5	81.1	Р			
Model: INR18650L22	2							
Saı	mples charge	ed at charging te	emperature uppe	er limit (45°C)				
NCT23027001- INR18650L22-C6#	55.2	4.19	78.7	74.9	Р			
NCT23027001- INR18650L22-C7#	55.2	4.20	85.3	81.4	Р			
NCT23027001- INR18650L22-C8#	55.2	4.19	82.6	75.4	Р			
NCT23027001- INR18650L22-C9#	55.2	4.20	76.2	72.7	Р			
NCT23027001- INR18650L22-C10#	55.2	4.19	84.8	78.3	Р			
Sa	mples charg	ed at charging t	emperature low	er limit (0°C)				
NCT23027001- INR18650L22-C11#	55.4	4.13	79.2	79.5	Р			
NCT23027001- INR18650L22-C12#	55.4	4.14	88.7	84.2	Р			
NCT23027001- INR18650L22-C13#	55.4	4.13	80.3	80.4	Р			

IEC 62133-2							
Clause Requirem	nent + Test	120 02	Result - Remark				
NCT23027001-	<u> </u>		<u> </u>	Ι			
INR18650L22-C14#	55.4	4.14	84.4	81.6	Р		
NCT23027001- INR18650L22-C15#	55.4	4.14	89.7	83.5	Р		
Model: INR18650L20	6						
Sa	mples charge	ed at charging te	emperature uppe	er limit (45°C)			
NCT23027001- INR18650L26-C6#	54.9	4.20	83.2	72.9	Р		
NCT23027001- INR18650L26-C7#	54.9	4.20	88.0	70.8	Р		
NCT23027001- INR18650L26-C8#	54.9	4.21	81.1	73.8	Р		
NCT23027001- INR18650L26-C9#	54.9	4.20	86.4	72.6	Р		
NCT23027001- INR18650L26-C10#	54.9	4.21	84.5	70.4	Р		
Sa	amples charg	ed at charging t	emperature low	er limit (0°C)			
NCT23027001- INR18650L26-C11#	55.3	4.14	82.6	80.2	Р		
NCT23027001- INR18650L26-C12#	55.3	4.14	83.9	79.5	Р		
NCT23027001- INR18650L26-C13#	55.3	4.13	86.8	80.3	Р		
NCT23027001- INR18650L26-C14#	55.3	4.13	80.7	82.0	Р		
NCT23027001- INR18650L26-C15#	55.3	4.14	82.2	81.2	Р		
Model: INR18650L32	2						
Sa	mples charge	ed at charging te	emperature uppe	er limit (45°C)			
NCT23027001- INR18650L32-C6#	55.5	4.20	83.4	71.6	Р		
NCT23027001- INR18650L32-C7#	55.5	4.21	79.1	76.7	Р		
NCT23027001- INR18650L32-C8#	55.5	4.20	86.5	70.9	Р		
NCT23027001- INR18650L32-C9#	55.5	4.21	75.8	74.6	Р		
NCT23027001- INR18650L32-C10#	55.5	4.20	80.4	75.5	Р		
Sa	amples charg	ed at charging t	emperature low	er limit (0°C)			
NCT23027001-	55.6	4.13	85.9	75.8	Р		

			1 age 20 0	1 33		Report No.	. CINZOQINCIN O
			IEC 62	133-2			
Clause	Requirem	ent + Test			Result	: - Remark	Verdict
INR18650I	L32-C11#						
NCT230 INR18650		55.6	4.14	77.	3	77.4	Р
NCT230 INR18650		55.6	4.13	82.	5	84.9	Р
NCT230 INR18650I		55.6	4.14	87.	2	79.5	Р
NCT230 INR18650I		55.6	4.14	76.	6	80.3	Р
Suppleme - No fire or	•						

TABLE: External short circuit (battery)							
Ambient T	OCV before test (Vdc)	Resistance of circuit (mΩ)	Maximum case temperature rise △T ( <del>K)</del> °C	Component single fault condition	Results		
	4 <del>-</del>		(°C) test (Vdc) of circuit	(°C) test (Vdc) of circuit case temperature rise $\Delta T$	(°C) test (Vdc) of circuit case temperature condition		

7.3.5	7.3.5 TABLE: Crush (cells)						
Sample No.		OCV before test (Vdc)	OCV at removal of crushing force (Vdc)	Maximum force applied to the cell during crush (kN)	Re	sults	
Model: IM	R18650T1	2					
	Sa	mples charged at ch	arging temperature	upper limit (45°C)			
NCT2302 IMR18650T		4.21	4.20	12.99		Р	
NCT2302 IMR18650T		4.21	4.21	13.01		Р	
NCT23027001- IMR18650T12-C31#		4.20	4.19	12.96		Р	
NCT23027001- IMR18650T12-C32#		4.20	4.20	13.03		Р	

	Fage 27 of 39 Report No.: CN23QNCN of							
01	T <sub>D</sub> .		IEC 62133-2					
Clause	Requirem	nent + Test	F	Result - Remark	Verdict			
	027001- 0T12-C33#	4.21	4.21	13.01	Р			
	S	amples charged at c	harging temperature	lower limit (0°C)				
	027001- 0T12-C34#	4.14	4.14	13.02	Р			
	027001- 0T12-C35#	4.13	4.13	13.00	Р			
	027001- 0T12-C36#	4.13	4.12	12.98	Р			
	027001- 0T12-C37#	4.14	4.13	13.01	Р			
	027001- 0T12-C38#	4.13	4.13	13.03	Р			
Model: II	MR18650T1	6						
	Sa	mples charged at ch	narging temperature	upper limit (45°C)				
	027001- 0T16-C29#	4.21	4.20	13.02	Р			
	027001- 0T16-C30#	4.20	4.20	13.01	Р			
	027001- 0T16-C31#	4.21	4.21	12.97	Р			
	027001- 0T16-C32#	4.21	4.20	13.01	Р			
	027001- 0T16-C33#	4.20	4.19	13.03	Р			
	S	amples charged at c	harging temperature	lower limit (0°C)				
	027001- 0T16-C34#	4.13	4.12	13.02	Р			
	027001- 0T16-C35#	4.13	4.13	13.01	Р			
	027001- 0T16-C36#	4.14	4.13	13.03	Р			
	027001- 0T16-C37#	4.13	4.12	13.02	Р			
	027001- 0T16-C38#	4.14	4.14	13.03	Р			
Model: II	MR18650T1	8						
	Sa	mples charged at ch	narging temperature	upper limit (45°C)				
	027001- 0T18-C29#	4.20	4.19	13.03	Р			
NCT23	027001-	4.21	4.21	12.99	Р			
-			•					

		IEC 63133.3		. 01123Q11011
<u> </u>	· + ·	IEC 62133-2		
	nent + Test		Result - Remark	Verdict
IMR18650T18-C30#				
NCT23027001- IMR18650T18-C31#	4.21	4.20	13.01	Р
NCT23027001- IMR18650T18-C32#	4.20	4.20	13.02	Р
NCT23027001- IMR18650T18-C33#	4.21	4.21	13.01	Р
Sa	amples charged at cl	harging temperature	lower limit (0°C)	
NCT23027001- IMR18650T18-C34#	4.13	4.12	12.98	Р
NCT23027001- IMR18650T18-C35#	4.14	4.14	13.02	Р
NCT23027001- IMR18650T18-C36#	4.14	4.13	12.96	Р
NCT23027001- IMR18650T18-C37#	4.13	4.13	13.01	Р
NCT23027001- IMR18650T18-C38#	4.13	4.13	13.02	Р
Model: INR18650L22	2			
Sa	mples charged at ch	arging temperature	upper limit (45°C)	
NCT23027001- INR18650L22-C29#	4.19	4.19	13.02	Р
NCT23027001- INR18650L22-C30#	4.20	4.20	12.96	Р
NCT23027001- INR18650L22-C31#	4.19	4.19	13.03	Р
NCT23027001- INR18650L22-C32#	4.19	4.18	12.99	Р
NCT23027001- INR18650L22-C33#	4.20	4.20	13.00	Р
Sa	amples charged at c	harging temperature	lower limit (0°C)	
NCT23027001- INR18650L22-C34#	4.14	4.14	12.98	Р
NCT23027001- INR18650L22-C35#	4.13	4.12	13.01	Р
NCT23027001- INR18650L22-C36#	4.14	4.14	12.97	Р
NCT23027001- INR18650L22-C37#	4.13	4.13	13.03	Р
NCT23027001- INR18650L22-C38#	4.14	4.14	12.95	Р
Model: INR18650L26	6			

Page 29 of 39 Report No.: CN23QNCN 001

			•	
		IEC 62133-2		
Clause	Requirement + Test		Result - Remark	Verdict

Sa	mples charged at ch	narging temperature	upper limit (45°C)		
NCT23027001- INR18650L26-C29#	4.20	4.19	13.03	Р	
NCT23027001- INR18650L26-C30#	4.21	4.20	13.01	Р	
NCT23027001- INR18650L26-C31#	4.21	4.21	13.03	Р	
NCT23027001- INR18650L26-C32#	4.20	4.19	13.02	Р	
NCT23027001- INR18650L26-C33#	4.20	4.20	13.01	Р	
S	amples charged at c	harging temperature	lower limit (0°C)		
NCT23027001- INR18650L26-C34#	4.14	4.13	13.01	Р	
NCT23027001- INR18650L26-C35#	4.13	4.13	12.97	Р	
NCT23027001- INR18650L26-C36#	4.13	4.12	13.02	Р	
NCT23027001- INR18650L26-C37#	4.14	4.14	12.98	Р	
NCT23027001- INR18650L26-C38#	4.14	4.13	13.01	Р	
Model: INR18650L3	2				
Sa	mples charged at ch	arging temperature	upper limit (45°C)		
NCT23027001- INR18650L32-C29#	4.20	4.20	13.02	Р	
NCT23027001- INR18650L32-C30#	4.21	4.20	12.96	Р	
NCT23027001- INR18650L32-C31#	4.21	4.21	13.00	Р	
NCT23027001- INR18650L32-C32#	4.20	4.20	12.98	Р	
NCT23027001- INR18650L32-C33#	4.21	4.21	13.03	Р	
S	Samples charged at charging temperature lower limit (0°C)				
NCT23027001- INR18650L32-C34#	4.14	4.14	12.97	Р	
NCT23027001- INR18650L32-C35#	4.13	4.13	13.01	Р	
NCT23027001- INR18650L32-C36#	4.14	4.14	12.99	Р	

		1 0	ige 30 01 33	report No.	. 01123011011 00
			IEC 62133-2		
Clause Requirement + Test Result - Remark				Result - Remark	Verdict
NCT23027001- INR18650L32-C37#		4.13	4.12	13.02	Р
NCT230 INR18650	)27001- L32-C38#	4.14	4.14	12.98	Р

## Note:

A 13KN force applied at the longitudinal axis of cylindrical cells. No voltage abrupt drop occurred. **Supplementary information:** 

- No fire or explosion

7.3.6	TABL	TABLE: Over-charging of battery					
Constant	chargin	g current (A)	:			_	
Supply voltage (Vdc):							
Sample No. OCV before charging Total charging time Maximum outer case (Vdc) (minute) temperature (°C)					sults		
Supplem	entary i	nformation:					

7.3.7	TABL	E: Forced discharge (	cells)		Р
Sample	No.	OCV before application of reverse charge (Vdc)	Measured reverse charge I <sub>t</sub> (A)	Lower limit discharge voltage (Vdc)	Results
Model: IN	1R18650	)T12			
NCT2302 IMR1865 C39a	0T12-	3.02	1.20	2.50	Р
NCT2302 IMR1865 C40a	0T12-	3.00	1.20	2.50	Р
NCT2302 IMR1865 C41a	0T12-	3.01	1.20	2.50	Р
NCT2302 IMR1865 C42	0T12-	3.03	1.20	2.50	Р
NCT2302 IMR1865 C43	0T12-	3.02	1.20	2.50	Р

	Ropolt No.: ONZ	ALTON OC
IEC 62133-2		
Clause Requirement + Test	Result - Remark	Verdict

•				<u> </u>
Model: IMR18650	T16			
NCT23027001- IMR18650T16- C39#	2.91	1.60	2.50	Р
NCT23027001- IMR18650T16- C40#	2.92	1.60	2.50	Р
NCT23027001- IMR18650T16- C41#	2.92	1.60	2.50	Р
NCT23027001- IMR18650T16- C42#	2.91	1.60	2.50	Р
NCT23027001- IMR18650T16- C43#	2.92	1.60	2.50	Р
Model: IMR18650	T18			
NCT23027001- IMR18650T18- C39#	3.04	1.80	2.50	Р
NCT23027001- IMR18650T18- C40#	3.05	1.80	2.50	Р
NCT23027001- IMR18650T18- C41#	3.06	1.80	2.50	Р
NCT23027001- IMR18650T18- C42#	3.04	1.80	2.50	Р
NCT23027001- IMR18650T18- C43#	3.08	1.80	2.50	P
Model: INR18650	L22			
NCT23027001- INR18650L22- C39#	3.03	2.20	2.50	Р
NCT23027001- INR18650L22- C40#	3.05	2.20	2.50	P
NCT23027001- INR18650L22- C41#	3.04	2.20	2.50	Р
NCT23027001- INR18650L22- C42#	3.03	2.20	2.50	Р

ge 32 01 39	Пероп	. NO.: CN23	QINCIN U
 IEC 62133-2			
	Result - Remark		Verdict
2.20	2.50	Р	
2.60	2.50	Р	
3.20	2.50	Р	

7.3.8.1 TABLE: Vibration							N/A
Sample N	Ю.	OCV before test (Vdc)	OCV after test (Vdc)	Mass before test (g)	Mass after test (g)	Re	sults

		1 age 00 t	31 00	Roportin	10:: 01120Q11011 00
		IEC 62	2133-2		
Clause	Requirement + Test			Result - Remark	Verdict
	•				
Suppleme	entary information:				
ĺ					

7.3.8.2	TABLE: Mechanical shock						
Sample N	О.	OCV before test (Vdc)	OCV after test (Vdc)	Mass before test (g)	Mass after test (g)	Results	
Supplemen	tary	information:					

7.3.9 TAB	LE: Forced intern	al short circuit (	(cells)			Р					
Sample No.	Chamber ambient T (°C)	OCV before test (Vdc)	Particle location <sup>1)</sup>	Maximum applied pressure (N)	Re	sults					
Model: IMR18650T12											
	Samples charge	ed at charging to	emperature uppe	er limit (45°C)							
NCT23027001- IMR18650T12- C44#	45	4.20	1	800		Р					
NCT23027001- IMR18650T12- C45#	45	4.21	1	800		Р					
NCT23027001- IMR18650T12- C46#	45	4.20	1	800		Р					
NCT23027001- IMR18650T12- C47#	45	4.21	1	800		Р					
NCT23027001- IMR18650T12- C48#	45	4.21	1	800		Р					
	Samples charg	ed at charging t	emperature low	er limit (0°C)							
NCT23027001- IMR18650T12- C49#	0	4.14	1	800		Р					
NCT23027001- IMR18650T12- C50#	0	4.13	1	800		Р					

			IEC 621			. 01423Q14014 00
Clause	Requ	uirement + Test		Res	ult - Remark	Verdict
NCT23027 IMR18650 C51#	T12-	0	4.13	1	800	Р
NCT23027 IMR18650 C52#	T12-	0	4.14	1	800	Р
NCT23027 IMR18650 C53#	T12-	0	4.13	1	800	Р
Model: IN	1R1865	50T16				
		Samples charge	ed at charging to	emperature up	per limit (45°C)	
NCT23027 IMR18650 C44#	)T16-	45	4.20	1	800	Р
NCT23027 IMR18650 C45#	)T16-	45	4.21	1	800	Р
NCT23027 IMR18650 C46#	)T16-	45	4.21	1	800	Р
NCT23027 IMR18650 C47#	T16-	45	4.21	1	800	Р
NCT23027 IMR18650 C48#	)T16-	45	4.20	1	800	Р
		Samples charg	ed at charging t	emperature lo	wer limit (0°C)	
NCT23027 IMR18650 C49#	T16-	0	4.14	1	800	Р
NCT23027 IMR18650 C50#	)T16-	0	4.13	1	800	Р
NCT23027 IMR18650 C51#	)T16-	0	4.14	1	800	Р
NCT23027 IMR18650 C52#	)T16-	0	4.13	1	800	Р
NCT23027 IMR18650 C53#	)T16-	0	4.13	1	800	Р
Model: IN	1R1865	50T18				
		Samples charge	ed at charging to	emperature up	per limit (45°C)	

		IEC 621	133-2	<u> </u>	
Clause Red	quirement + Test			sult - Remark	Verdict
NCT23027001- IMR18650T18- C44#		4.20	1	800	Р
NCT23027001- IMR18650T18- C45#		4.20	1	800	Р
NCT23027001- IMR18650T18- C46#		4.21	1	800	Р
NCT23027001- IMR18650T18- C47#		4.21	1	800	Р
NCT23027001- IMR18650T18- C48#		4.20	1	800	Р
	Samples charg	ed at charging t	emperature lo	ower limit (0°C)	
NCT23027001- IMR18650T18- C49#		4.13	1	800	Р
NCT23027001- IMR18650T18- C50#		4.13	1	800	Р
NCT23027001- IMR18650T18- C51#		4.14	1	800	Р
NCT23027001- IMR18650T18- C52#		4.13	1	800	Р
NCT23027001- IMR18650T18- C53#		4.14	1	800	Р
Model: INR186	650L22				
	Samples charge	ed at charging to	emperature u	pper limit (45°C)	
NCT23027001- INR18650L22- C44#		4.20	1	800	Р
NCT23027001- INR18650L22- C45#		4.19	1	800	Р
NCT23027001- INR18650L22- C46#		4.20	1	800	Р
NCT23027001- INR18650L22- C47#		4.19	1	800	Р

			IEC 621		Nopon No.	. CNZSQNCN UC
Clause	Requ	uirement + Test	.20 02		: - Remark	Verdict
NCT23027 INR18650 C48#	7001- )L22-	45	4.20	1	800	Р
		Samples charg	ed at charging t	emperature low	er limit (0°C)	
NCT23027 INR18650 C49#	)L22-	0	4.13	1	800	Р
NCT23027 INR18650 C50#	)L22-	0	4.14	1	800	Р
NCT23027 INR18650 C51#	)L22-	0	4.13	1	800	Р
NCT23027 INR18650 C52#	)L22-	0	4.14	1	800	Р
NCT23027 INR18650 C53#	)L22-	0	4.14	1	800	Р
Model: IN	IR1865	0L26				
		Samples charge	ed at charging to	emperature uppe	er limit (45°C)	
NCT23027 INR18650 C44#	)L26-	45	4.20	1	800	Р
NCT23027 INR18650 C45#	)L26-	45	4.20	1	800	Р
NCT23027 INR18650 C46#	)L26-	45	4.21	1	800	Р
NCT23027 INR18650 C47#	)L26-	45	4.20	1	800	Р
NCT23027 INR18650 C48#	)L26-	45	4.21	1	800	Р
		Samples charg	ed at charging t	emperature low	er limit (0°C)	
NCT23027 INR18650 C49#	)L26-	0	4.13	1	800	Р
NCT23027 INR18650 C50#	)L26-	0	4.13	1	800	Р
NCT23027 INR18650		0	4.14	1	800	Р

		Page 37 of	f 39	Report No.	: CN23QNCN 00	
		IEC 62	133-2			
Clause Red	quirement + Test		Resul	esult - Remark Verd		
C51#						
NCT23027001- INR18650L26- C52#		4.14	1	800	Р	
NCT23027001- INR18650L26- C53#		4.13	1	800	Р	
Model: INR180	650L32					
	Samples charge	ed at charging to	emperature uppo	er limit (45°C)		
NCT23027001- INR18650L32- C44#		4.20	1	800	Р	
NCT23027001- INR18650L32- C45#		4.21	1	800	Р	
NCT23027001- INR18650L32- C46#		4.21	1	800	Р	
NCT23027001- INR18650L32- C47#		4.20	1	800	Р	
NCT23027001- INR18650L32- C48#		4.20	1	800	Р	
	Samples charg	ed at charging t	emperature low	er limit (0°C)		
NCT23027001- INR18650L32- C49#		4.13	1	800	Р	
NCT23027001- INR18650L32- C50#		4.14	1	800	Р	
NCT23027001- INR18650L32- C51#		4.13	1	800	Р	
NCT23027001- INR18650L32- C52#		4.14	1	800	Р	
NCT23027001- INR18650L32- C53#		4.13	1	800	Р	

#### Supplementary information:

<sup>1)</sup> Identify one of the following:

<sup>1:</sup> Nickel particle inserted between positive and negative (active material) coated area.

<sup>2:</sup> Nickel particle inserted between positive aluminium foil and negative active material coated area.

<sup>-</sup> No fire

Page 38 of 39 Report No.: CN23QNCN 001

			·	
		IEC 62133-2		
Clause	Requirement + Test		Result - Remark	Verdict

D.2	TABLE: Internal AC resistance for coin cells					
Sample no.		Ambient T (°C)	Store time (h)	Resistance Rac ( $\Omega$ )	Re	sults 1)
Suppleme	ntary info	rmation:				

			- <b>I</b>	
		IEC 62133-2		
Clause	Requirement + Test		Result - Remark	Verdict

ABLE: Critical com	ponents informat	tion			Р
Manufacturer/ trademark	Type / model	Technical data	Standard		k(s) of formity <sup>1)</sup>
Anhui TKT New Energy Co., Ltd.	230µm	LiNixCo <sub>y</sub> Mn <sub>1-x-y</sub> O <sub>2</sub> , LiMnO <sub>2</sub> , Ni: Co: Mn=8: 1: 1, CNT, SP, NMP, Aluminum foil			
Anhui TKT New Energy Co., Ltd.	200μm	CMC, SBR, NMP, H <sub>2</sub> O, SP, Graphite, Copper foil			
Shenzhen Wandef u New Energy Technology Co., Ltd.	One-sided ceramic	PE+Ceramic, Width: 61mm, Thickness: 11.5±1.5µm, Shutdown temperature: 130°C			
Xiamen Shouneng Technology Co., Ltd	TKT01	Ethylene carbonate, Diethyl carbonate, Lithium hexafluorophosphate			
Huizhou JuDing Electronics Co Ltd	JD-D1	Ih: 3.5A, It: 7A, Vmax 15Vdc, Imax: 40A, Tmoa: 70°C	UL 1434	UL E	E482764
	Manufacturer/ trademark  Anhui TKT New Energy Co., Ltd.  Anhui TKT New Energy Co., Ltd.  Shenzhen Wandef u New Energy Technology Co., Ltd.  Xiamen Shouneng Technology Co., Ltd  Huizhou JuDing	Manufacturer/ trademark  Anhui TKT New Energy Co., Ltd.  Anhui TKT New Energy Co., Ltd.  Shenzhen Wandef u New Energy Technology Co., Ltd.  Xiamen Shouneng Technology Co., Ltd  Huizhou JuDing JD-D1	trademarkLiNixCoyMn1-x-yO2, LiMnO2, Ni: Co: Mn=8: 1: 1, CNT, SP, NMP, Aluminum foilAnhui TKT New Energy Co., Ltd.200μmCMC, SBR, NMP, H₂O, SP, Graphite, Copper foilShenzhen Wandef u New Energy Technology Co., Ltd.One-sided ceramicPE+Ceramic, Width: 61mm, Thickness: 11.5±1.5μm, Shutdown temperature: 130°CXiamen Shouneng Technology Co., LtdTKT01Ethylene carbonate, Diethyl carbonate, Lithium hexafluorophosphateHuizhou JuDing Electronics Co LtdJD-D1Ih: 3.5A, It: 7A, Vmax 15Vdc, Imax: 40A,	Manufacturer/ trademarkType / modelTechnical dataStandardAnhui TKT New Energy Co., Ltd.230μmLiNixCoyMn1-x-yO2, LiMnO2, Ni: Co: Mn=8: 1: 1, CNT, SP, NMP, Aluminum foilAnhui TKT New Energy Co., Ltd.200μmCMC, SBR, NMP, H₂O, SP, Graphite, Copper foilShenzhen Wandef u New 	Manufacturer/ trademarkType / modelTechnical dataStandardMarconAnhui TKT New Energy Co., Ltd.230μmLiNixCoyMn1-xyO2, LiMnO2, Ni: Co: Mn=8: 1: 1, CNT, SP, NMP, Aluminum foilAnhui TKT New Energy Co., Ltd.200μmCMC, SBR, NMP, H₂O, SP, Graphite, Copper foilShenzhen Wandefu New Energy Technology Co., Ltd.One-sided ceramicPE+Ceramic, Width: 61mm, Thickness: 11.5±1.5μm, Shutdown temperature: 130°CXiamen Shouneng Technology Co., LtdTKT01Ethylene carbonate, Diethyl carbonate, Lithium hexafluorophosphateHuizhou JuDing Electronics Co LtdJD-D1Ih: 3.5A, It: 7A, Vmax 15Vdc, Imax: 40A,UL 1434UL 1

License available upon request.

<sup>1)</sup> Provided evidence ensures the agreed level of compliance. See OD-CB2039.

<sup>--</sup> End of Report --



#### Page 1 of 4

Report No.: CN23QNCN 001

	IEC62133_2B ATTACHMENT							
Clause	Requirement + Test		Result - Remark	Verdict				

# ATTACHMENT TO TEST REPORT IEC 62133-2

#### (Republic of Korea) NATIONAL DIFFERENCES

(Secondary cells and batteries containing alkaline or other non-acid electrolytes - Safety requirements for portable sealed secondary lithium cells, and for batteries made from them, for use in portable applications - Part 2: Lithium systems)

Differences according to.....: National standard KC62133-2(2020-07)

TRF template used:....: IECEE OD-2020-F3, Ed. 1.1

Attachment Form No. ..... KR\_ND\_IEC62133\_2B

Attachment Originator....: KTR

Master Attachment.....: Dated 2022-05-27

Copyright © 2020 IEC System for Conformity Testing and Certification of Electrical Equipment (IECEE), Geneva, Switzerland. All rights reserved.

7.3.6  Over-charging of battery  [Add the bolded text]  b) Test  The test shall be carried out in an ambient temperature of 20 °C ± 5 °C. Each test battery shall be discharged at a constant current of 0,2 lt A, to a final discharge voltage specified by the manufacturer. Sample batteries shall then be charged at a constant current of 2,0 lt A, using a supply voltage which is:  • 1,4 times the upper limit charging voltage	N/A
b) Test  The test shall be carried out in an ambient temperature of 20 °C ± 5 °C. Each test battery shall be discharged at a constant current of 0,2 lt A, to a final discharge voltage specified by the manufacturer. Sample batteries shall then be charged at a constant current of 2,0 lt A, using a supply voltage which is:  • 1,4 times the upper limit charging voltage	
presented in Table A.1 (but not to exceed 6,0 V) for single cell/cell block batteries or  1,2 times the upper limit charging voltage presented in Table A.1 per cell for series connected multi-cell batteries, and  sufficient to maintain a current of 2,0 lt A throughout the duration of the test or until the supply voltage is reached.  In case the charging voltage specified by the manufacturer is higher than the overcharge test voltage, the maximum charging voltage	I only. N/A



## Page 2 of 4

Report No.:CN23QNCN 001

IEC62133_2B ATTACHMENT				
Clause	Requirement + Test	Result - Remark	Verdict	
	[Replace to the following statement]  c) Acceptance criteria  Filling beyond the manufacturer's specified limits should not result in ignition or explosion		N/A	
Annex G	Definition for shape and materials of outer case for cell			
(Addition)	G.1 General Annex G provides definitions for shape and materials of outer case for cell G.2 Shape of outer case for cell G.2.1 Cylindrical cell Cell with a cylindrical shape in which the overall height is equal to or greater than diameter. G.2.2 Prismatic cell Cell having the shape of a parallelepiped whose faces are rectangular G.3 Materials of outer case for cell G.3.1 Soft case Non-metallic outer case or container for cell G.3.2 Hard case Metallic outer case or container for cell.	(Shape of outer cases)  ☑ Cylindrical ☐ Prismatic  (Materials of outer cases) ☑ Hard ☐ Soft	_	
Annex H	Calculation method of the volumetric energy density for cell		_	



## Page 3 of 4

Report No.: CN23QNCN 001

IEC62133_2B ATTACHMENT					
Clause	Requirement + Test	Result - Remark	Verdict		
(Addition)	Annex H provide a calculation method of the volumetric energy density for cell in use of smart phone, tablet, notebook.  H.1 General Unless otherwise stated in the Annex E, the dimensions for calculation are based on these for cell before shipment and the volumetric energy density shall be calculated with a maximum values specified by manufacturer. If the specification for cell can't be provided a dimension for calculation, the manufacturer's other documentation shall be provided to demonstrate compliance for its calculation.	IMR18650T12: 250.2Wh / L IMR18650T16: 333.7Wh / L IMR18650T18: 375.4Wh / L IMR18650L18: 375.4Wh / L IMR18650T20: 417.1Wh / L INR18650T20: 417.1Wh / L INR18650T22: 458.8Wh / L INR18650L22: 458.8Wh / L INR18650L25: 521.3Wh / L INR18650L25: 521.3Wh / L INR18650L26: 542.2Wh / L INR18650L26: 542.2Wh / L INR18650L30: 625.6Wh / L INR18650L32: 667.3Wh / L			



## Page 4 of 4

Report No.: CN23QNCN 001

IEC62133_2B ATTACHMENT			
Clause	Requirement + Test	Result - Remark	Verdict
	H.2 Calculation Method  L: Length (max.) of cell (including terrace) W: Width (max.) of cell T: Thickness (max.) when shipping charge (For reference, Please Exclude the dimension of any tape that Is attached to cell)		
	$Volumetric\ energy\ density\ (Wh/L) = \frac{Nominal\ voltage\ (V) \times Rated\ capacity\ (Ah)}{Length\ (L) \times Width\ (W) \times Thickness\ (T)}$		
	[H.1 — Prismatic cell using soft case]  L: Length (max.) of cell  W: Width (max.) of cell  T: Thickness when shipping charge (For reference, Please Exclude the dimension of any tape that Is attached to cell)  Volumetric energy density $(Wh/L) = \frac{Nominal\ voltage\ (V) \times Rated\ capacity\ (Ah)}{Length\ (L) \times Width\ (W) \times Thickness\ (T)}$		_
	[H.2 – Prismatic cell using hard case]		
	D: Diameter (max.) of cell L: Length (max.) of cell L (According to shape of cell at shipping, The dimension of tube for cell may be included In overall dimension of cell)		
	$Volumetric\ energy\ density\ (Wh/L) = \frac{Nominal\ voltage\ (V) \times Rated\ capacity\ (Ah)}{3.14159 \times \frac{Diameter\ (D)^2}{4} \times Length(L)}$		
	[H.3 – Cylindrical cell using hard case]		

#### **Photo Documentation**

Page 1 of 6 Report No.: CN23QNCN 001


Product: Lithium-ion Cell

Type Designation: IMR18650T12, IMR18650T16, IMR18650T18, IMR18650L18, INR18650T20,


INR1865020, INR18650T22, INR18650L22, INR18650T25, INR18650L25,

INR18650T26, INR18650L26, INR18650L30, INR18650L32

Remark: The tested models IMR18650T12, IMR18650T16, IMR18650T18, INR18650L22, INR18650L26, INR18650L32 are representatives of all models.



Picture 1 Top view of cell (Model: IMR18650T12)



Picture 2 Bottom view of cell (Model: IMR18650T12)


## **Photo Documentation**

Page 2 of 6 Report No.: CN23QNCN 001


Product: Lithium-ion Cell

<u>Type Designation:</u> **IMR18650T12**, **IMR18650T16**, **IMR18650T18**, IMR18650L18, INR18650T20,

INR1865020, INR18650T22, INR18650L22, INR18650T25, INR18650L25,



Picture 3 Top view of cell (Model: IMR18650T16)



Picture 4 Bottom view of cell (Model: IMR18650T16)


## **Photo Documentation**

Page 3 of 6 Report No.: CN23QNCN 001


Product: Lithium-ion Cell

<u>Type Designation:</u> **IMR18650T12**, **IMR18650T16**, **IMR18650T18**, IMR18650L18, INR18650T20,

INR1865020, INR18650T22, **INR18650L22**, INR18650T25, INR18650L25,



Picture 5 Top view of cell (Model: IMR18650T18)



Picture 6 Bottom view of cell (Model: IMR18650T18)


## **Photo Documentation**

Page 4 of 6 Report No.: CN23QNCN 001

Product: Lithium-ion Cell

<u>Type Designation:</u> **IMR18650T12**, **IMR18650T16**, **IMR18650T18**, IMR18650L18, INR18650T20,

INR1865020, INR18650T22, INR18650L22, INR18650T25, INR18650L25,



Picture 7 Top view of cell (Model: INR18650L22)



Picture 8 Bottom view of cell (Model: INR18650L22)


## **Photo Documentation**

Page 5 of 6 Report No.: CN23QNCN 001


Product: Lithium-ion Cell

<u>Type Designation:</u> **IMR18650T12**, **IMR18650T16**, **IMR18650T18**, IMR18650L18, INR18650T20,

INR1865020, INR18650T22, **INR18650L22**, INR18650T25, INR18650L25,



Picture 9 Top view of cell (Model: INR18650L26)



Picture 10 Bottom view of cell (Model: INR18650L26)


## **Photo Documentation**

Page 6 of 6 Report No.: CN23QNCN 001


Product: Lithium-ion Cell

<u>Type Designation:</u> **IMR18650T12**, **IMR18650T16**, **IMR18650T18**, IMR18650L18, INR18650T20,

INR1865020, INR18650T22, **INR18650L22**, INR18650T25, INR18650L25,



Picture 11 Top view of cell (Model: INR18650L32)



Picture 12 Bottom view of cell (Model: INR18650L32)