

Test Report

Report No. : AGC05443250522-001

SAMPLE NAME : Handwarmer power bank

MODEL NAME : MO6949

APPLICANT: MID OCEAN BRANDS B.V.

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : May 27, 2025

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Report No.: AGC05443250522-001
Applicant: MID OCEAN BRANDS B.V.

Address : Unit 711-716, 7/F., Tower A, 83 King Lam Street, Cheung Sha Wan, Kowloon, Hong

Kong.

Test Site : 6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng Street,

Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : Handwarmer power bank

Model : MO6949

Vendor code : 114538

Country of Origin : CHINA

Country of Destination : EUROPE

Sample Received Date : May 16, 2025

Testing Period : May 16, 2025 to May 27, 2025

Test Requested : Selected test(s) as requested by client.

Test Requested: Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43

- Aromatic Amines Azodyes (AZO) Content

- Color fastness to rubbing

Approved by: Suhong living

Pass

Pass

Pass

Pass

Suhongliang

Technical Director




Report Revise Record

Report No.: AGC0544325	50522-001
------------------------	-----------

Report Version	Issued Date	Valid Version	Notes
/	May 27, 2025	Valid	Initial release





The photo of the sample





AGC®


Report No.: AGC05443250522-001























AGC®









The photo of AGC05443250522-001 is for use only with the original report.

Test Point Description

Test point	Test module	Test parts	Test point description
Model: Mo	O6949		
1			Black metallic shell
2		Outer shell	Black plastic shell
3			Translucent plastic lamp post
4			Black thin sling
5		Sling	Black plastic buckle
6			Black thick sling
7			Tan tape
8			FPC
9		FPC	Solder
10		TPC	Black wire jacket
11			Red wire jacket
12			Conductor
13			Black screw
14			USB metal device
15	Circuit board	USB device	Grey plastic joint
16	Circuit board		Metal pin
17		Type-C connector	Type-C metal connector



		T	Report No.: AGC05443250522-001	
18			Grey plastic joint	
19			Metal pin	
20			Grey plastic switch	
21		Switch	Metallic shell	
22		Switch	Metallic shrapnel	
23			White plastic base	
24		Correction throateness	Grey magnetic frame	
25		Grey inductance	Enameled wire	
26			Chip capacitor	
27			Chip resistor	
28			Chip IC	
29			PCB	
30			Solder	
31			Chip triode	
32			Chip white LED	
33			Chip yellow LED	
34			IC body	
35		IC	Solder at the pins	
36			Pin	
37			Black thermistor body	
38		Thermistor	Enameled wire	
39			Barley paper	
40			White plastic sheet	
41			Black foam with glue	
42			Purple bushing	
43		Battery	Tan tape	
44			Black wire jacket	
45			Red wire jacket	
46			Conductor	
USB cable	;		L	
47			USB metal plug	
48		USB plug	White plastic plug	
49		1 6	Metal pin	
50			Grey plastic plug	
51		Type-C plug	Metal pin	
52	USB 转 Type-C	71 18	Type-C metal plug	
53	Plug		Milk white inner glue	
54			Black handle	
55			Green PCB	
56			Solder	
57			Chip resistor	
58			Type-C metal plug	
59		Type-C plug	White plastic plug	
60		-7118	Metal pin	
00		1	mom pm	



		<u> </u>
61		Metallic pogopin
62		Black PCB
63		Solder
64		Milk white inner glue
65		Chip capacitor
66		Black outer wire jacket
67		Green wire jacket
68		Black wire jacket
69	 Wire rod	White wire jacket
70		Red wire jacket
71		Yellow wire jacket
72		Conductor

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001% Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019/CNAS-GL015:2022.

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method	-		
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1 μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Page 10 of 39

Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-0
	-	Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
	Cr((Cr^{6+})	BL	/	
1	Br	PBBs	N/A	/	Conformity
		PBDEs	DT/A	/	
-		IBP	N/A	/	
		OBP OR DE	N/A	/	
-		BP	N/A	/	
		ЕНР	N/A	/	
_		Pb	BL	/	
		Cd	BL	/	
_		Hg	BL	/	
_	Cr((Cr ⁶⁺)	BL	/	
2	Br	PBBs	IN	N.D.	Conformity
2		PBDEs		N.D.	Comorning
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
-)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	N.D. /	
-		Cd	BL	/	
-				/	
		Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
4	Br	PBBs	BL	/	Conformity
-	-	PBDEs	37/4	/	
		IBP	N/A	N.D.	
<u> </u>		OBP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
	D.	EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-00
		Pb	BL	/	
	(Cd	BL	/	
		Hg	BL	/	
	Cr((Cr ⁶⁺)	BL	/	
5	Br	PBBs	IN	N.D.	Conformity
3	DI	PBDEs	IIN	N.D.	Comorning
	D	IBP	N/A	N.D.	
	Г	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr^{6+})	BL	/	
6	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
7	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
)BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
8]	Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
	וע	D111	1 V / F 1	IN.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-00
]	Pb	BL	/	
	(Cd	BL	/	
	I	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
9	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
10		PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
11	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
-			BL	/	
		Cr ⁶⁺)	BL	/	
12	Br	PBBs PBDEs	N/A	/	Conformity
 	D.	IBP	N/A	/	
 		BP	N/A	,	
 		BP	N/A	/	
 		EHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	b	BL	/	
	(Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	$\mathbb{C}r^{6+}$)	BL	/	
12	D	PBBs	DT/A	/	G 6 '
13	Br	PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
	D.	BP	N/A	/	
	B	BP	N/A	/	
	DE	НР	N/A	/	
	F	b	BL	/	
	(Cd	BL	/	
	H	[g	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
1.4	D	PBBs	27/4	/	G 6 :
14	Br	PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
15	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	1
		BP	N/A	N.D.	
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	
		b	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		Cr^{6+})	BL	/	
16	Br	PBBs PBDEs	N/A	/	Conformity
<u> </u>	DI	BP	N/A	/	
<u> </u>		BP	N/A	/	
<u> </u>		BP	N/A	/	
 		CHP	N/A	/	

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Web: http://www.agccert.com/



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-0
		Pb	BL	/	
	(Cd	BL	/	
]	Hg	BL	/	
		(Cr^{6+})	IN	N.D.	
1.7	D.,	PBBs	NT/A	/	C f : t
17	Br	PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
	Γ	BP	N/A	/	
	В	BP	N/A	/	
	D.	ЕНР	N/A	/	
		Pb	BL	/	
	(Cd	BL	/	
		Hg	BL	/	
	Cr((Cr ⁶⁺)	BL	/	
18	Br	PBBs	BL	/	Conformity
10		PBDEs		/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
	Cd		BL	/	
	Нд		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
19	Br	PBBs	N/A	/	Conformity
19	PBDEs		IN/A	/	Conformity
	D	IBP	N/A	/	
	Σ	BP	N/A	/	
	В	BP	N/A	/	
	D	ЕНР	N/A	/	
		Pb	BL	/	
	(Cd	BL	/	
	Hg		BL	/	
	Cr((Cr^{6+})	BL	/	
20	Br	PBBs	BL	/	Conformity
20	DI	PBDEs	DL	/	Conformity
	D	IBP	N/A	N.D.	
Γ	Г)BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	D.	ЕНР	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-00
	F	P b	BL	/	
	(Cd	BL	/	
	F	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
21	Br	PBBs PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	
		BP	N/A	/	
		BP	N/A	/	
		EHP	N/A	/	
		Pb	BL	/	
_		Cd Cd	BL	/	
-		Ig	BL	/	
		Cr ⁶⁺)	IN	N.D.	
22	Br	PBBs PBDEs	N/A	/	Conformity
_	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
	Cd		BL	/	
	Hg		BL	/	
	$Cr(Cr^{6+})$		BL	/	
23	Br	PBBs PBDEs	BL	/	Conformity
	Dl	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
	ŀ	łg	BL	/	
ļ		Cr ⁶⁺)	IN	N.D.	
24	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	Di	BP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
-		BP	N/A	N.D.	
<u> </u>		EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
		łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
25		PBBs	DI	/	C f : t
25	Br	PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
]	Pb	BL	/	
	(Cd	BL	/	
	I	łg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
26	ъ	PBBs	DI	/	Conformity
26	Br	PBDEs	BL	/	
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
]	Pb	BL	/	
	(Cd	BL	/	
	I	łg	BL	/	
		Cr ⁶⁺)	BL	/	ı
27	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
			BL	/	
		Cr ⁶⁺)	BL	/	
28	Br	PBBs PBDEs	BL	/	Conformity
	D.	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
-		EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	P b	BL	/	
	(Cd	BL	/	
	F	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
20		PBBs	D.I.	N.D.	G C :
29	Br	PBDEs	IN	N.D.	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	B	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	Pb	BL	/	
	C	Cd	BL	/	
	Н	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
		PBBs	27/1	/	Conformity
30	Br	PBDEs	N/A	/	
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
	Pb		BL	/	
		Cd	BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)	BL	/	1
31	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd Cd	BL	/	
		lg	BL	/	
		Cr ⁶⁺)	BL	/	
32	Br	PBBs PBDEs	BL	/	Conformity
-	DI	BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
-		он СНР	N/A	N.D.	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
		(Cr^{6+})	BL	/	
33	Br	PBBs PBDEs	BL	/	Conformity
		IBP	N/A	N.D.	
)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	
				N.D. /	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr^{6+})	BL	/	
34	34 Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		(Cr ⁶⁺)	BL	/	l
35	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
		EHP	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr^{6+})	BL	/	
	CI	PBBs	DL	/	
36	Br	PBDEs	N/A	/	Conformity
	ח	IBP	N/A	/	
)BP	N/A N/A	/	
		BBP		/	
			N/A	/	
	D.	EHP	N/A	/	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-00
	I	Pb	BL	/	
	(Cd	BL	/	
	F	Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
37	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		Cr ⁶⁺)	BL	/	
38	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		-Ig	BL	/	
		Cr ⁶⁺)	BL	/	
39	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
	Hg		BL	/	
		Cr ⁶⁺)	BL	/	
40	Br	PBBs PBDEs	BL	/	Conformity
-	D	IBP	N/A	N.D.	
-		BP	N/A	N.D.	
-		BP	N/A	N.D.	
<u> </u>		ЕНР	N/A	N.D.	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-0
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
41	Br	PBBs PBDEs	BL	/	Conformity
-	D	DIBP	N/A	N.D.	
-		OBP	N/A	N.D.	
-	Е	BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
ļ		Cd	BL	/	
ļ		Hg	BL	/	
		(Cr^{6+})	BL	/	
42	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
-	BBP		N/A	N.D.	
-	DEHP		N/A	N.D.	
		Pb	BL	/	
-		Cd	BL	/	
		Hg	BL	/	
-	$Cr(Cr^{6+})$		BL	/	
43	Br	PBBs PBDEs	BL	/	Conformity
-	D	DIBP	N/A	N.D.	
		OBP	N/A	N.D.	
		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
ļ		Cd	BL	/	
	Hg		BL	/	
ļ		(Cr^{6+})	BL	/	
44	Br	PBBs PBDEs	BL	/	Conformity
	n	OIBP	N/A	N.D.	
)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	
	D.	r-11	1 1/ /1	14.1.	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-0 Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
-		(Cr^{6+})	BL	/	
45	Br	PBBs PBDEs	BL	/	Conformity
-		OIBP	N/A	N.D.	
-)BP	N/A	131	
-		BBP	N/A	N.D.	
-		ььг ЕНР	N/A	N.D.	
				N.D. /	
_		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
-	Cr	(Cr^{6+})	BL	/	
46	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
-	$Cr(Cr^{6+})$		BL	/	
47	Br	PBBs PBDEs	N/A	/	Conformity
-	Г	OIBP	N/A	/	
-)BP	N/A	/	
-		BBP	N/A	/	
-		EHP	N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
-		(Cr ⁶⁺)	BL	/	
-	Cr	PBBs	DL	/	
48	Br	PBDEs	BL	/	Conformity
-	T-	OIBP	N/A	N.D.	
-					
-		OBP OBD	N/A	N.D.	
-		BBP	N/A	N.D.	
	D	EHP	N/A	N.D.	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-00
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
49	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
)BP	N/A	/	
	E	BBP	N/A	/	
	D	ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
50	Br	PBBs PBDEs	BL	/	Conformity
_	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	1
51	Br	PBBs PBDEs	N/A	/	Conformity
	D	OIBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	IN	N.D.	
52	Br PBBs PBDEs		N/A	/	Conformity
	D	IBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
_		EHP	N/A	/	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Cos443250522-0
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
53	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
54	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
		PBBs	D.	N.D.	
55	Br PBDEs		IN	N.D.	Conformity
	D	IBP	N/A	N.D.	
	Ι)BP	N/A	N.D.	
		BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
ļ		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
56	Br	PBBs PBDEs	N/A	/	Conformity
ŀ	n	IBP	N/A	/	
ŀ)BP	N/A	,	
ŀ		BBP	N/A	/	
ŀ		EHP	N/A	/	
	D	P111	1 N/ FA	1	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	b	BL	/	
	(Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	$\mathbb{C}r^{6+}$)	BL	/	
57	D	PBBs	DI	/	G 6 :
57	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D.	BP	N/A	N.D.	
	B	BP	N/A	N.D.	
	DE	НР	N/A	N.D.	
	F	b	BL	/	
		Cd	BL	/	
	H	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	IN	N.D.	
50		PBBs	27/4	/	Conformity
58	Br	PBDEs	N/A	/	
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DE	CHP	N/A	/	
	Pb		BL	/	
	(Cd	BL	/	
	Hg		BL	/	1
		Cr ⁶⁺)	BL	/	
59	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP EHP	N/A	N.D.	
		b	BL	/	
		Cd	BL	/	
		lg	BL	/	
		Cr^{6+})	BL	/	
		PBBs		/	
60	Br	PBDEs	N/A	/	Conformity
	DI	BP	N/A	/	1
		BP	N/A	/	
		BP	N/A	/	
-		CHP	N/A	/	



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443250522-0 Conclusion
		Pb	BL	/	
	(Cd	BL	/	
]	Hg	BL	/	
	Cr((Cr^{6+})	IN	N.D.	
61	Br	PBBs	N/A	/	Conformity
01	DI	PBDEs	IV/A	/	Comornity
	D	IBP	N/A	/	
	Σ	BP	N/A	/	
	Е	BBP	N/A	/	
	D.	ЕНР	N/A	/	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr^{6+})	BL	/	
62	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
	Cr((Cr ⁶⁺)	BL	/	
63	Br	PBBs PBDEs	N/A	/	Conformity
	D	IBP	N/A	/	
)BP	N/A	/	
_		BBP	N/A	/	
		ЕНР	N/A	/	
		Pb	BL	/	
-		Cd	BL	/	
-		Hg	BL	/	
		(Cr^{6+})	BL	/	
64	Br	PBBs PBDEs	BL	/	Conformity
-	D	IBP	N/A	N.D.	
-)BP	N/A	N.D.	
-		BBP	N/A	N.D.	
		EHP	N/A	N.D.	-



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr((Cr ⁶⁺)	BL	/	
65	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
)BP	N/A	N.D.	
_		BP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
		(Cr^{6+})	BL	/	
66	Br	PBBs PBDEs	BL	/	Conformity
_	DIBP		N/A	N.D.	
-	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
]	Hg	BL	/	
	$Cr(Cr^{6+})$		BL	/	
67	Br	PBBs PBDEs	BL	/	Conformity
<u> </u>	D	IBP	N/A	N.D.	1
<u> </u>)BP	N/A	N.D.	
<u> </u>		BP	N/A	N.D.	
<u> </u>		EHP	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
-		Hg	BL	/	
		(Cr ⁶⁺)	BL	/	
68	Br	PBBs PBDEs	BL	/	Conformity
-	D	IBP	N/A	N.D.	
-)BP	N/A	N.D.	
		BBP	N/A	N.D.	
		EHP	N/A	N.D.	-



Test point	Tes	t Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
69	Br	PBBs	BL	/	Conformity
09	DI	PBDEs	DL	/	Conformity
	D	IBP	N/A	N.D.	
	Ι)BP	N/A	N.D.	
	F	BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr^{6+})	BL	/	
70	D	PBBs	DI	/	G C :
70	Br	PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	Pb		BL	/	
		Cd	BL	/	
	Hg		BL	/	
	Cr	(Cr ⁶⁺)	BL	/	
71	Br	PBBs PBDEs	BL	/	Conformity
-	D	OIBP	N/A	N.D.	
-		DBP	N/A	N.D.	
-		BBP	N/A	N.D.	
		ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
72		$\frac{-c}{(\operatorname{Cr}^{6+})}$	BL	/	
		PBBs		/	~ ~ .
	Br	PBDEs	N/A	/	Conformity
	D	OIBP	N/A	/	
)BP	N/A	/	
		BBP	N/A	/	
		EHP	N/A	,	

Remark: The samples of the following test points were resubmitted on May 26, 2025:30,35



Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>N/A</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	N/A	BL≤250-3σ <x< td=""></x<>

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number	Colorimetric result (Cr(VI) concentration)	Judgement
1	$X < 0.1 \mu g/cm^2$	Negative
2	0.1μg/cm ² ≤X≤0.13μg/cm ²	Uncertainty
3	$X > 0.13 \mu g/cm^2$	Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.



Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s) 2+3+5
Benzo[a]pyrene(BaP)	mg/kg	1	0.1	N.D.
Benzo[e]pyrene(BeP)	mg/kg	1	0.1	N.D.
Benzo[a]anthracene(BaA)	mg/kg	1	0.1	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	1	0.1	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	1	0.1	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	1	0.1	N.D.
Chrysene(CHR)	mg/kg	1	0.1	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	1	0.1	N.D.
Co	Conformity			

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 2+3+5

Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5
Chrysene(CHR)	218-01-9	/	≤ 1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the "Dedicated Testing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc01@agccert.com.

Report No.: AGC05443250522-001

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 43

- Aromatic Amines Azodyes (AZO) Content

Test Methods and Equipment: EN ISO 14362-1:2017; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s) 4+6
4-Aminobiphenyl CAS:92-67-1	mg/kg	30	5	N.D.
Benzidine CAS:92-87-5	mg/kg	30	5	N.D.
4-Chloro-o-toluidine CAS:95-69-2	mg/kg	30	5	N.D.
2-Naphthylamine CAS:91-59-8	mg/kg	30	5	N.D.
o-Aminoazotoluene CAS:97-56-3	mg/kg	30	5	N.D.
5-Nitro-o-toluidine CAS:99-55-8	mg/kg	30	5	N.D.
p-Chloroaniline CAS:106-47-8	mg/kg	30	5	N.D.
4-Methoxy-m-phenylenediamine CAS:615-05-4	mg/kg	30	5	N.D.
4,4'-Diaminodiphenylmethane CAS:101-77-9	mg/kg	30	5	N.D.
3,3'-Dichlorobenzidine CAS:91-94-1	mg/kg	30	5	N.D.
3,3'-Dimethoxybenzidine CAS:119-90-4	mg/kg	30	5	N.D.
3,3'-Dimethybenzidine CAS:119-93-7	mg/kg	30	5	N.D.
4,4'-Methylenedi-o-toluidine CAS:838-88-0	mg/kg	30	5	N.D.
p-Cresidine CAS:120-71-8	mg/kg	30	5	N.D.
4,4'-Methylenebis[2-chloroaniline] CAS:101-14-4	mg/kg	30	5	N.D.
4,4'-Oxydianiline CAS:101-80-4	mg/kg	30	5	N.D.
4,4'-Thiodianiline CAS:139-65-1	mg/kg	30	5	N.D.
2-Aminotoluene CAS:95-53-4	mg/kg	30	5	N.D.
2,4-Toluylendiamine CAS:95-80-7	mg/kg	30	5	N.D.
2,4,5-Trimethylaniline CAS:137-17-7	mg/kg	30	5	N.D.
o-Anisidine CAS:90-04-0	mg/kg	30	5	N.D.
4-Aminoazobenzene CAS:60-09-3	mg/kg	30	5	N.D.
CAS.00-07-3	Conformity			

Report No.: AGC05443250522-001



1. As specified by client, the submitted samples were mixed to test, the test points: 4+6

Note: 4-aminoazobenzene: The EN ISO 14362-1:2017 or ISO 17234-1:2020 methods will enable further cleavage of 4-aminoazobenzene to aniline and / or 1,4-phenylenediamine. If aniline and / or 1,4-phenylenediamine are detected, 4-aminoazobenzene shall be further determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

- Color fastness to rubbing

Test Method: ISO 105-X12:2016

Rubbing finger: Cylinder

The time of conditioning as well as the atmospheric conditions during testing: 19.9°C, 63 %R.H., 4 hrs

The long direction of the specimen Endwise/ Crossrange The percentage of soak of wet rubbing cloth: 95%~100%

	Test 1	Conclusion		
Test point	Colour fastness to			
	Dry rubbing	Wet rubbing		
4	4-5	4-5	Conformity	
6	4-5	4-5	Conformity	
Limit (Client's Requirement)	≥2-3	≥2-3	/	

Note:


Colour Fastness Grade:


Grade 5 = No Colour Change (Best Grade)

Grade 1 = Colour Change Seriously (Bad Grade)

9 grades in gray sample card: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.


Test Flow Chart of XRF









Test Flow Chart of Phthalates









Test Flow Chart of PBBs and PBDEs









Test Flow Chart of Hexavalent Chromium (Cr6+)









Test Flow Chart of Hexavalent Chromium (Cr6+)








Test Flow Chart of Lead, Cadmium and Mercury





These sample were dissolved totally by pre-conditioning method according to above flow chart






Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)







Test Flow Chart of AZO





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***