



TEST REPORT

Customer information	Client	Mid Ocean Brands B.V.
	Address	7/F., Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong
Sample information	Name of sample	Nurse watch
	Test Model No.	MO8256
	Trade mark	N/A
	Lot number	----
	Manufacturer	114628
Test information	Sample received	December 04, 2024
	Testing date	December 04, 2024 to December 11, 2024
	Test sort	Commission Test
	Requested/item	RoHS directive 2011/65/EU Annex II amending Annex(EU)2015/863. (1) Lead, Cadmium, Mercury, Hexavalent Chromium, PBBs and PBDEs Content. (2) Di-(2-ethylhexyl) phthalate(DEHP), Benzylbutyl phthalate(BBP), Dibutyl phthalate(DBP), Disobutyl phthalate(DIBP) Content.
	Standard/Foundation	(1)With reference to IEC 62321-3-1:2013, scanning by XRF Spectroscopy Chemical test method: With reference to IEC 62321-5:2013, determination of Cadmium, lead by ICP With reference to IEC 62321-4:2013+AMD1:2017, determination of Mercury by ICP With reference to IEC 62321-7-2:2017&IEC 62321-7-1:2015, determination of Hexavalent Chromium by Colorimetric method. With reference to IEC 62321-6:2015 determination of PBBs and PBDEs by GC-MS (2)With reference to IEC 62321-8:2017, and analysis was performed by GC-MS.
	Conclusion	(1)The tested sample complied with RoHS directive (2011/65/EU). (2)The tested part of submitted sample complied with directive (EU)2015/863
Remark	----	

Tested By:



Checked By:



Approved By:



Date:

2024/12/11

Date:

2024/12/11

Date:

2024/12/11

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 http://www.sit-cert.com

Test result: 1. Structural parts

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
1	Transparent plastic screen	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
2	White plastic watch shell	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
3	White plastic ring	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
4	White plastic inner frame	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
5	Silver metal stick	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
6	Silver metal shaft	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
7	Black soft plastic ring	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
8	Silver metal button	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
9	Silver metal base shell	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
10	White coating	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
11	Silver metal ring	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
12	Silver metal raised words	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
13	Silver metal needle	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
14	Green coating	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
15	Silver metal raised words	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
16	White coating	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
17	Silver metal shaft	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
18	Black plastic frame	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
19	Silver metal sheet	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
20	Silver metal shaft	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
21	Copper wire	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
22	Transparent plastic	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
23	Copper sheet	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
24	Transparent plastic	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
25	White plastic	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
26	White plastic wheel	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
27	Silver metal button battery shell	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
28	Silver metal shaft	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
29	Silver metal sheet	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
30	Solder	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
31	Black glue point	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P
32	Solder	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
33	Silver metal component	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
34	Circuit board	Cd	P	N.D.	<100	P
		Cr(VI)	P	N.D.	<1000	P
		Hg	P	N.D.	<1000	P
		Pb	P	N.D.	<1000	P
		PBBs	P	N.D.	<1000	P
		PBDEs	P	N.D.	<1000	P

Remark:

- 1 It is the result on total Br while test PBBs and PBDEs by EDXRF. It is the result on total Cr while test Hexavalent Chromium by EDXRF.
- 2 Results are obtained by EDXRF for primary screening, and chemical testing by ICP (for Cd, Pb, Hg),UV-VIS (Cr(VI)) and GCMS (for PBBs, PBDEs) is recommended to be performed.
- 3.

Element	Polymer	Metal	Composite Materials
Cd	$P \leq 70 - 3\sigma < D < 130 + 3\sigma \leq F$	$P \leq 70 - 3\sigma < D < 130 + 3\sigma \leq F$	$P \leq 50 - 3\sigma < D < 150 + 3\sigma \leq F$
Pb	$P \leq 700 - 3\sigma < D < 1300 + 3\sigma \leq F$	$P \leq 700 - 3\sigma < D < 1300 + 3\sigma \leq F$	$P \leq 500 - 3\sigma < D < 1500 + 3\sigma \leq F$
Hg	$P \leq 700 - 3\sigma < D < 1300 + 3\sigma \leq F$	$P \leq 700 - 3\sigma < D < 1300 + 3\sigma \leq F$	$P \leq 500 - 3\sigma < D < 1500 + 3\sigma \leq F$
Br	$P \leq 300 - 3\sigma < D$	----	$P \leq 250 - 3\sigma < D$
Cr	$P \leq 700 - 3\sigma < D$	$P \leq 700 - 3\sigma < D$	$P \leq 500 - 3\sigma < D$

P = PASS; F = FAIL; D = DETECTED;

4. mg/kg = ppm; N.D. = NOT DETECTED (<MDL) Pb, Cd, Hg,Cr(VI): 2mg/kg; PBBs, PBDEs: 5mg/kg
5. With reference to IEC 62321:-7-1:2015, result on Cr (VI) for metal sample is shown as Positive/Negative.
Positive = Presence of Cr(VI) coating, Negative = Absence of Cr(VI) coating
- 6 *According to Annex III of European Council Directive 2011/65/EU, Lead in copper alloy containing up to 4% lead by weight.
- 7 **According to Annex III of European Council Directive 2011/65/EU, Lead in steel alloy containing up to 0.35% lead by weight.
- 8 #According to Annex III of European Council Directive 2011/65/EU, Cadmium and its compounds in electrical contacts is exempted.

(3) DEHP, BBP, DBP, DIBP

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)					MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	1	2	3	4	7		
Di-2-ethylhexyl phthalate (DEHP)	ND	ND	ND	ND	ND	30	1000
Dibutyl phthalate (DBP)	ND	ND	ND	ND	ND	30	1000
Benzylbutyl phthalate (BBP)	ND	ND	ND	ND	ND	30	1000
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND	ND	30	1000

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)					MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	10	14	16	18	22		
Di-2-ethylhexyl phthalate (DEHP)	ND	ND	ND	ND	ND	30	1000
Dibutyl phthalate (DBP)	ND	ND	ND	ND	ND	30	1000
Benzylbutyl phthalate (BBP)	ND	ND	ND	ND	ND	30	1000
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND	ND	30	1000


ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)					MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	24	25	26	31	34		
Di-2-ethylhexyl phthalate (DEHP)	ND	ND	ND	ND	ND	30	1000
Dibutyl phthalate (DBP)	ND	ND	ND	ND	ND	30	1000
Benzylbutyl phthalate (BBP)	ND	ND	ND	ND	ND	30	1000
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND	ND	30	1000

Note: MDL = Method Detection Limit, ND=not detected (<Method Detection Limit).


Appearance photograph of EUT




Appearance photograph of EUT




Appearance photograph of EUT




Appearance photograph of EUT



Appearance photograph of EUT



Appearance photograph of EUT



List of apparatus

No.	Name	Model	Calibration Valid Date	USE(√)
1	ICP-OES	VISTA-MPX	2025/06/28	√
2	GC-MS	5975i	2025/06/16	√
3	UV-Vis	Lambda 25	2025/06/16	√
4	XRF	EDX3000B	2025/06/22	√

***** END OF REPORT *****