



中国认可
国际互认
检测
TESTING
CNAS L6478



TEST REPORT

Report No. : WTF24F04088945C

Applicant..... : Mid Ocean Brands B.V.

Address..... : 7/F., Kings Tower, 111 King Lam Street, Cheung Sha
Wan, Kowloon, Hong Kong

Manufacturer : 111652

Sample Name : Backpack with USB

Sample Model..... : MO9439

Test Requested : Refer to next page (s)

Test Method..... : Refer to next page (s)

Test Conclusion : Refer to next page (s)

Date of Receipt sample : 2024-04-19

Testing period : 2024-04-19 to 2024-04-25

Date of Issue..... : 2024-04-26

Test Result..... : Refer to next page (s)

Prepared By:

Waltek Testing Group (Foshan) Co., Ltd.

Address: No.13-19, 2/F., 2nd Building, Sunlink Machinery City, Xingye 4 Road, Guanglong Industrial
Park, Chihua Neighborhood Committee, Chencun Town, Shunde District, Foshan, Guangdong, China
Tel:+86-757-23811398 Fax:+86-757-23811381 E-mail:info@waltek.com.cn

Signed for and on behalf of
Waltek Testing Group (Foshan) Co., Ltd.

Swing Liang

Swing.Liang



WTF24F04088945C



Report No.: WTF24F04088945C Job No.: FSW2024041977630CJ

Summary:

Test Requested	Test Conclusion
In accordance with the RoHS Directive 2011/65/EU and its amendment (EU) No. 2015/863, to determine the 10 restricted substances content in the submitted sample.	Pass (Please refer to next pages for details)

Sample Photo(s):



**Test Results:****1. Lead, Mercury, Cadmium, Hexavalent Chromium, PBBs and PBDEs**

Test method:

- 1) With reference to IEC 62321-2:2021, disassembly, disjunction and mechanical sample preparation
- 2) With reference to IEC 62321-3-1:2013, screening –Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry
- 3) With reference to IEC 62321-4:2013+AMD1:2017 CSV, determination of Mercury by ICP-OES
- 4) With reference to IEC 62321-5:2013, determination of Lead and Cadmium by ICP-OES
- 5) With reference to IEC 62321-7-2: 2017 and IEC 62321-7-1: 2015, determination of Hexavalent Chromium by UV-Vis
- 6) With reference to IEC 62321-6:2015, determination of PBBs and PBDEs by GC-MS

Part No.	Part Description	Result of XRF					Result of Wet Chemical Testing (mg/kg)
		Cd	Pb	Hg	Cr	Br	
1	Black plastic shell	BL	BL	BL	BL	BL	NA
2	Black plastic wire jacket	BL	BL	BL	BL	BL	NA
3	Black plastic jacket(USB plug)	BL	BL	BL	BL	BL	NA
4	Black plastic jacket(USB socket)	BL	BL	BL	BL	BL	NA
5	White plastic core(USB socket)	BL	BL	BL	BL	IN	PBBs : ND PBDEs : 13
6	Golden metal pin(USB socket)	BL	BL	BL	BL	--	NA
7	Silvery metal shell(USB socket)	BL	BL	BL	BL	--	NA
8	Solder(USB socket)	BL	BL	BL	BL	--	NA
9	Silvery metal shell(USB plug)	BL	BL	BL	BL	--	NA
10	White plastic core(USB plug)	BL	BL	BL	BL	BL	NA
11	Golden metal pin(USB plug)	BL	BL	BL	BL	--	NA
12	Solder(USB plug)	BL	BL	BL	BL	--	NA
13	Blue plastic wire covering	BL	BL	BL	BL	BL	NA
14	Black plastic wire covering	BL	BL	BL	BL	BL	NA
15	Green plastic wire covering	BL	BL	BL	BL	BL	NA



Part No.	Part Description	Result of XRF					Result of Wet Chemical Testing (mg/kg)
		Cd	Pb	Hg	Cr	Br	
16	Red plastic wire covering	BL	BL	BL	BL	BL	NA
17	Coppery metal wire	BL	BL	BL	BL	--	NA

Remark:

- (1) Results are obtained by EDXRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-VIS (for Cr⁶⁺) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1: 2013 (unit: mg/kg)

Element	Polymer	Metal	Composite Materials
Cd	$BL \leq (70-3\sigma) < IN < (130+3\sigma) \leq OL$	$BL \leq (70-3\sigma) < IN < (130+3\sigma) \leq OL$	$LOD < IN < (150+3\sigma) \leq OL$
Pb	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < IN < (1500+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < IN < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < IN < (1500+3\sigma) \leq OL$
Cr	$BL \leq (700-3\sigma) < IN$	$BL \leq (700-3\sigma) < IN$	$BL \leq (500-3\sigma) < IN$
Br	$BL \leq (300-3\sigma) < IN$	--	$BL \leq (250-3\sigma) < IN$

BL= Below Limit

OL= Over Limit

LOD = Limit of Detection

-- = Not Regulated

- (2) "IN" expresses the inconclusive region, and further chemical testing to confirm whether it complies with the requirement of RoHS Directive.
- (3) The XRF screening test for RoHS elements – the reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) mg / kg =milligram per kilogram=ppm, $\mu\text{g}/\text{cm}^2$ = Micrograms per square centimetre.
- (5) ND = Not Detected or lower than limit of quantitation.
- (6) NA = Not Applicable, as the XRF screening test result was below the limit or as the XRF screening directly determine that test result was over the limit, it was not need to conduct the wet chemical testing.
- (7) LOQ = Limit of quantitation.

Test Items	Pb	Cd	Hg	Cr ⁶⁺		PBB	PBDE
Units	mg/kg	mg/kg	mg/kg	mg/kg	$\mu\text{g}/\text{cm}^2$	mg/kg	mg/kg
LOQ	2	2	2	8	0.1	5	5

The LOQ for single compound of PBBs and PBDEs is 5 mg/kg, LOQ of Cr⁶⁺ for polymer and composite sample is 8 mg/kg and LOQ of Cr⁶⁺ for metal sample is 0.1 $\mu\text{g}/\text{cm}^2$.



Report No.: WTF24F04088945C

Job No.: FSW2024041977630CJ

(8) RoHS Requirement

Restricted Substances	Limits
Cadmium (Cd)	0.01% (100 mg/kg)
Lead (Pb)	0.1% (1000 mg/kg)
Mercury (Hg)	0.1% (1000 mg/kg)
Chromium (VI) (Cr ⁶⁺)	0.1% (1000 mg/kg)
Polybrominated Biphenyls (PBBs)	0.1% (1000 mg/kg)
Polybrominated Diphenyl Ethers (PBDEs)	0.1% (1000 mg/kg)

- (9) According to IEC 62321-7-1:2015, determined of Cr⁶⁺ on metal sample by boiling water extraction test method, and result is shown as Positive/Negative.

Boiling water extraction:

Negative = Absence of Cr⁶⁺ coating, the detected concentration in boiling water extraction solution is less than 0.10 ug/cm².

Positive = Presence of Cr⁶⁺ coating, the detected concentration in boiling water extraction solution is greater than 0.13 ug/cm².

Information on storage conditions and production date of the tested sample is unavailable and thus Cr⁶⁺ results represent status of the sample at the time of testing.

(10) Abbreviation:

"Pb" denotes Lead, "Cd" denotes Cadmium, "Hg" denotes Mercury, "Cr" denotes Chromium, "Cr (VI)" denotes Hexavalent Chromium, "Br" denotes Bromine, "PBBs" denotes Total Polybrominated Biphenyls, "PBDEs" denotes Total Polybrominated Diphenyl Ethers.

2. Phthalates:

Test method:

With reference to IEC 62321-8:2017, determination of Phthalates content by GC-MS.

Serial No.	Part No.	Result (mg/kg)			
		DBP	BBP	DEHP	DIBP
T01	1+2+3 [△]	281	ND	ND	ND
T02	4+5+10 [△]	ND	ND	ND	ND
T03	6	--	--	--	--
T04	7	--	--	--	--
T05	8	--	--	--	--
T06	9	--	--	--	--
T07	11	--	--	--	--
T08	12	--	--	--	--
T09	13+14 [△]	169	ND	ND	ND
T10	15+16 [△]	164	ND	ND	ND
T11	17	--	--	--	--

Note:

- (1) mg/kg = milligram per kilogram= ppm
(2) ND = Not Detected or lower than limit of quantitation.
(3) -- = Not Regulated.



- (4) LOQ = Limit of quantitation.

Test Items	DBP	BBP	DEHP	DIBP
Units	mg/kg	mg/kg	mg/kg	mg/kg
LOQ	50	50	50	50

- (5) Abbreviation:


“DBP” denotes Dibutyl phthalate, “BBP” denotes Benzyl butyl phthalate (BBP), “DEHP” denotes Bis(2-ethylhexyl)-phthalate, “DIBP” denotes Diisobutyl phthalate, “PHT” denotes Phthalates.


- (6) RoHS requirement

Restricted Substances	Limits
Dibutyl phthalate (DBP)	0.1% (1000 mg/kg)
Benzyl butyl phthalate (BBP)	0.1% (1000 mg/kg)
Di(2-ethylhexyl) phthalate (DEHP)	0.1% (1000 mg/kg)
Di-iso-butyl phthalate (DIBP)	0.1% (1000 mg/kg)

- (7) “△”= As client’s requirement, the testing was conducted based on mixed components. Results are calculated by the minimum weight of mixed components.

Measurement Flowchart:



**Photograph(s) of parts tested:****Remarks:**

1. The results shown in this test report refer only to the sample(s) tested;
2. This test report cannot be reproduced, except in full, without prior written permission of the company;
3. The report would be invalid without specific stamp of test institute and the signatures of compiler and approver;
4. The Applicant name and Address, the sample(s) and sample information was/were provided by the applicant who should be responsible for the authenticity which Waltek hasn't verified;
5. If the report is not stamped with the accreditation recognized seal, it will only be used for scientific research, education, and internal quality control activities, and is not used for the purpose of issuing supporting data to the society.
6. The sample material information (Model No. information) is provided by client, not verified by test laboratory. The samples of reference Model No. are not tested. Test laboratory not responsible for the accuracy, appropriateness, completeness and authenticity of the information provided by client.

===== End of Report =====