

Test Report

Report No. : AGC05443231028-001

SAMPLE NAME : LCD writing tablet

MODEL NAME : MO9537

APPLICANT: MID OCEAN BRANDS B.V

STANDARD(S) : Please refer to the following page(s).

DATE OF ISSUE : Oct. 30, 2023

Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd.





Report No.: AGC05443231028-001

pplicant : MID OCEAN BRANDS B.V

Address : 7/F, Kings Tower, 111 King Lam Street, Cheung Sha Wan, Kowloon, Hong Kong. Test Site : 5,6/F., Building 2, Sanwei Chaxi Industrial Park, Sanwei Community, Hangcheng

Street, Bao'an District, Shenzhen, Guangdong, China

Report on the submitted sample(s) said to be:

Sample Name : LCD writing tablet

Model : MO9537
Vendor code : 106613
Country of Origin : CHINA
Country of Destination : EUROPE
Labeled Age Grading : Not stated

Requested Age Grading : 3+
Age Group Applied in : 3+

Testing

Sample receiving state : Normal Sample Received Date : Oct. 19, 2023

Testing Period : Oct. 19, 2023 to Oct. 30, 2023

Test Requested : Selected test(s) as requested by client.

Approved by : Jessie liang

Liangdan, Jessie.Liang

Technical Director



Conclusion

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Pass

European Standard on Safety of Toys

- EN 71-1:2014+A1:2018: Mechanical and Physical Properties

Pass

European Standard on Safety of Toys

- EN 71-2:2020: Flammability

Pass

The Directive 2009/48/EC-Safety of Toys

- Labeling requirement (Washing/Cleaning Label, CE mark, importer / manufacturer mark (name, address), product identification)

Pass

European Standard on Safety of Toys

- EN 71-3:2019+A1:2021: Migration of Certain Elements (Al, Sb, As, Ba, B, Cd, Cr(III), Cr(VI), Co, Cu, Pb, Mn, Hg, Ni, Se, Sr, Sn, Zn)

Pass

European Standard on Safety of Toys

- EN 71-3:2019+A1:2021: Migration of Certain Elements (Organic Tin)

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Pass

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 5

- Benzene Content

Pass




Report Revise Record


Report No.: AGC05443231028-001	
--------------------------------	--

Report Version	Issued Date	Valid Version	Notes
/	Oct. 30, 2023	Valid	Initial release



The photo of the sample







The photo of AGC05443231028-001 is for use only with the original report.

Test Point Description

escription						
Test module	Test parts	Test point description				
LCD writing tablet Model: M09537						
		Black plastic sheet				
	Display panel	White plastic sheet				
		Conductive tape				
		Black plastic frame				
		Black plastic shell				
		Silver screw				
		PCB				
7		Solder				
	T4 C:4-1	Transparent tape				
	Tact Switch	Metallic shrapnel				
		Chip capacitor				
Circuit board		Chip resistor				
		Chip diode				
		IC body				
		Metallic pin with solder				
		Black magnetic frame				
	Battery chip	Metallic sheet				
		Black plastic pen				
		Black plastic sheet				
		Black plastic frame				
		Black plastic shell				
		Black plastic pen				
		Black plastic shell+Black plastic pen				
	Test module g tablet Model : Mo	Test module Test parts gtablet Model: M09537				

Note: "---" = The test point exists alone in the sample and is not attached to the test module or test parts.



Note: N.D.=Not Detected (less than method detection limit), MDL = Method Detection Limit, 1mg/kg=0.0001%

2011/65/EU (RoHS) and its amendment directive (EU) 2015/863

- Pb, Cd, Hg, Cr⁶⁺, PBBs, PBDEs, DBP, BBP, DEHP, DIBP

Test Item	Test Method/ Instrument	MDL	Maximum Limit
Lead (Pb)		/	1000mg/kg
Cadmium (Cd)		/	100mg/kg
Mercury (Hg)	IEC 62321-3-1:2013/ XRF	/	1000mg/kg
Total Chromium		/	/
Total Bromine		/	/
Chemistry Method		L	
Lead (Pb)	IEC 62321-5:2013/ ICP-OES	2mg/kg	1000mg/kg
Cadmium (Cd)	IEC 62321-5:2013/ ICP-OES	2mg/kg	100mg/kg
Mercury (Hg)	IEC 62321-4: 2013+A1:2017/ ICP-OES	2mg/kg	1000mg/kg
Non-metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-2:2017/ UV-Vis	8mg/kg	1000mg/kg
Metal: Hexavalent Chromium (Cr ⁶⁺)	IEC 62321-7-1:2015/ UV-Vis	0.1μg/cm ²	/
-Monobromobiphenyl (MonoBB) -Dibromobiphenyl (DiBB) -Tribromobiphenyl (TriBB) -Tetrabromobiphenyl (TetraBB) -Pentabromobiphenyl (PentaBB) -Hexabromobiphenyl (HexaBB) -Heptabromobiphenyl (HeptaBB) -Octabromobiphenyl (OctaBB) -Nonabromodiphenyl (NonaBB) -Decabromodiphenyl (DecaBB)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
PolybrominatedDiphenylethers (PBDEs) -Monobromodiphenyl ether (MonoBDE) -Dibromodiphenyl ether (DiBDE) -Tribromodiphenyl ether (TriBDE) -Tetrabromodiphenyl ether (TetraBDE) -Pentabromodiphenyl ether (PentaBDE) -Hexabromodiphenyl ether (HexaBDE) -Heptabromodiphenyl ether (HeptaBDE) -Octabromodiphenyl ether (OctaBDE) -Nonabromodiphenyl ether (NonaBDE) -Decabromodiphenyl ether (DecaBDE)	IEC 62321-6:2015/ GC-MS	Single 5mg/kg	Sum 1000mg/kg
Di-iso-butyl phthalate (DIBP)		50mg/kg	1000mg/kg
Dibutyl phthalate (DBP)		50mg/kg	1000mg/kg
Butylbenzyl phthalate (BBP)	IEC 62321-8:2017/ GC-MS	50mg/kg	1000mg/kg
Di-(2-ethylhexyl) Phthalate (DEHP)		50mg/kg	1000mg/kg



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231028-0 Conclusion
]	Pb	BL	/	
	(Cd	BL	/	
		Hg	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DI	ЕНР	N/A	N.D.	
]	Pb	BL	/	
		Cd	BL	/	
	I	Hg	BL	/	
		Cr ⁶⁺)	BL	/	
2	Br	PBBs PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
		Pb	BL	/	
	(Cd	BL	/	
	I	Hg	BL	/	
		Cr ⁶⁺)	BL	/	
3	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
	DBP		N/A	N.D.	†
		BP	N/A	N.D.	
	DEHP		N/A	N.D.	1
		Pb	BL	/	
		Cd	BL	/	
	I	Hg	BL	/	
		Cr ⁶⁺)	BL	/	
4	Br	PBBs PBDEs	BL	/	Conformity
	D	IBP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
			N/A	N.D.	
	DEHP		1 V / F 1	IN.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	P b	BL	/	
	Cd		BL	/	
	F	Ig	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
<u></u>		PBBs	DI	/	G C :
5	Br	PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	B	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	P b	BL	/	
	(Cd	BL	/	
	H	Ig	BL	/	
		Cr ⁶⁺)	BL	/	
_		PBBs		/	
6	Br	Br PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	1
		Pb	BL	/	
	Cd		BL	/	
	Hg		BL	/	
	Cr(Cr ⁶⁺)		BL	/	
7	Br	PBBs PBDEs	BL	/	Conformity
	DI	BP	N/A	N.D.	
		BP	N/A	N.D.	
			N/A	N.D.	
	BBP DEHP		N/A	N.D.	
		Pb	BL	/	
		Cd Cd	BL	/	
		Ig	BL	/	
		Cr^{6+})	BL	/	
-		PBBs		/	
8	Rr —	PBDEs	N/A	/	Conformity
-	וח	BP	N/A	/	
-		BP	N/A	/	
		BP	N/A N/A	/	
-		EHP	N/A N/A	/	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	C05443231028-0
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
		(Cr^{6+})	BL	/	
9	Br	PBBs	BL	/	Conformity
_	Di	PBDEs	DL	/	Comorning
		IBP	N/A	N.D.	
	Ι	DBP	N/A	N.D.	
	F	BBP	N/A	N.D.	
	D	ЕНР	N/A	N.D.	
		Pb	BL	/	
		Cd	BL	/	
		Hg	BL	/	
	Cr	(Cr^{6+})	IN	N.D.	
10	Br	PBBs PBDEs	N/A	/	Conformity
	DIBP		N/A	/	
-	DBP		N/A	/	
	BBP		N/A	/	
	DEHP		N/A	/	
		Pb	BL	/	
	Cd		BL	/	
-	Hg		BL	/	
-		(Cr^{6+})	BL	/	
11	Br	PBBs	BL	/	Conformity
-	DIBP PBDEs		27/4	/	
-			N/A	N.D.	 -
-		OBP OBP	N/A	N.D.	
-	BBP		N/A	N.D.	
		EHP	N/A	N.D.	
-		Pb	BL	/	
-		Cd	BL	/	
		Hg	BL	/	
-	Cr	(Cr^{6+})	BL	/	
12	Br PBBs	BL	/	Conformity	
		PBDEs		/	Comomity
		IBP	N/A	N.D.	
)BP	N/A	N.D.	
<u> </u>		BBP	N/A	N.D.	
	D	EHP	N/A	N.D.	



Test point	Test	Item	X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	Pb		BL	/	
	(Cd	BL	/	
	I	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
12	D	PBBs	DI	/	G 6 '
13	Br	PBDEs	BL	/	Conformity
	Dl	BP	N/A	N.D.	
	D	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DE	ЕНР	N/A	N.D.	
	F	P b	BL	/	
	(Cd	BL	/	
	I	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
1.4	Br	PBBs	DI	/	
14		PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	DBP		N/A	N.D.	
	BBP		N/A	N.D.	
	DEHP		N/A	N.D.	
	F	P b	IN	45	
	Cd		BL	/	
	ŀ	Ig	BL	/	
	Cr(Cr ⁶⁺)	BL	/	
15	Br	PBBs PBDEs	N/A	/	Conformity
	Dl	BP	N/A	/	
	DBP BBP	BP	N/A	/	
		N/A	/		
	DEHP		N/A	/	
	Pb	BL	/		
		Cd	BL	/	
	Hg		BL	/	1
		Cr ⁶⁺)	BL	/	
16	Br	PBBs PBDEs	BL	/	Conformity
	Dl	BP	N/A	N.D.	
		BP	N/A	N.D.	
		BP	N/A	N.D.	
		EHP	N/A	N.D.	



Test point	Test Item		X-ray Fluorescence Spectrometry (XRF) mg/kg	Wet Chemistry Method mg/kg	Conclusion
	F	'b	BL	/	
	C	Cd .	BL	/	
	Н	[g	BL	/	
	Cr(0	Cr ⁶⁺)	IN	N.D.	
17	D.,	PBBs	NI/A	/	C C :
17	Br	PBDEs	N/A	/	Conformity
	DIBP	BP	N/A	/	
	DBP		N/A	/	
	BBP	BP	N/A	/	
	DEHP		N/A	/	
	F	'b	BL	/	
	Cd		BL	/	
	Н	[g	BL	/	
	Cr(0	Cr ⁶⁺)	BL	/	
18	D.,	PBBs	DI	/	C C : -
18	Br	PBDEs	BL	/	Conformity
	DIBP		N/A	N.D.	
	D:	BP	N/A	N.D.	
	В	BP	N/A	N.D.	
	DF	НР	N/A	N.D.	

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>N/A</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	N/A	BL≤250-3σ <x< td=""></x<>

Remark:

- (1) BL= Below Limit, OL= Over limited, IN = Inconclusive, Scanning by XRF and detected by chemical method, N/A = Not applicable.
- (2) Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value.
- (3) The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.
- (4) Boiling-water-extraction:(X represents the results of the tested sample)

Number Colorimetric result (Cr(VI) concentration)	Judgement
---	-----------



 Report No.: AGC05443231028-001

 1
 $X < 0.1 \mu g/cm^2$ Negative

 2
 $0.1 \mu g/cm^2 \le X \le 0.13 \mu g/cm^2$ Uncertainty

 3
 $X > 0.13 \mu g/cm^2$ Positive

Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

(5) Disclaimers: This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes. The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

European Standard on Safety of Toys

- EN 71-1:2014+A1:2018: Mechanical and Physical Properties

Clause	Description	Result
4	GENERAL REQUIREMENTS	Pass
4.1	Material cleanliness	Pass
4.2	Assembly	N/A
4.3	Flexible plastics sheeting	N/A
4.4	Toy bags	N/A
4.5	Glass	N/A
4.6	Expanding materials	N/A
4.7	Edges	Pass
4.8	Points and metallic wires	Pass
4.9	Protruding parts	N/A
4.10	Parts moving against each other	N/A
4.10.1	Folding and sliding mechanisms	N/A
4.10.2	Driving mechanisms	N/A
4.10.3	Hinges	N/A
4.10.4	Springs	N/A
4.11	Mouth-actuated toys and other toys intended to be put in the mouth	N/A
4.12	Balloons	N/A
4.13	Cords of toy kites and other flying toys	N/A
4.14	Enclosures	N/A
4.14.1	Toys which a child can enter	N/A
4.14.2	Masks and helmets	N/A
4.15	Toys intended to bear the mass of a child	N/A
4.15.1	Toys propelled by a child or by other means	N/A
4.15.1.1	General	N/A
4.15.1.2	Warnings and instructions for use	N/A
4.15.1.3	Strength	N/A
4.15.1.4	Stability	N/A



	Report No.: AGC034	
4.15.1.5	Braking	N/A
4.15.1.6	Transmission and wheel arrangement	N/A
4.15.1.7	Adjustable seat pillar and handlebar stem minimum insertion marks	N/A
4.15.1.8	Electrically-driven ride-on toys	N/A
4.15.2	Toy bicycles	N/A
4.15.2.1	General	N/A
4.15.2.2	Warnings and instructions for use	N/A
4.15.2.3	Braking requirements	N/A
4.15.3	Rocking horses and similar toys	N/A
4.15.4	Toys not propelled by a child	N/A
4.15.5	Toy scooters	N/A
4.15.5.1	General	
4.15.5.2	Warnings and instructions for use	N/A
4.15.5.3	Strength	N/A
4.15.5.4	Adjustable and folding steering tubes	N/A
4.15.5.5	Braking	N/A
4.15.5.6	Wheel size	N/A
4.15.5.7	Protruding parts	N/A
4.16	Heavy immobile toys	N/A
4.17	Projectiles	N/A
4.17.1	General	
4.17.2	All projectiles	N/A
4.17.2.1	Leading parts	N/A
4.17.2.2	Foam shaft projectiles with a suction cup as a leading part	N/A
4.17.2.3	Other types of projectile with a suction cup as a leading part	N/A
4.17.3	Projectile toys with stored energy	N/A
4.17.3.1	Energy limitation	N/A
4.17.3.2	Edges	N/A
4.17.3.3	Projectiles with a protective cap, cover or tip	N/A
4.17.3.4	Impact resistance	N/A
4.17.3.5	Improvised projectiles	N/A
4.17.4	Certain projectile toys without stored energy	N/A
4.17.4.1	Darts	N/A
4.17.4.2	Bows and arrows	N/A
4.17.4.3	Toy catapults and projectiles propelled by an elastic band	N/A
4.17.4.4	Projectile toys without stored energy where the discharge mechanism can store energy,	N/A
4.10	only when held in place by the user	NT/A
4.18	Aquatic toys and inflatable toys	N/A
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	N/A
4.20	Acoustics Taylor containing a new electrical heat gayree	N/A
4.21	Toys containing a non-electrical heat source	N/A
4.22	Small balls	N/A
4.23	Magnets	N/A
4.23.1	General Control of the control of th	 >T/A
4.23.2	Toys other than magnetic/electrical experimental sets intended for children over 8 years	N/A
4.23.3	Magnetic/electrical experimental sets intended for children over 8 years	N/A
4.24	Yo-yo balls	N/A
4.25	Toys attached to food	N/A
4.26	Toy Disguise Costumes	N/A
4.27	Flying toys	N/A
4.27.1	General	N/A
4.27.2	Rotors and propellers on flying toys	N/A



4.27.2	Report No.: AGCOS-	
4.27.3	Rotors and propellers on remote controlled flying toys	N/A N/A
5.1	TOYS INTENDED FOR CHILDREN UNDER 36 MONTHS	N/A N/A
5.2	General requirements Filling materials	N/A N/A
5.3	Plastic sheeting	N/A N/A
5.4	Cords, chains and electrical cables in toys	N/A N/A
5.4.1	General	
5.4.2		N/A
5.4.2.1	Cords and chains in toys intended for children under 18 months	N/A N/A
5.4.2.2	Cords and chains with the potential to tangle Two cords or chains with the potential to tangle	N/A N/A
5.4.2.3	Separated cords and chains	N/A N/A
5.4.2.4	Free length of cords and chains	N/A
5.4.2.4	Cords and chains in toys intended for children of 18 months or over but under 36 months	N/A N/A
-		N/A
5.4.3.1 5.4.3.2	Cords and chains with the potential to tangle Two cords or chains with the potential to tangle	N/A N/A
	Separated cords and chains	N/A
5.4.3.3	1	N/A N/A
5.4.3.4	Free length of cords and chains	
5.4.3.5	Cords and chains not suitable for children under 18 months	N/A
5.4.4	Fixed loops, tangled loops and nooses	N/A
5.4.5	Cords and chains on pull along toys	N/A
5.4.6	Electrical cables	N/A
5.4.7	Cross-sectional dimension of certain cords	N/A
5.4.8	Self-retracting cords	N/A
5.4.9	Toys attached to or intended to be strung across a cradle, cot or perambulator	N/A
5.4.9.1	Toys intended to be strung across a cradle, cot or perambulator	N/A
5.4.9.2	Toys otherwise intended to be attached to a cradle, cot or perambulator	N/A
5.5	Liquid-filled toys	N/A
5.6	Speed limitation of electrically driven toys	N/A
5.7	Glass and porcelain	N/A
5.8	Shape and size of certain toys	N/A
5.9	Toys comprising monofilament fibres	N/A
5.10	Small balls	N/A
5.11	Play figures	N/A
5.12	Hemispheric-shaped toys	N/A
5.13	Suction cups	N/A
5.14	Straps intended to be worn fully or partially around the neck	N/A
5.15	Sledges with cords for pulling	N/A
6	PACKAGING	N/A
7	Warnings, markings and instructions for use	N/A
7.1	General	N/A
7.2	Toys not intended for children under 36 months	N/A
7.3	Latex balloons	N/A
7.4	Aquatic toys	N/A
7.5	Functional toys	N/A
7.6	Hazardous sharp functional edges and points	N/A
7.7	Projectile toys	N/A
7.8	Imitation protective masks and helmets	N/A
7.9	Toy kites	N/A
7.10	Roller skates, inline skates, skateboards and certain other ride-on toys	N/A
7.10.1	Roller skates, inline skates and skateboards	N/A
7.10.2	Ride-on toys without a braking device	N/A
7.10.3	Electrically-driven ride-on toys	N/A



7.10.4	Instructions for use	N/A
7.11	Toys intended to be strung across a cradle, cot, or perambulator	N/A
7.12	Liquid-filled teethers	N/A
7.13	Percussion caps specifically designed for use in toys	N/A
7.14	Acoustics	N/A
7.15	Toy bicycles	N/A
7.16	Toys intended to bear the mass of a child	N/A
7.17	Toys comprising monofilament fibres	N/A
7.18	Toy scooters	N/A
7.19	Rocking horses and similar toys	N/A
7.20	Magnetic/electrical experimental sets	N/A
7.21	Toys with electrical cables exceeding 300 mm in length	N/A
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	N/A
7.23	Toys intended to be attached to a cradle, cot or perambulator	N/A
7.24	Sledges with cords for pulling	N/A
7.25	Flying toys	N/A
7.25.1	Flying toys	N/A
7.25.2	Remote controlled flying toys	N/A
7.26	Improvised projectiles	N/A

European Standard on Safety of Toys

- EN 71-2:2020: Flammability

Clause	Requirements	Result
4	Requirements	Pass
4.1	General	Pass
4.2	Toys to be worn on the head	N/A
4.2.1	General	
4.2.2	Beards, moustaches, wigs, etc, made from hair, pile or material with similar features (e.g. freehanging ribbons, paper or cloth strands), which protrude more than or equal to 50 mm from the surface of the toy	N/A
4.2.3	Beards, moustaches, wigs etc. made from hair, pile or material with similar features (e.g. freehanging ribbons, paper or cloth strands etc.), which protrude less than 50 mm from the surface of the toy	N/A
4.2.4	Full or partial moulded head masks	N/A
4.2.5	Flowing elements of toys to be worn on the head (except those covered by 4.2.2 and 4.2.3), hoods, head-dresses etc. and fabric masks which partially or fully cover the head, but excluding those items covered by 4.3	N/A
4.3	Toys disguise costumes and other toys intended to be worn by a child in play	N/A
4.4	Toys intended to be entered by a child	N/A
4.5	Soft Filled Toys (animals and dolls, etc) with a piled or textile surface	N/A



The Directive 2009/48/EC-Safety of Toys

- Labeling requirement (Washing/Cleaning Label, CE mark, importer / manufacturer mark (name, address),

Report No.: AGC05443231028-001

product identification)

	On product	On packaging	
Washing/Cleaning instruction	N/A	N/A	
CE marking	Absent	Present	
Manufacturer's name	Absent	Absent	
Manufacturer's address	Absent	Absent	
Importer's name	Absent	Present	
Importer's address	Absent	Present	
Sample ID	Absent	Present	

Remark 1:

Washing/Cleaning label: According to Directive 2009/48/EC the following safety requirements apply regarding cleaning and washing: A toy intended for use by children under 36 months must be designed and manufactured in such a way that it can be cleaned. A textile toy must, to this end, be washable, except if it contains a mechanism that may be damaged if soak washed. The toy must fulfill the safety requirements also after having been cleaned in accordance with this point and the manufacturer's instructions. The manufacturer should, if applicable, provide instructions on how the toy has to be cleaned.

Remark 2:

Toys made available on the market must bear the CE marking. The CE marking must be subject to the general principles set out in Article 30 of Regulation (EC) No 765/2008. The CE marking must be affixed visibly, legibly and indelibly to the toy, to an affixed label or to the packaging. In the case of small toys and toys consisting of small parts, the CE marking may alternatively be affixed to a label or an accompanying leaflet. Where, in the case of toys sold in counter displays, that is not technically possible, and on condition that the counter display was originally used as packaging for the toy, the CE marking may be affixed to the counter display. Where the CE marking is not visible from outside the packaging, if any, it shall as a minimum be affixed to the packaging. Where specific legislation does not impose specific dimensions, the CE marking must be at least 5 mm high.

Remark 3

The manufacturer's name, registered trade name or registered trade mark and the address at which the manufacturer can be contacted must be indicated on the toy or, where that is not possible, on its packaging or in a document accompanying the toy. This requirement applies also to the name and address etc. of any importer

Remark 4:

Manufacturers must ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.

Note

Per the client's requirement, the testing age grading is over 3 years of age

Evaluation only performed on the artwork, no practical packaging evaluated

N/A=Not Applicable; N/T=Not Tested; DNI = Did Not Ignite; IBSE = Ignite But Self-Extinguished; --=No judgement required

European Standard on Safety of Toys

- EN 71-3:2019+A1:2021: Migration of Certain Elements (Al, Sb, As, Ba, B, Cd, Cr(III), Cr(VI), Co, Cu, Pb, Mn,

Report No.: AGC05443231028-001

Hg, Ni, Se, Sr, Sn, Zn)

Test Methods and Equipment: EN 71-3:2019+A1:2021; ICP-OES

Test Items(s)	T Init	Limit	MDI	Test Result(s)		
Test Item(s)	Unit	Limit	MDL	1-1	1-4	
Aluminium(Al)	mg/kg	28130	50	N.D.	N.D.	
Antimony(Sb)	mg/kg	560	2.0	N.D.	N.D.	
Arsenic(As)	mg/kg	47	0.5	N.D.	N.D.	
Barium(Ba)	mg/kg	18750	50	N.D.	N.D.	
Boron(B)	mg/kg	15000	50	N.D.	N.D.	
Cadmium(Cd)	mg/kg	17	0.3	N.D.	N.D.	
Chromium (III) (Cr(III))	mg/kg	460	0.2	N.D.	N.D.	
Chromium (VI) (Cr(VI))	mg/kg	0.053	0.005	N.D.	N.D.	
Cobalt(Co)	mg/kg	130	2.5	N.D.	N.D.	
Copper(Cu)	mg/kg	7700	50	N.D.	N.D.	
Lead(Pb)	mg/kg	23	0.25	N.D.	N.D.	
Manganese(Mn)	mg/kg	15000	50	N.D.	N.D.	
Mercury(Hg)	mg/kg	94	1.0	N.D.	N.D.	
Nickel(Ni)	mg/kg	930	10	N.D.	N.D.	
Selenium(Se)	mg/kg	460	5	N.D.	N.D.	
Strontium(Sr)	mg/kg	56000	50	N.D.	N.D.	
Tin(Sn)	mg/kg	180000	50	N.D.	N.D.	
Zinc(Zn)	mg/kg	46000	50	N.D.	N.D.	
Co	Conformity	Conformity				

Tost Itam(s)	Unit	Limit	MDL	Test Result(s)		
Test Item(s)	Ollit	Lillit	MIDL	1-5	1-18	
Aluminium(Al)	mg/kg	28130	50	N.D.	N.D.	
Antimony(Sb)	mg/kg	560	2.0	N.D.	N.D.	
Arsenic(As)	mg/kg	47	0.5	N.D.	N.D.	
Barium(Ba)	mg/kg	18750	50	N.D.	N.D.	
Boron(B)	mg/kg	15000	50	N.D.	N.D.	
Cadmium(Cd)	mg/kg	17	0.3	N.D.	N.D.	
Chromium (III) (Cr(III))	mg/kg	460	0.2	9	N.D.	
Chromium (VI) (Cr(VI))	mg/kg	0.053	0.005	N.D.	N.D.	
Cobalt(Co)	mg/kg	130	2.5	N.D.	N.D.	
Copper(Cu)	mg/kg	7700	50	N.D.	N.D.	
Lead(Pb)	mg/kg	23	0.25	N.D.	N.D.	
Manganese(Mn)	mg/kg	15000	50	N.D.	N.D.	
Mercury(Hg)	mg/kg	94	1.0	N.D.	N.D.	
Nickel(Ni)	mg/kg	930	10	N.D.	N.D.	
Selenium(Se)	mg/kg	460	5	N.D.	N.D.	
Strontium(Sr)	mg/kg	56000	50	N.D.	N.D.	
Tin(Sn)	mg/kg	180000	50	N.D.	N.D.	
Zinc(Zn)	mg/kg	46000	50	N.D.	N.D.	
Co	Conclusion					



Migration of Certain Elements: Permissible Limit for Different Materials (Unit: mg/kg)

Item	Category III In scraped-off toy material	Category II In liquid or sticky toy material	Category I In dry, brittle, powder-like or pliable toy material	
Aluminium (Al)	28130	560	2250	
Antimony (Sb)	560	11.3	45	
Arsenic (As)	47	0.9	3.8	
Barium (Ba)	18750	375	1500	
Boron (B)	15000	300	1200	
Cadmium (Cd)	17	0.3	1.3	
Chromium III(Cr(III))	460	9.4	37.5	
Chromium VI (Cr(VI))	0.053	0.005	0.02	
Cobalt (Co)	130	2.6	10.5	
Copper (Cu)	7700	156	622.5	
Lead (Pb)	23	0.5	2.0	
Manganese (Mn)	15000	300	1200	
Mercury (Hg)	94	1.9	7.5	
Nickel (Ni)	930	18.8	75	
Selenium (Se)	460	9.4	37.5	
Strontium (Sr)	56000	1125	4500	
Tin (Sn)	180000	3750	15000	
Zinc (Zn)	46000	938	3750	

Note:

- 1. "-" = If less than 0,010 g of toy material can be obtained, it is not required to analyse.
- 2. "*" = For accessible glass, metal and ceramic toys or toy parts, if they are not small parts, the soluble test is not required.

European Standard on Safety of Toys

- EN 71-3:2019+A1:2021: Migration of Certain Elements (Organic Tin)

Test Methods and Equipment: EN 71-3:2019+A1:2021; GC-MS

Tost Itam(s)	Unit	I imit	MDL	Test Result(s)		
Test Item(s)	Onit	Limit	MDL	1-1	1-4	
Organic Tin	mg/kg	12	0.15	N.D.	N.D.	
Con	Conformity	Conformity				



Tost Itam(a)	Unit	Limit	MDI	Test Result(s)		
Test Item(s)		Lillit	MDL	1-5	1-18	
Organic Tin	mg/kg	12	0.15	N.D.	N.D.	
Co	Conformity	Conformity				

Migration of Certain Elements: Permissible Limit for Different Materials (Unit: mg/kg)

Item Category III In scraped-off toy material		Category II In liquid or sticky toy material	Category I In dry, brittle, powder-like or pliable toy material	
Organic Tin	12	0.2	0.9	

Note:

- 1. "-" = If less than 0.010 g of toy material can be obtained, it is not required to analyse.
- 2. "*" = For accessible glass, metal and ceramic toys or toy parts, if they are not small parts, the soluble test is not required.
- 3. Migration of organic tin is expressed as tributyl tin cation content in mg/kg.

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 51&52

- Phthalates Content

Test Methods and Equipment: IEC 62321-8:2017; GC-MS

Test Item(s)	Unit	Limit	Limit MDL	Test Result(s)			
rest item(s)	Om	LIIIII	MIDL	1-1	1-4	1-5+1-18	
Diisobutyl phthalate (DIBP) CAS:84-69-5	%	0.1	0.005	N.D.	N.D.	N.D.	
Dibutyl phthalate (DBP) CAS:84-74-2	%	0.1	0.005	N.D.	N.D.	N.D.	
Butylbenzyl phthalate (BBP) CAS:85-68-7	%	0.1	0.005	N.D.	N.D.	N.D.	
Di-(2-ethylhexyl) Phthalate (DEHP) CAS:117-81-7	%	0.1	0.005	N.D.	N.D.	N.D.	
Di-n-octyl phthalate (DNOP) CAS:117-84-0	%	/	0.005	N.D.	N.D.	N.D.	
Di-isononyl phthalate (DINP) CAS:28553-12-0, 68515-48-0	%	/	0.005	N.D.	N.D.	N.D.	
Di-isodecyl phthalate(DIDP) CAS:26761-40-0, 68515-49-1	%	/	0.005	N.D.	N.D.	N.D.	
Sum of DIBP +DBP+BBP+DEHP	%	0.1	/	N.D.	N.D.	N.D.	
Sum of DNOP+DINP+DIDP	%	0.1	/	N.D.	N.D.	N.D.	
Con	Conclusion						

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5+1-18



Limit requirements of Phthalates

Report No.: AGC05443231028-001

Toys and childcare articles		Each of DEHP, DBP, BBP, DIBP is less than 0.1% or the sum of DEHP+DBP+BBP+DIBP is less than 0.1%		
	Toys and childcare articles which can be placed in the	The sum of DINP+DIDP+DNOP is less than 0.1%		

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 50

- Polycyclic-aromatic Hydrocarbons (PAHs) Content

Test Methods and Equipment: Afps GS 2019:01 PAK; GC-MS

Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-1	1-4	1-5+1-18
Benzo[a]pyrene(BaP)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Benzo[e]pyrene(BeP)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Benzo[a]anthracene(BaA)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Benzo[b]fluoranthene(BbF)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Benzo[j]fluoranthene(BjFA)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Benzo[k]fluoranthene(BkF)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Chrysene(CHR)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Dibenzo[a,h]anthracene(DBA)	mg/kg	0.5	0.1	N.D.	N.D.	N.D.
Conclusion				Conformity	Conformity	Conformity

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5+1-18

Limit requirements of Polycyclic-aromatic Hydrocarbons (PAHs) (Unit: mg/kg)

Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Benzo[a]pyrene(BaP)	50-32-8	≤ 1	≤ 1	≤ 0.5
Benzo[e]pyrene(BeP)	192-97-2	/	≤ 1	≤ 0.5
Benzo[a]anthracene(BaA)	56-55-3	/	≤ 1	≤ 0.5
Benzo[b]fluoranthene(BbF)	205-99-2	/	≤ 1	≤ 0.5
Benzo[j]fluoranthene(BjFA)	205-82-3	/	≤ 1	≤ 0.5
Benzo[k]fluoranthene(BkF)	207-08-9	/	≤ 1	≤ 0.5



Items	CAS No.	Extender oils or used for the production of tyres or parts of tyres	Any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity	Toys, including activity toys, and childcare articles, any of their rubber or plastic components that come into direct as well as prolonged or short-term repetitive contact with the human skin or the oral cavity
Chrysene(CHR)	218-01-9	/	≤1	≤ 0.5
Dibenzo[a,h]anthracene(DBA)	53-70-3	/	≤ 1	≤ 0.5
Sum of BaP+ BeP+ BaA+ BbF+ BjFA+ BkF+ CHR+ DBA	/	≤ 10	/	/

Annex XVII of the REACH Regulation (EC) No 1907/2006, entry 5

- Benzene Content


Test Methods and Equipment: EPA 3550C:2007 & EPA 8260D:2018; GC-FID


Test Item(s)	Unit	Limit	MDL	Test Result(s)		
				1-1	1-4	1-5+1-18
Benzene	mg/kg	5	5	N.D.	N.D.	N.D.
Con	Conformity	Conformity	Conformity			

Remark:

1. As specified by client, the submitted samples were mixed to test, the test points: 1-5+1-18


Test Flow Chart of XRF









Test Flow Chart of Phthalates









Test Flow Chart of Hexavalent Chromium (Cr6+)








Test Flow Chart of Lead, Cadmium and Mercury





These sample were dissolved totally by pre-conditioning method according to above flow chart






Test Flow Chart of Migration of Certain Elements









Test Flow Chart of Migration of Certain Elements (Organic Tin)









Test Flow Chart of Phthalates









Test Flow Chart of Polycyclic-aromatic Hydrocarbons (PAHs)







Test Flow Chart of Monoaromatic Hydrocarbons





Conditions of Issuance of Test Reports

- 1. All samples and goods are accepted by the Attestation of Global Compliance (Shenzhen) Std & Tech Co., Ltd. (the "Company") solely for testing and reporting in accordance with the following terms and conditions. The company provides its services on the basis that such terms and conditions constitute express agreement between the company and any person, firm or company requesting its services (the "Clients").
- 2. Any report issued by Company as a result of this application for testing services (the "Report") shall be issued in confidence to the Clients and the Report will be strictly treated as such by the Company. It may not be reproduced either in its entirety or in part and it may not be used for advertising or other unauthorized purposes without the written consent of the Company. The Clients to whom the Report is issued may, however, show or send it, or a certified copy thereof prepared by the Company to its customer, supplier or other persons directly concerned. The Company will not, without the consent of the Clients, enter into any discussion or correspondence with any third party concerning the contents of the Report, unless required by the relevant governmental authorities, laws or court orders.
- 3. The Company shall not be called or be liable to be called to give evidence or testimony on the Report in a court of law without its prior written consent, unless required by the relevant governmental authorities, laws or court orders.
- 4. In the event of the improper use of the report as determined by the Company, the Company reserves the right to withdraw it, and to adopt any other additional remedies which may be appropriate.
- 5. Samples submitted for testing are accepted on the understanding that the Report issued cannot form the basis of, or be the instrument for, any legal action against the Company.
- 6. The Company will not be liable for or accept responsibility for any loss or damage however arising from the use of information contained in any of its Reports or in any communication whatsoever about its said tests or investigations. 7. Clients wishing to use the Report in court proceedings or arbitration shall inform the Company to that effect prior to submitting the sample for testing.
- 8. The Company is not responsible for recalling the electronic version of the original report when any revision is made to them. The Client assumes the responsibility to providing the revised version to any interested party who uses them.
- 9. Subject to the variable length of retention time for test data and report stored hereinto as otherwise specifically required by individual accreditation authorities, the Company will only keep the supporting test data and information of the test report for a period of six years. The data and information will be disposed of after the aforementioned retention period has elapsed. Under no circumstances shall we provide any data and information which has been disposed of after retention period. Under no circumstances shall we be liable for damage of any kind, including (but not limited to) compensatory damages, lost profits, lost data, or any form of special, incidental, indirect, consequential or punitive damages of any kind, whether based on breach of contract of warranty, tort (including negligence), product liability or otherwise, even if we are informed in advance of the possibility of such damages.

*** End of Report ***